At 31 December 2022



## 8 March 2023

# Increases in Mineral Resources and Ore Reserves from Exploration Success

# **Highlights**

- Mineral Resources increased by 1.7 million ounces (Moz) to 11.2 Moz of gold, net of depletion
- Ore Reserves have increased by 0.6 Moz to 4.6 Moz, net of depletion
- Syama Mineral Resources increased significantly following exploration success at Syama North
- Mineral Resources at Syama North increased to 3.2 Moz and Ore Reserves increased to 854 koz, with 10% (85koz) of oxide material
- Further 126 koz of Mineral Resources at Syama Underground converted to Ore Reserves due to improved mining productivities
- Mako Ore Reserves and Mineral Resources reduced in line with mining depletion

Resolute Mining Limited (ASX/LSE: RSG, Resolute or the Company) is pleased to announce the Company's Annual Ore Reserve and Mineral Resource Statement at 31 December 2022.

Ore Reserves have increased to 4.6 Moz of gold and Mineral Resources have increased to 11.2 Moz of gold after accounting for the effects of mining depletion, improved productivities underground and exploration success.

A detailed breakdown of the Company's Ore Reserves and Mineral Resources at 31 December 2022 representing the Syama and Mako operations is presented in the tables below. The 2022 Annual Ore Reserve Statement is included at Table 3 of this announcement and the 2022 Annual Mineral Resource Statement is included at Table 4.

At 31 December 2022 Resolute's direct share of Ore Reserves was 3.8 Moz and Mineral Resources of 9.1 Moz.

The exploration success at Syama North has added 2 million ounces of gold to the Mineral Resource this year and added 850,000oz to the Ore Reserve

All tonnes and grade information have been rounded to reflect the relative uncertainty of the estimate, small differences may be present in the totals.

Resolute's Chief Executive Officer, Mr Terry Holohan, commented:

"The continued success of the drilling program at Syama North over the second half of 2022 exceeded our expectations. The drill rigs are still turning on this contiguous strike discovery of over 6km which remains open at depth. At this stage the 850 koz of Syama North Ore Reserves focus only on the widest sections of the A21 pit, thus we expect further updates later this year as in-fill drilling continues delineating additional economic mineralisation. It is also worth noting that the 10% oxides delineated at Syama North now represent some of the highest grades of oxides at Syama such that they will get processing preference once mining starts in earnest.

"I am extremely proud of the 31 December 2022 Mineral Resource and Ore Reserve Statement, which incorporates these significant additions to our business, demonstrating our exploration team's achievements.

Also due to recent sustainable efficiency improvements at the Syama underground operation over 2022, the Company was able to convert a further 126 koz of the existing Mineral Resource Estimate to Ore Reserves.

At 31 December 2022



"The company now turns its focus to the Syama North pre-feasibility study (PFS), which is intended to be the first step in exploiting the sulphide reserve, due for publication in the middle of 2023. Significant additions to our Mineral Resources and Ore Reserves, such as Syama North clearly demonstrate that the Syama Belt is surprisingly under-explored and justifies the need for further exploration work to be undertaken along the prospective >85 km of strike."



## Table 1: Ore Reserves (100% Basis)

Ore reserves		Proved		P	robable			Total	
As at December 2022	Tonnes (000s)	g/t	oz (000s)	Tonnes (000s)	g/t	oz (000s)	Tonnes (000s)	g/t	oz (000s)
Syama	2,880	1.6	148	46,226	2.7	3,964	49,106	2.6	4,112
Mako	4,558	1.2	173	4,948	2.2	348	9,506	1.7	520
Managed Ore Reserves	7,438	1.3	320	51,174	2.6	4,312	58,613	2.5	4,633

Ore Reserves as at 31 December 2022 on a 100% basis total 4.6 Moz after mining depletion with the increase coming from the new reserve at Syama North.

In Mali, the Ore Reserves at the Syama Gold Mine (Syama) increased due to an expansion in the Ore Reserves at Syama North. Overall 40% of the Measured and Indicated Mineral Resources were converted into Ore Reserves. We expect the Ore Reserve to increase this year as we continue to convert Inferred Resources to the Indicated category. Exploration success at Syama North in 2022 led to a significant increase in Mineral Resources after completing intensive drilling programs throughout the year. The large increase in Measured and Indicated Mineral Resources led to a substantial increase in Ore Reserves at Syama North to 10.6 million tonnes (Mt) at 2.5g/t Au for 854,000oz. Drilling is continuing at Syama North with the expectation of significant increases in the Ore Reserves during the year.

Underground Ore Reserves at Syama only decreased slightly as inventory increases in the cave flow modelling, due to productivity improvements offset mining depletion reductions.

Ore Reserves at the Mako Gold Mine (Mako) decreased in line with mining depletion.

Resolute's asset ownership is 80% of Syama (Mali Government 20%), 90% of Tabakoroni (Mali Government 10%), 90% of Mako (Senegalese Government 10%). As such, the Company's fully attributable Ore Reserves position net government interests, is 3.8 Moz of gold.

The chart below presents the proposed pit design at A21 in Long Section.





# Table 2: Mineral Resources (100% Basis)

Mineral Resources	Me	easure	d	In	dicate	d	h	nferred		Total F	Resour	ces
As at December 2022	Tonnes (000s)	g/t	oz (000s)	Tonnes (000s)	g/t	oz (000s)	Tonnes (000s)	g/t	oz (000s)	Tonnes (000s)	g/t	oz (000s)
Syama	25,603	3.2	2,645	58,834	2.9	5,570	39,207	1.8	2,265	123,644	2.6	10,481
Mako	4,955	1.1	177	8,458	1.8	487	682	0.9	19	14,095	1.5	683
Managed Mineral Resources	30,558	2.9	2,823	67,293	2.8	6,057	39,888	1.8	2,284	137,739	2.5	11,164

Mineral Resources (inclusive of Ore Reserves) at 31 December 2022, on a 100% basis, contain 11.2 Moz of gold. The Company's fully attributable Mineral Resources position, net of government interests is 9.1 Moz of gold.

In Senegal, the Mineral Resources at Mako decreased in line with mining depletion. At Syama the Mineral Resources increased significantly in 2022 following the addition of 2 Moz discovered at Syama North during the year.

The highly successful drilling programs in 2021 and 2022 at Syama North have outlined a company significant Mineral Resource which has the potential to transform the mining operation at Syama. During 2022 the Syama North Mineral Resource increased to 34Mt @ 2.9g/t Au for 3.2 Moz an increase of 2 Moz.

#### Syama North Plan view:





## **Table 3: Ore Reserves Statement**

		Proved			Probable	1		Total			
Ore Reserves As at December 2022	Tonnes (000s)	g/t	oz (000s)	Tonnes (000s)	g/t	oz (000s)	Tonnes (000s)	g/t	oz (000s)	oz (000s)	
Mali										80%	
Syama Underground	0	0.0	0	25,500	2.6	2,094	25,500	2.6	2,094	1,675	
Syama Stockpiles	707	2.0	46	1,817	1.3	78	2,523	1.5	124	99	
Sub Total (Sulphides)	707	2.0	46	27,317	2.5	2,172	28,023	2.5	2,218	1,774	
Syama Satellite Deposits	164	2.2	11	12,367	2.5	975	12,530	2.4	987	789	
Stockpiles (satellite deposits)	881	1.3	38	1,403	1.0	43	2,284	1.1	81	65	
Sub Total Satellite Deposits	1,045	1.5	49	13,770	2.3	1,018	14,815	2.2	1,067	854	
										90%	
Tabakoroni Underground	0	0.0	0	5,028	4.7	766	5,028	4.7	766	689	
Tabakoroni Open Pit	48	1.9	3	222	1.7	12	270	1.7	15	13	
Tabakoroni Satellite Deposits	0	0.0	0	0	0.0	0	0	0.0	0	0	
Tabakoroni Stockpiles	1,080	1.4	50	0	0.0	0	1,080	1.4	50	45	
Sub Total Tabakoroni	1,129	1.5	53	5,250	4.6	778	6,378	4.1	831	748	
Mali Total	2,880	1.6	148	46,226	2.7	3,964	49,106	2.6	4,112	3,373	
Senegal										90%	
Mako	697	2.0	44	4,948	2.2	348	5,645	2.2	392	353	
Mako Stockpiles	3,861	1.0	128	0	0.0	0	3,861	1.0	128	115	
Senegal Total	4,558	1.2	173	4,948	2.2	348	9,506	1.7	520	468	
Total Ore Reserves	7,438	1.3	320	51,174	2.6	4,312	58,613	2.5	4,633	3,841	

Notes:
 Mineral Resources include Ore Reserves.
 All tonnes and grade information have been rounded to reflect relative uncertainty of the estimate, small differences may be present in the totals.
 Syama Underground mine planning is based on a shut-off grade of 2g/t.
 Syama Satellite Reserves are reported above 0.8g/t cut-off.
 Tabakoroni Underground Reserves are reported above 0.8g/t cut-off.
 Tabakoroni Satellite Reserves are reported above 0.8g/t cut-off.
 Mako Reserves are reported above 0.9g/t cut-off.



## **Table 4: Mineral Resources Statement**

	Меа	sure	d	Ind	icated	d	In	ferred		Total R	esouro	es	Group Share
Mineral Resources As at December 2022	Tonnes (000s)	g/t	oz (000s)	Tonnes (000s)	g/t	oz (000s)	Tonnes (000s)	g/t	oz (000s)	Tonnes (000s)	g/t	oz (000s)	oz (000s)
Mali													80%
Syama Underground	21,235	3.5	2,362	25,920	3.0	2,483	1,359	2.6	112	48,514	3.2	4,957	3,966
Stockpiles (sulphide)	707	2.0	46	1,771	1.3	75	0	0.0	0	2,478	1.5	120	96
Sub Total (Sulphides)	21,942	3.4	2,408	27,691	2.9	2,558	1,359	2.6	112	50,992	3.1	5,077	4,062
Satellite Deposits	1,748	2.5	141	24,102	2.8	2,135	19,156	2.6	1,604	45,006	2.7	3,880	3,104
Stockpiles (satellite deposits)	739	1.6	38	1,657	1.0	52	46	1.1	2	2,442	1.2	91	73
Sub Total Satellite Deposits	2,487	2.2	179	25,759	2.6	2,187	19,202	2.6	1,606	47,448	2.6	3,972	3,177
Old Tailings	0	0.0	0	0	0.0	0	17,000	0.7	365	17,000	0.7	365	292
													90%
Tabakoroni Open Pit	33	3.9	4	205	5.0	33	1	6.0	0	239	4.9	38	34
Tabakoroni Underground	6	3.5	1	5,179	4.8	792	1,644	3.5	182	6,829	4.4	976	878
Tabakoroni Satellite Deposits	190	2.0	12	0	0.0	0	0	0.0	0	190	2.0	12	11
Tabakoroni Stockpiles	945	1.4	42	0	0.0	0	0	0.0	0	945	1.4	42	38
Sub Total Tabakoroni	1,174	1.6	59	5,384	4.8	826	1,646	3.5	183	8,204	4.0	1,067	960
Mali Total	25,603	3.2	2,645	58,834	2.9	5,570	39,207	1.8	2,265	123,644	2.6	10,481	8,492
Senegal													90%
Mako	1,103	1.6	56	8,458	1.8	487	682	0.9	19	10,243	1.7	561	505
Mako Stockpiles	3,852	1.0	121	0	0.0	0	0	0.0	0	3,852	1.0	121	109
Senegal Total	4,955	1.1	177	8,458	1.8	487	682	0.9	19	14,095	1.5	683	614
Total Mineral Resources	30,558	2.9	2,823	67,293	2.8	6,057	39,888	1.8	2,284	137,739	2.5	11,164	9,106

Notes:

Notes:
 Mineral Resources include Ore Reserves.
 All tonnes and grade information have been rounded to reflect relative uncertainty of the estimate, small differences may be present in the totals.
 Resources are reported above 1.0g/t cut-off for the Syama North.
 Resources for the SLC at Syama is reported within an MSO shape generated at 1.3g/t and south of the SLC within an MSO shape generated at 1.5g/t.
 Resources for the Cashew NE, Paysans, Tellem and Porphyry Zone (Splay) are reported above a cut-off of 1.0g/t.
 Resources for the Tabakoroni Open Pit are reported above a cut-off of 1.0g/t and within a US\$2,000 optimised shell.
 Resources are reported above a cut-off of 0.5g/t and within a US\$2,000 optimised shell.



## **Summary of Mineral Resource Parameters**

A summary of JORC Table 1 is provided below for compliance regarding the Mineral Resources reported within and in-line with the requirements of ASX Listing Rule 5.8.1. There has been a material change to Syama Satellite Mineral resource as detailed in the ASX release dated January 2023. Syama Mineral Resources increased significantly following exploration success at Syama North.

## Geology and geological interpretation

The Syama Project is found on the northern margin of the Achaean-Proterozoic Leo Shield which forms the southern half of the West African Craton. The project area straddles the boundary between the Kadiana–Madinani terrane and the Kadiolo terrane. The Kadiana-Madinani terrane is dominated by greywackes and a narrow belt of interbedded basalt and argillite. The Kadiolo terrane comprises polymictic conglomerate and sandstone that were sourced from the Kadiana-Madinani terrane and deposited in a late- to syntectonic basin.

Prospects are centred on the NNE striking, west dipping, Syama-Bananso Fault Zone and Birimian volcanosedimentary units of the Syama Formation.

#### Sampling and sub-sampling techniques

Diamond core has been sampled at 1m intervals and cut in half to obtain a 2-4kg sample.

Reverse circulation samples were collected on 1m intervals by riffle split (dry) or by scoop (wet) to obtain a 2-4kg sample (Syama) or 1-3kg sample.

Sample preparation for diamond core and RC samples includes oven drying, crushing to 10mm and splitting, pulverising to 85% passing -75um. These preparation techniques are deemed to be appropriate to the material and element being sampled.

Drill core coarse duplicates were split by the laboratory after crushing at a rate of 1:20 samples. Reverse circulation field duplicates were collected by the company at a rate of 1:20 samples.

#### Drilling techniques

Drill types used include diamond core of HQ and NQ sizes. Core is oriented at 3m down hole intervals using a Reflex Act II RD Orientation Tool and more recently using a Reflex north seeking gyro instrument.

#### **Classification criteria**

Mineral Resources were classified in accordance with the Australasian Code for the Reporting of Exploration Results, Mineral Resources and Ore Reserves (JORC, 2012).

The deposit has been classified as Measured, Indicated, and Inferred Mineral Resource based on a combination of quantitative and qualitative criteria which include geologic continuity, confidence in volume models, data quality, sample spacing, lode continuity, and estimation parameters (number of informing composites, estimation pass number, kriging quality parameters, and minimum and average distance composites).

The Measured portion of the Resource was defined using areas populated on the first estimation pass, within 20m of informing composites; the kriging efficiency and slope of regression were generally >=0.7; and high confidence exists in lode continuity (strike and thickness).

The Indicated portion of the Resource was defined using areas populated on the first two estimation passes within 50m of informing composites; the kriging efficiency and slope of regression were generally >=0.7; and moderate to high confidence exists in lode continuity (strike and thickness).

Mineralisation that not classified by the above parameters has been classified as Inferred.

The input data is comprehensive in its coverage and does not favour or misrepresent the in situ mineralisation. The definition of the mineralised zones is based on a high level of geologic understanding from good quality



sample data, producing models of continuous mineralised lodes. Validation of the block model shows good correlation of the input data to the block estimated grades.

The Mineral Resource estimate appropriately reflects the view of the Competent Person

#### Sample analysis method

All samples were dispatched to ALS Bamako for gold analysis by 30g fire assay fusion with AAS instrument finish (method code Au-AA25). Over-range results were re-analysed and reported by 30g fire assay fusion with gravimetric finish (method code Au-GRA21). The analytical method was appropriate for the style of mineralisation.

No geophysical tools were used to determine elemental concentrations.

Quality control (QC) procedures included the use of certified standards (1:40), non-certified sand blanks (1:40), diamond core coarse duplicates (1:20) and reverse circulation field duplicates (1:20).

Laboratory quality control data, including laboratory standards, blanks, duplicates, repeats, grind size results and sample weights were also captured into the digital database.

Analysis of the QC sample assay results indicates that an acceptable level of accuracy and precision has been achieved.

#### Estimation methodology

Estimation of gold grade has been completed using Ordinary Kriging (OK).

The deposit mineralisation has been constrained by wireframes constructed using a combination of downhole gold assay and associated lithological logging. These lode wireframes have been used to define domain codes used for estimation. The drillholes have been flagged with the domain code and composited using the domain code to segregate the data.

Domain boundary analysis has been undertaken, with hard boundaries used for all domains.

Drillholes have been composited to 1m intervals using Leapfrog Geo 2021.2.5 with residual lengths distributed evenly across all composites. There are no residual samples.

The influence of extreme gold assays has been reduced by top-cutting across selected domains. Top-cuts have been determined using a combination of log probability, log histogram, and mean-variance plots. Top-cuts have been reviewed and applied to the composites on a domain-by-domain basis.

Variography has been determined using Datamine Supervisor v.8.14 software using top-cut values. Where there is insufficient data in individual domains to generate meaningful variograms, domains have been grouped, or variograms borrowed from other similar domains.

Drillhole data spacing ranges from 10m spacing in areas of dense drilling to approximately 100m spacing in sparsely drilled, deeper areas.

The block model parent block size is 5m (X) by 10m (Y) by 5m (Z) with sub-blocks down to 0.3125m (X) by 0.625m (Y) by 0.3125m (Z), with the sub-blocks estimated at the scale of the parent block. The block size is considered appropriate for the drillhole spacing throughout the deposit.

Grade estimation has been completed in three passes:

Pass 1 estimation has been undertaken using a minimum and maximum number of sample composites (determined using Datamine Supervisor v.8.14 KNA tool) into a search ellipsoid with dimensions equal to half the variogram range of the domain.

Pass 2 estimation has been undertaken with the same minimum/maximum samples as Pass 1 into a search ellipsoid twice the first pass.

Pass 3 estimation has been undertaken with a minimum of 4 samples, and the same maximum number of samples as the first two passes into a search ellipsoid twice the second pass



A four drillhole limit has been applied to the passes.

Previous Mineral Resource estimates are comparable in size and scope when considering the additional extensional drilling included in the current estimate.

The Mineral Resource estimate has been validated using visual validation tools, mean grade comparisons between the block model and declustered composite grade means, and swath plots comparing the input composite grades and the block model grades by Northing, Easting, and RL

No selective mining units are assumed in the estimate. There will be no by-products recovered from mining. No additional or deleterious elements have been estimated. The model focuses on interpreting mineralisation beneath existing open pits. Historical reconciliation data is incomplete and has not been used.

#### Basis for selected cut-off grade

A cut-off grade of 1.0 g/t Au has been used for construction of mineralised wireframes, based on mining parameters of the nearby Syama and Tabakoroni deposits.

#### Mining and metallurgical methods and other material modifying factors

Extensive metallurgical investigations and reporting have been completed prior to the commencement of mining and milling at the nearby Syama deposit.

The processing method involves crushing, milling, flotation and roasting, followed by conventional CIL recovery.

There is no evidence to suggest that the metallurgical characteristics of ore extracted from Syama North would change from that encountered at Syama.

## **Summary of Ore Reserve Parameters**

A summary of JORC Table 1 is provided below in Appendix for compliance regarding the Ore Reserves reported within and in-line with the requirements of ASX Listing Rule 5.9.1. There has been a material change to the Syama North Satellite Reserve; i.e, change in tonnes, grades, rock type (Oxide; Transistional and Fresh).

#### Material assumptions and the outcomes of the [preliminary] feasibility study

The Syama North deposit consist of A21, Beta, Alpha & Ba04 pits.

Feasibility Studies were completed for mining of Northern satellite deposits in 2009, and mining of satellite pits has been occurring since then. Recent drilling in Syama North has identified a significant resource in sulphide, spread across the Syama North region, an extension to the known oxide deposit. Additional drilling was completed targeting the A21 area and the resource model was updated in Dec 22 with additional information. Overall, 40% of the Measured and Indicated Mineral Resources were converted into Ore Reserves. Infill drilling is ongoing, and we expect the Ore Reserve to increase this year as we convert Inferred Resources to Indicated category.

Pit was reoptimized using the new resource model and redesigned to match the latest optimisation. All Reserves were declared as Probable as more test works and drilling is ongoing to firm up the modifying factors (geotechnical inputs).



The work undertaken to date has addressed all material Modifying Factors required for the conversion of a Mineral Resources estimate into an Ore Reserve estimate and has shown material change where there is a significant increase in Measured and Indicated Mineral Resources. As a result, Ore Reserves at Syama North increases to 10.6 million tonnes (Mt) at 2.5g/t Au for 854,000oz. Drilling is continuing at Syama North with the expectation of significant increases in the Ore Reserves during the year.

## **Classification criteria**

The Ore Reserves are based on the Mineral Resource estimate detailed in the ASX release dated January 2023.

Proved and Probable Ore Reserves were declared based on the Measured and Indicated Mineral Resources. None of the Measured Mineral Resource was converted to Proven Ore Reserves as the PFS study for plant expansion is underway and drilling is ongoing to firm up the geotechnical inputs.

## Mining methodology

Mining is planned to be undertaken by conventional open pit methods of drill and blast, followed by load and haul. The Ore from Syama North will be trucked to Syama and treated through Syama Processing plant.

Detailed pit design work was completed based on pit optimisations result. Only Measured and Indicated Resources were used in the pit optimisation.

#### **Processing method**

Metallurgical test work was conducted on multiple samples. The tests indicated that, similarly to the Syama ore. The processing of the ore will be similar to that of the Syama sulphide circuit which has been in operation for several years and is well understood, consisting of the following stages:

- Crushing and grinding utilising the existing oxide process plant infrastructure
- · Gravity gold recovery utilising the existing oxide gravity circuit
- Flotation to produce a sulphide rich concentrate
- Concentrate thickening
- Roasting, followed by calcine quench and wash
- Carbon-in-leach (CIL)
- Tailings disposal

A total gold recovery of 86%, 80% and 78%, has been assumed for Oxide, Transistional and Fresh Material respectively, based on test results to date. This is in line with similar ore being processed at Syama.

#### Basis for selected cut-off grade

The mill cut-off grade is used for Reserve Reporting. It is the derived from the long-term gold price, processing cost, mining dilution, royalty and selling costs. The above-mentioned economic parameters are the same as in the Financial Model 2022

#### **Estimation methodology**

The reported Ore Reserve estimates for Syama North are based on pit optimisations conducted using the Lerchs-Grossman (LG) algorithm utilizing the NPV Scheduler and reviewed in Whittle to calculate the optimal pit at specific input parameters and pit designs. Costs are based on existing contract mining and haulage rates and site costs which are understood with a high degree of accuracy.

Detailed pit design work was completed based on pit optimisations result. Only Measured and Indicated Resources were used in the pit optimisation.

Overall slope angles are dependent on rock type; approximately 34° for Oxide, 38° for Transisitional and 50° for Fresh as recommended by Geotechnical consultants and operational experience in mining other similar pits in same region.



A 5% dilution and 10 % mining loss factor applied. All Inferred material is treated as waste and is excluded from Reserve Reporting.

Inferred Mineral Resources are not included in the pit optimisation and pit design. A mining and production schedule were completed with Inferred Mineral Resource treated as waste. As a result, the conversion of Inferred Mineral Resource to processed product is not required for the overall financial viability of the project.

## Material modifying factors

Detailed pit design work was completed based on pit optimisations result. Only Measured and Indicated Resources were used in the pit optimisation.

Overall slope angles are dependent on rock type; approximately 34° for Oxide, 38° for Transistional and 50° for Fresh as recommended by Geotechnical consultants and operational experience in mining other similar pits in same region.

A 5% dilution and 10 % mining loss factor applied. The Dilution and mining loss assumptions are derived from the reconciliation results at Syama. All Inferred material is treated as waste and is excluded from Reserve Reporting.

The Syama North pits are located within approximately 8km of Syama. Ore is trucked to Syama where it is processed at Syama. General and administration costs are shared between the oxide plant and the sulphide plant. As part of ongoing operations, capital and operating budgets are prepared from first principles and considering existing contractual agreements.

The processing plant produces gold doré (without problematic deleterious elements) that is subsequently refined offsite. Refining costs are not material.

A gold price of US\$1,500/oz formed the basis of the Ore Reserves

Exchange rates used for planning purposes are from consensus forecasts provided by external corporate advisers.

Ad valorem Government royalties of 6% are payable on gold production.

No penalties are incurred, nor is any revenue received from co-products.



## **Competent Persons Statement**

The information in this announcement that relates to data quality, geological interpretation and Mineral Resource estimation for the various projects unless specified in the list below is based on information compiled by Bruce Mowat, a Competent Person who is a Member of the Australian Institute of Geoscientists and a full-time employee of Resolute Corporate Services Pty Ltd, a wholly-owned subsidiary of Resolute Mining Limited. Mr Mowat has sufficient experience that is relevant to the styles of mineralisation and type of deposits under consideration and to the activity being undertaken as a Competent Person as defined in the 2012 Edition of the "Australasian Code for Reporting of Exploration Results, Mineral Resources and Ore Reserves" (JORC Code 2012). Mr Mowat consents to the inclusion in this announcement of the material compiled by him in the form and context in which it appears.

The information in this statement that relates to the Mineral Resources and Ore Reserves listed below is based on information and supporting documents prepared by the Competent Person identified. Each person specified in the list has sufficient experience which is relevant to the style of mineralisation and type of deposit under consideration and to the activity, which has been undertaken to qualify as a Competent Person as defined in the JORC Code 2012.

Mr Ndjibu and Mr Patani are full-time employees of Resolute Corporate Services Pty Ltd, a wholly-owned subsidiary of Resolute Mining Limited. Mr Johnson is a full-time employee of MPR Geological Consultants Pty Ltd.

Mr Osiejak is a full-time employee of Cube Consulting Pty Ltd. Ms Havlin is an employee of Snowden Optiro Pty Ltd. Each person identified in the list below consents to the inclusion in this announcement of the material compiled by them in the form and context in which it appears.

Activity	Competent Person	Membership Institution
Syama Resource	Patrick Smillie	Society for Mining, Metallurgy & Exploration
Syama Reserve	Gito Patani	Australasian Institute of Mining and Metallurgy
Syama North Resource	Patrick Smillie	Society for Mining, Metallurgy & Exploration
Syama North Reserves	Kitwa Ndjibu	Australasian Institute of Mining and Metallurgy
Syama Tailings Facility	Susan Havlin	Australasian Institute of Mining and Metallurgy
Tabakoroni OP Resource	Susan Havlin	Australasian Institute of Mining and Metallurgy
Tabakoroni OP Reserves	Kitwa Ndjibu	Australasian Institute of Mining and Metallurgy
Tabakoroni UG Resource	Susan Havlin	Australasian Institute of Mining and Metallurgy
Tabakoroni UG Reserves	Gito Patani	Australasian Institute of Mining and Metallurgy
Tellem Resource	Nic Johnson	Australian Institute of Geoscientists
Tellem Reserves	Kitwa Ndjibu	Australasian Institute of Mining and Metallurgy
Cashew NE Resource	Bruce Mowat	Australian Institute of Geoscientists
Cashew NE Reserves	Kitwa Ndjibu	Australasian Institute of Mining and Metallurgy
Paysans Resource	Nic Johnson	Australian Institute of Geoscientists
Paysans Reserves	Kitwa Ndjibu	Australasian Institute of Mining and Metallurgy
Porphyry Zone Resource	Bruce Mowat	Australian Institute of Geoscientists
Porphyry Zone Reserves	Kitwa Ndjibu	Australasian Institute of Mining and Metallurgy
Mako Resources – In Situ	Marcus Osiejak	Australasian Institute of Mining and Metallurgy
Mako Resources – Stockpiles	Bruce Mowat	Australian Institute of Geoscientists
Mako Reserves	Kitwa Ndjibu	Australasian Institute of Mining and Metallurgy



## **Cautionary Statement about Forward-Looking Statements**

This announcement contains certain "forward-looking statements" including statements regarding our intent, belief or current expectations with respect to Resolute's business and operations, market conditions, results of operations and financial condition, and risk management practices. The words "likely", "expect", "aim", "should", "could", "may", "anticipate", "predict", "believe", "plan", "forecast" and other similar expressions are intended to identify forward-looking statements. Indications of, and guidance on, future earnings, anticipated production, life of mine and financial position and performance are also forward-looking statements. These forward-looking statements involve known and unknown risks, uncertainties and other factors that may cause Resolute's actual results, performance and achievements or industry results to differ materially from any future results, performance or achievements, or industry results, expressed or implied by these forwardlooking statements. Relevant factors may include (but are not limited to) changes in commodity prices, foreign exchange fluctuations and general economic conditions, increased costs and demand for production inputs. the speculative nature of exploration and project development, including the risks of obtaining necessary licences and permits and diminishing quantities or grades of reserves, political and social risks, changes to the regulatory framework within which Resolute operates or may in the future operate, environmental conditions including extreme weather conditions, recruitment and retention of personnel, industrial relations issues and litigation.

Forward-looking statements are based on Resolute's good faith assumptions as to the financial, market, regulatory and other relevant environments that will exist and affect Resolute's business and operations in the future. Resolute does not give any assurance that the assumptions will prove to be correct. There may be other factors that could cause actual results or events not to be as anticipated, and many events are beyond the reasonable control of Resolute. Readers are cautioned not to place undue reliance on forward-looking statements, particularly in the current economic climate with the significant volatility, uncertainty and disruption caused by the COVID-19 pandemic. Forward-looking statements in this document speak only at the date of issue. Except as required by applicable laws or regulations, Resolute does not undertake any obligation to publicly update or revise any of the forward-looking statements or to advise of any change in assumptions on which any such statement is based. Except for statutory liability which cannot be excluded, each of Resolute, its officers, employees and advisors expressly disclaim any responsibility for the accuracy or completeness of the material contained in these forward-looking statements and excludes all liability whatsoever (including in negligence) for any loss or damage which may be suffered by any person as a consequence of any information in forward-looking statements or any error or omission.

## **About Resolute**

Resolute Mining (ASX/LSE: RSG) is an African gold miner, developer and explorer with more than 30 years of experience across Australia and Africa. To date, the company has produced over nine million ounces of gold. It currently operates the Syama Gold Mine in Mali and the Mako Gold Mine in Senegal. Resolute's gold production and cost guidance for FY2023 is 350,000oz at an All-In Sustaining Cost of \$1,480/oz.

Through all its activities, sustainability is the core value at Resolute. This means that protecting the environment, providing a safe and productive working environment for employees, uplifting host communities, and practising good corporate governance are non-negotiable priorities. Resolute's commitment to sustainability and good corporate citizenship has been cemented through its adoption of and adherence to the Responsible Gold Mining Principles (RGMPs). This framework, which sets out clear expectations for consumers, investors, and the gold supply chain as to what constitutes responsible gold mining, is an initiative of the World Gold Council of which Resolute has been a member since 2017. The Company is on track to reach full compliance with the RGMPs in 2023.

At 31 December 2022



For further information, contact:

#### Resolute

James Virgo, GM Finance and Investor Relations contact@rml.com.au +61 8 9261 6100

## **Corporate Broker**

Jennifer Lee, Berenberg +44 20 3753 3040

## **Public Relations**

Jos Simson / Emily Moss, Tavistock resolute@tavistock.co.uk +44 207 920 3150 / +44 7788 554 035

Authorised by Mr Terry Holohan, Managing Director and Chief Executive Officer



## **APPENDIX**

Ore Reserves Comparison to 31 December 2021 Reserves and Resources comply with the Australasian Code for Reporting of Mineral Resources and Reserves (The JORC Code 2004 and JORC Code 2012).

			Dec-22					Dec-21	0		
	Tonnes	Gold	Ounces	Group Share	Group Share	Tonnes	Gold grade	Ounces	Group Share	Group Share	
	(000s)	(a/t)	(000s)	%	Ounces	(000s)	(a/t)	(000s)	%	Ounces	
Ore Reserves	(0000)		Proved			(0000)	(3.4)	Proved		Com	- ment on Changes
Mali											
Syama Stockpiles (Sulphide)	707	2.0	46	80%	37	760	1.8	44	80%	35	Movement in operating stockpiles
Syama North	0	0.0	0	80%	0	793	1.8	46	80%	37	New Reserve (A21, Ba01N, Ba04, Alpha)
Stockpiles (Oxide)	881	1.3	38	80%	30	768	1.5	38	80%	30	Movement in operating stockpiles
Porphyry Zone (Splay)	164	2.2	11	80%	9						New pit design
Tabakoroni Open Pit	48	1.9	3	90%	0	962	1.6	49	90%	44	New Reserve
Tabakoroni Stockpiles	1080	1.4	50	90%	45	596	2.0	39	90%	35	Mining depletion
Senegal											
Mako	697	2.0	44	90%	40	2,037	1.9	122	90%	109	COG change and mining depletion
Mako Stockpiles	3861	1.0	128	90%	115	3,054	1.1	103	90%	93	Movement in operating stockpiles
Total Proved	7438	1.3	320		279	9,858	1.5	482		421	
			Probable					Probable		Com	ment on Changes
Mali											
Syama Underground	25,500	2.6	2,09 4	80%	1,675	25,678	2.6	2,159	80%	1,727	Depletion from mining & additional ounces from Optimisation
Syama Stockpiles (sulphide)	1,817	1.3	78	80%	63	1,806	1.3	77	80%	62	Movement in operating stockpiles
Syama North	10,582	2.5	854	80%	683	184	1.3	8	80%	6	New pit optimisation (A21, Ba01N, Ba04, Alpha): design soon
Stockpiles (Syama North)	1,403	1.0	43	80%	34	1,403	1.0	43	80%	34	Movement in operating stockpiles
Cashew South	109	1.4	5	80%	4						
Cashew NE					0	90	2.0	6	80%	5	Combined with Paysans
Paysans	609	1.7	33	80%	27	715	2.0	46	80%	37	New pit design
Tellem	1,065	2.5	84	80%	68	435	2.1	29	80%	23	Loew confidence in modifying factors
Folona	2	1.6	0.1	80%	0						New pit design
Tabakoroni Open Pit	222	1.7	12	90%	11	209	1.8	12	90%	11	Mining depletion & Optimisation at Taba Fresh
Tabakoroni Underground Senegal	5,028	4.7	766	90%	689	5,028	4.7	766	90%	689	No change
Mako	4,948	2.2	348	90%	313	7,101	1.9	437	90%	393	Mining depletion
Total Probable	51,284	2.6	4,31 7		3,566	42,649	2.6	3,583		2,988	
Total Reserves	58,723	2.5	4,63 7		3,845	52,506	2.4	4,065		3,409	

Appendix Table 1: Ore Reserves Comparison – 31 December 2022 to 31 December 2021



#### Notes:

- 1. Mineral Resources include Ore Reserves.
- All tonnes and grade information have been rounded to reflect relative uncertainty of the estimate, small differences may be present in the totals.
   Syama Underground mine planning is based on a shut-off grade of 2g/t.
   Syama Satellite Reserves are reported above 0.8g/t cut-off.

- Tabakoroni Underground Reserves are reported above a 2.75g/t cut-off.
   Tabakoroni Satellite Reserves are reported above 0.8g/t cut-off.
   Mako Reserves are reported above 0.9g/t cut-off.

## **Mineral Resources Comparison To 31 December 2021**

			Dec-22			Dec-21					
	Tonnes	Gold grade	Ounces	Group Share	Group Share	Tonnes	Gold grade	Ounces	Group Share	Group Share	_
	(000s)	(g/t)	(000s)	%	Ounces	(000s)	(g/t)	(000s)	%	Ounces	
Mineral Resources			Measure	d				Measure	d		Comment on Changes
Mali											
Syama Underground	21,235	3.5	2,362	80%	1,890	14,417	3.6	1,644	80%	1,315	Depletion due to mining and new Resource
Syama Stockpiles (Sulphide)	707	2.0	46	80%	37	760	1.8	44	80%	35	Movement in operating stockpiles
Syama North	717	3.5	81	80%	65	4,332	2.7	375	80%	300	New Resource
Stockpiles (Oxide)	739	1.6	38	80%	30	768	1.5	38	80%	30	Movement in operating stockpiles
Cashew NE	1,031	1.8	60	80%	48	1,031	1.8	60	80%	48	New Resource
Tabakoroni Open Pit	33	3.9	4	90%	4	524	3.3	55	90%	50	New Resource
Tabakoroni Underground	6	3.5	1	90%	1	6	3.5	1	90%	1	New Resource
Tabakoroni Stockpiles	945	1.4	42	90%	38	888	1.5	43	90%	39	Movement in operating stockpiles
Porphyry Zone (Splay)	190	2.0	12	90%	11	2,192	1.7	122	90%	110	New Resource
Senegal											
Mako	1,103	1.6	56	90%	50	2,455	1.7	135	90%	241	Depletion due to mining and new Resource
Mako Stockpiles	3,852	1.0	121	90%	109	3,054	1.1	103	90%	88	Movement in operating stockpiles
Total Measured	30,558	2.9	2,823		2,282	30,426	2.7	2,620		2,142	
			Indicated	ł				Indicated	ł		
Mali											
Syama Underground	25,920	3.0	2,483	80%	1,986	25,447	3.0	2,456	80%	1,965	Depletion due to mining and new Resource
Syama Stockpiles (Sulphide)	1,771	1.3	75	80%	60	1,825	1.4	79	80%	63	Movement in operating stockpiles
Syama North	18,457	3.0	1,774	80%	1,419	4,123	2.7	363	80%	291	New Resource
Stockpiles (Oxide)	1,657	1.0	52	80%	42	1,403	1.0	43	80%	34	No change
Cashew NE	0	0.0	0	80%	0	0	0.0	0	80%	0	Depletion due to mining and new Resource
Paysans	3,437	1.8	199	80%	159	4,210	1.7	230	80%	184	No change
Tellem	2,208	2.3	162	80%	130	1,770	1.9	110	80%	88	No change
Tabakoroni Open Pit	205	5.0	33	90%	30	2,127	4.6	318	90%	286	New Resource
Tabakoroni Underground	5,179	4.8	792	90%	713	5,179	4.8	792	90%	713	New Resource
Senegal											
Mako	8,458	1.8	487	90%	438	9,913	1.8	560	90%	504	New Resource and mining depletion
Total Indicated	67,293	2.8	6,057		4,977	55,997	2.8	4,951		4,128	

At 31 December 2022



			Dec-22					Dec-21			
	Tonnes	Gold grade	Ounces	Group Share	Group Share	Tonnes	Gold grade	Ounces	Group Share	Group Share	
	(000s)	(g/t)	(000s)	%	Ounces	(000s)	(g/t)	(000s)	%	Ounces	
Mineral Resources			Inferred					Inferred			Comment on Changes
Mali											
Syama Underground	1,359	2.6	112	80%	90	10,582	2.6	883	80%	706	New resource and depletion due to mining
Syama North	14,683	2.8	1,319	80%	1,055	3,495	3.2	358	80%	286	New resource
Stockpiles (Syama North)	46	1.1	2	80%	1	45	1.1	2	80%	1	Movement in operating stockpiles
Cashew NE	0	0	0	80%	0	0	0	0	80%	0	No change
Paysans	1,765	1.7	98	80%	78	920	1.6	40	80%	32	Updated resource
Tellem	2,528	2.3	187	80%	150	400	2.5	35	80%	28	Updated resource
Tabakoroni Open Pit	1	6	0	80%	0	21	5.6	4	80%	3	Depletion due to mining
Tabakoroni Underground	1,644	3.5	182	90%	164	1,644	3.5	182	90%	164	No change
Porphyry Zone	0	0	0	90%	0	0	0	0	90%	0	No change
Tailings Storage Facility	17,000	0.7	365	80%	292	17,000	0.7	365	80%	292	No change
Senegal											
Mako	682	0.9	19	90%	17	986	0.9	28	90%	25	Mining depletion
Total Inferred	39,888	1.8	2,284		1,848	35,094	1.7	1,896		1,538	
Total Resources	137,739	2.5	11,164		9,106	121,517	2.4	9,467		7,808	

Appendix Table 2: Mineral Resources Comparison – 31 December 2022 to 31 December 2021

Notes:

1.

Mineral Resources include Ore Reserves. All tonnes and grade information have been rounded to reflect relative uncertainty of the estimate, small differences may be present in the totals. 2.

Resources are reported above 1.0g/t cut-off for the Syama North.

2. 3. 4. 5. Resources are reported above 1.0gr. Cut-on for the Syama worth. Resources for the SLC at Syama is reported within an MSO shape generated at 1.3g/t and south of the SLC within an MSO shape generated at 1.5g/t. Resources for the Cashew NE, Paysans, Tellem and Porphyry Zone (Splay) are reported above a cut-off of 1.0g/t. Resources for Tabakoroni Open Pit are reported above a cut-off of 1.0g/t and within a US\$2,000 optimised shell. Resources for the Tabakoroni Underground are reported within an MSO shape generated at 1.75g/t (equivalent to US\$2,000). Mako Resources are reported above a cut-off of 0.5g/t and within a US\$2,000 optimised shell.

5. 6. 7. 8.



## JORC Code, 2012 Edition – Table 1 Report Syama Gold Mine

## Section 1 Sampling Techniques and Data

CRITERIA	JORC CODE EXPLANATION	COMMENTARY
Sampling techniques	<ul> <li>Nature and quality of sampling (e.g. cut channels, random chips, or specific specialised industry standard measurement tools appropriate to the minerals under investigation, such as down hole gamma sondes, or handheld XRF instruments, etc.).</li> </ul>	The mineral resource estimate was based on data collected from reverse circulation (RC) and diamond core (DD) drill holes completed by Resolute Mining Limited (2003-2017), Randgold Resources Ltd (1996-2000) and BHP (1987-1996).
	<ul> <li>These examples should not be taken as limiting the broad meaning of sampling.</li> <li>Include reference to measures taken to ensure sample representivity and the appropriate calibration of any measurement tools or systems used.</li> </ul>	Diamond core was sampled at 1m intervals and cut in half, to provide a 2-4kg sample, which was sent to the laboratory for crushing, splitting and pulverising, to provide a 30g charge for analysis.
	<ul> <li>Aspects of the determination of mineralisation that are Material to the Public Report.</li> <li>In cases where 'industry standard' work has been done this would be relatively simple (e.g. 'reverse circulation drilling was</li> </ul>	RC samples were collected on 1m intervals via a cyclone by riffle split (dry), or by scoop (wet), to obtain a 2-4kg sample which was sent to the laboratory for crushing, splitting and pulverising to provide a 30g charge for analysis.
	used to obtain 1 m samples from which 3 kg was pulverised to produce a 30 g charge for fire assay'). In other cases, more explanation may be required such as where there is coarse	Resolute sampling and sample preparation protocols are industry standard and are deemed appropriate by the Competent Person.
	gold that has inherent sampling problems. Unusual commodities or mineralisation types (e.g. submarine nodules) may warrant disclosure of detailed information.	The Randgold and BHP diamond core and RC samples were taken on 1m intervals. Due to the historical nature of the data sampling protocols are not known.
Drilling	• Drill type (e.g. core, reverse circulation, open-hole hammer,	Drill types used include diamond core of HQ and NQ sizes.
techniques	rotary air blast, auger, Bangka, sonic, etc.) and details (e.g. core diameter, triple or standard tube, depth of diamond tails, face-sampling bit or other type, whether core is oriented and if so, by what method, etc.).	Core is oriented at 3m down hole intervals using a Reflex Act II RD Orientation Tool and more recently using a Reflex north seeking gyro instrument.
Drill sample recovery	<ul> <li>Method of recording and assessing core and chip sample recoveries and results assessed.</li> <li>Measures taken to maximize sample recovery and ensure</li> </ul>	Drill core interval recoveries are measured from core block to core block using
	<ul><li>Weasures taken to maximise sample recovery and ensure representative nature of the samples.</li><li>Whether a relationship exists between sample recovery and</li></ul>	Appropriate measures are taken to maximise sample recovery and ensure representative nature of the samples.
	grade and whether sample bias may have occurred due to preferential loss/gain of fine/coarse material.	No apparent relationship between sample recovery and grade.
Logging	<ul> <li>Whether core and chip samples have been geologically and geotechnically logged to a level of detail to support appropriate Mineral Resource estimation, mining studies and metallurgical</li> </ul>	Drill holes were geologically logged by geologists for colour, grainsize, lithology, minerals, alteration and weathering on geologically domained intervals.
	<ul> <li>studies.</li> <li>Whether logging is qualitative or quantitative in nature.</li> <li>Core (or costean, channel, etc.) photography.</li> </ul>	Geotechnical and structure orientation data was measured and logged for all diamond core intervals.
	<ul> <li>The total length and percentage of the relevant intersections</li> </ul>	Diamond core was photographed (wet and dry).
	logged.	Holes were logged in their entirety (100%) and this logging was considered reliable and appropriate.



CRITERIA	JORC CODE EXPLANATION	COMMENTARY
Sub-sampling techniques	<ul> <li>If core, whether cut or sawn and whether quarter, half or all core taken.</li> </ul>	Diamond core has been sampled at 1m intervals and cut in half to obtain a 2-4kg sample.
and sample	<ul> <li>If non-core, whether riffled, tube sampled, rotary split, etc. and whether sampled wet or dry.</li> </ul>	Reverse circulation samples were collected on 1m intervals by riffle split (dry) or by scoop (wet) to obtain a 2-4kg sample.
ргерагацоп	<ul> <li>For all sample types, the nature, quality and appropriateness of the sample preparation technique.</li> <li>Quality control procedures adopted for all sub-sampling stages to maximise representivity of samples.</li> </ul>	Sample preparation for diamond core and RC samples includes oven drying, crushing to 10mm and splitting, pulverising to 85% passing -75um. These preparation techniques are deemed to be appropriate to the material and element being sampled.
	<ul> <li>Measures taken to ensure that the sampling is representative of the in-situ material collected, including for instance results for field duplicate/second-half sampling.</li> <li>Whether sample sizes are appropriate to the grain size of</li> </ul>	Drill core coarse duplicates were split by the laboratory after crushing at a rate of 1:20 samples. Reverse circulation field duplicates were collected by the company at a rate of 1:20 samples.
	the material being sampled.	Resolute sampling, sample preparation and quality control protocols are of industry standard and all attempts were made to ensure an unbiased representative sample was collected. The methods applied in this process were deemed appropriate by the Competent Person.
		Sub-sampling techniques and sample preparation completed by previous owners is not known.
Quality of assay data and laboratory tests	<ul> <li>The nature, quality and appropriateness of the assaying and laboratory procedures used and whether the technique is considered partial or total.</li> <li>For geophysical tools, apportunities tools and bald XDE.</li> </ul>	All Resolute samples were analysed for gold by 30g fire assay fusion with AAS instrument finish. The analysis was performed by ALS Bamako or SGS Morila. The analytical method was appropriate for the style of mineralisation.
	<ul> <li>For geophysical tools, spectrometers, handned XKF instruments, etc., the parameters used in determining the ophysic including instrument make and model, reading</li> </ul>	No geophysical tools were used to determine elemental concentrations.
	<ul> <li>times, calibrations factors applied and their derivation, etc.</li> <li>Nature of quality control procedures adopted (e.g. standards, blanks, duplicates, external laboratory checks) and whether accentable levels of accuracy (i.e. lack of bias).</li> </ul>	Quality control (QC) procedures included the use of certified standards and blanks (1:20), non- certified sand blanks (1:20), diamond core coarse duplicates (1:20) and reverse circulation field duplicates (1:20).
	and precision have been established.	Laboratory quality control data, including laboratory standards, blanks, duplicates, repeats and grind size results were also captured into the digital database.
		Analysis of the QC sample assay results indicates that an acceptable level of accuracy and precision has been achieved.
		The assay techniques used by Randgold and BHP include fire assay fusion with AAS instrument finish and aqua regia with AAS. The majority of the samples were analysed at the onsite Syama laboratory. Due to the historical nature of the Randgold and BHP data the assay procedures are not known for all samples.
Verification of sampling and	The verification of significant intersections by either     independent or alternative company percented	Verification of significant intersections have been completed by company personnel and the competent person.
assaying	<ul> <li>The use of twinned holes.</li> </ul>	No drill holes within the resource area were twinned.
	<ul> <li>Documentation of primary data, data entry procedures, data verification, data storage (physical and electronic) protocols.</li> <li>Discuss any adjustment to assay data.</li> </ul>	Drill holes were logged onto paper templates or Excel templates with lookup codes, validated and then compiled into a relational SQL 2012 database using DataShed data management software. The database has a variety of verification protocols which are used to validate the data entry. The drill hole database is backed up daily to the head office server.
		Assay result files were reported by the laboratory in PDF and CSV format and imported directly into the SQL database without adjustment or modification.
		Resolute has conducted extensive reviews, data validation and data verification on the historic data collected by the previous owners, Randgold and BHP.



CRITERIA	JORC CODE EXPLANATION	COMMENTARY
Location of data points	<ul> <li>Accuracy and quality of surveys used to locate drill holes (collar and down-hole surveys), trenches, mine workings and other locations used in Mineral Resource estimation.</li> </ul>	Collar coordinates were picked up in UTM (WGS84) by staff surveyors using an RTK DGPS with an expected accuracy of ±0.05m; elevations were height above EGM96 geoid.
	<ul> <li>Specification of the grid system used.</li> <li>Quality and adequacy of topographic control.</li> </ul>	Down hole surveys were collected using single shot and multi shot magnetic survey tools including Reflex EZTrac and EZShot instruments. A time-dependent declination was applied to the magnetic readings to determine UTM azimuth. Diamond drilling completed in 2017 and 2018 has utilised a Reflex EZ Gyro downhole survey instrument to provide more frequent data points and reduced magnetic interference.
		Coordinates and azimuth are reported in UTM WGS84 Zone 29 North in this release.
		Coordinates were translated to local mine grid where appropriate.
		Local topographic control is via satellite photography and drone UAV Aerial Survey.
Data spacing and distribution	<ul> <li>Data spacing for reporting of Exploration Results.</li> <li>Whether the data spacing and distribution is sufficient to</li> </ul>	The drill hole spacing was sufficient to demonstrate geological and grade continuity appropriate for
	establish the degree of geological and grade continuity appropriate for the Mineral Resource and Ore Reserve	Mineral Resource estimation and classification in accordance with the 2012 JORC Code.
	<ul><li>estimation procedure(s) and classifications applied.</li><li>Whether sample compositing has been applied.</li></ul>	The appropriateness of the drill spacing was reviewed by the geological technical team, both on site and within the Resolute group. This was also reviewed by the Competent Person.
		RC and diamond core samples were collected on 1m intervals; no sample compositing is applied during sampling.
Orientation of data in relation to	Whether the orientation of sampling achieves unbiased	Holes were drilled predominantly perpendicular to mineralised domains where possible.
geological structure	<ul> <li>sampling of possible structures and the extent to which this is known, considering the deposit type.</li> <li>If the relationship between the drilling orientation and the orientation of key mineralised structures is considered to have introduced a sampling bias, this should be assessed and reported if material.</li> </ul>	No orientation-based sampling bias has been identified in the data.
Sample security	• The measures taken to ensure sample security.	Samples were collected from the drill site and stored on site. All samples were individually bagged and labelled with unique sample identifiers then securely dispatched to the laboratories.
		All aspects of sampling process were supervised and tracked by SOMISY personnel.
Audits or reviews	The results of any audits or reviews of sampling techniques and data.	External audits of procedures indicate protocols are within industry standards.



## **Section 2 Reporting of Exploration Results**

CRITERIA	JORC CODE EXPLANATION	COMMENTARY
Mineral tenement and land tenure status	<ul> <li>Type, reference name/number, location and ownership including agreements or material issues with third parties such as joint ventures, partnerships, overriding royalties, native title interests, historical sites, wilderness or national park and environmental settings.</li> <li>The security of the tenure held at the time of reporting along with any known impediments to obtaining a licence to operate in the area.</li> </ul>	Drilling was conducted within the Malian Exploitation Concession Permit PE 93/003 which has an area of 200.6km <sup>2</sup> . Resolute Mining Limited has an 80% interest in the Syama project and the Exploitation Permit PE—93/003, on which it is based, through its Malian subsidiary, Sociêtê des Mines de Syama SA (SOMISY). The Malian Government holds a free carried 20% interest in SOMISY. The Permit is held in good standing. Malian mining law provides that all mineral resources are administered by DNGM (Direction Nationale de la Géologie et des Mines) or National Directorate of Geology and Mines under the Ministry of Mines, Energy and Hydrology.
Exploration done by other parties	Acknowledgment and appraisal of exploration by other parties.	The Syama deposit was originally discovered by a regional geochemical survey undertaken by the Direction National de Géologie et des Mines (DNGM) with assistance from the United Nations Development Program (UNDP) in 1985. There had also been a long history of artisanal activities on the hill where an outcropping chert horizon originally marked the present-day position of the open pit. BHP during 1987-1996 sampled pits, trenches, auger, RC and diamond drill holes across Syama prospects. Randgold Resources Ltd during 1996-2000 sampled pits, trenches, auger, RAB, RC and diamond drill holes across Syama prospects.
Geology	Deposit type, geological setting and style of mineralisation.	The Syama Project is found on the northern margin of the Achaean-Proterozoic Leo Shield which forms the southern half of the West African Craton. The project area straddles the boundary between the Kadiana–Madinani terrane and the Kadiolo terrane. The Kadiana-Madinani terrane is dominated by greywackes and a narrow belt of interbedded basalt and argillite. The Kadiolo terrane comprises polymictic conglomerate and sandstone that were sourced from the Kadiana-Madinani terrane and deposited in a late- to syntectonic basin. Prospects are centred on the NNE striking, west dipping, Syama-Bananso Fault Zone and Birimian volcano- sedimentary units of the Syama Formation. The major commodity being sought is gold.
Drill hole Information	<ul> <li>A summary of all information material to the understanding of the exploration results including a tabulation of the following information for all Material drill holes: <ul> <li>easting and northing of the drill hole collar.</li> <li>elevation or RL (Reduced Level – elevation above sea level in metres) of the drill hole collar.</li> <li>dip and azimuth of the hole.</li> <li>down hole length and interception depth.</li> <li>Whole length.</li> </ul> </li> <li>If the exclusion of this information is justified on the basis that the information is not Material and this exclusion does not detract from the understanding of the report, the Competent Person should clearly explain why this is the case.</li> </ul>	No new exploration results have been reported in this release. The listing of the entire drill hole database used to estimate the resource was not considered relevant for this release.



CRITERIA	JORC CODE EXPLANATION	COMMENTARY
Data aggregation methods	<ul> <li>In reporting Exploration Results, weighting averaging techniques, maximum and/or minimum grade truncations (e.g. cutting of high grades) and cut-off grades are usually Material and should be stated.</li> </ul>	No new exploration results have been reported in this release. Metal equivalent values are not used in reporting.
	<ul> <li>Where aggregate intercepts incorporate short lengths of high-grade results and longer lengths of low-grade results, the procedure used for such aggregation should be stated and some typical examples of such aggregations should be shown in detail.</li> </ul>	
	<ul> <li>The assumptions used for any reporting of metal equivalent values should be clearly stated.</li> </ul>	
Relationship between	<ul> <li>These relationships are particularly important in the reporting of Exploration Results.</li> </ul>	The mineralisation is steeply dipping at approximately 60 <sup>0</sup> from the horizontal.
mineralisation widths and intercept lengths	• If the geometry of the mineralisation with respect to the drill hole angle is known, its nature should be reported.	Most of the drill holes are planned at local grid 090 <sup>0</sup> at a general inclination of -60 <sup>0</sup> east to achieve as close to
	<ul> <li>If it is not known and only the down hole lengths are reported, there should be a clear statement to this effect (e.g. 'down hole length, true width not known').</li> </ul>	At the angle of the drill holes and the dip of the ore zones, the reported intercepts will be slightly more than true width.
Diagrams	<ul> <li>Appropriate maps and sections (with scales) and tabulations of intercepts should be included for any significant discovery being reported. These should include, but not be limited to a plan view of drill hole collar locations and appropriate sectional views.</li> </ul>	Relevant maps, diagrams and tabulations are included in the body of text.
Balanced reporting	<ul> <li>Where comprehensive reporting of all Exploration Results is not practicable, representative reporting of both low and high grades and/or widths should be practiced to avoid misleading reporting of Exploration Results.</li> </ul>	Mineral Resources are being reported in this announcement. No new exploration results have been reported in this release.
Other substantive exploration data	<ul> <li>Other exploration data, if meaningful and material, should be reported including (but not limited to): geological observations; geophysical survey results; geochemical survey results; bulk samples – size and method of treatment; metallurgical test results; bulk density, groundwater, geotechnical and rock characteristics; potential deleterious or contaminating substances.</li> </ul>	No geophysical and geochemical data and any additional exploration information has been reported in this release, as they are not deemed relevant to the release.
Further work	<ul> <li>The nature and scale of planned further work (e.g. tests for lateral extensions or depth extensions or large-scale stepout drilling).</li> <li>Diagrams clearly highlighting the areas of possible extensions, including the main geological interpretations and future drilling areas, provided this information is not commercially sensitive.</li> </ul>	Depth extension drilling is planned to test the down-dip potential of the Syama ore body at depth, and beneath the current limit of drilling.



## Section 3 Estimation and Reporting of Mineral Resources

CRITERIA	JORC CODE EXPLANATION	COMMENTARY
Database integrity	<ul> <li>Measures taken to ensure that data has not been corrupted by, for example, transcription or keying errors, between its initial collection and its use for Mineral Resource estimation purposes.</li> <li>Data validation procedures used.</li> </ul>	Data has been compiled into a relational SQL database; the setup of this database precludes the loading of data which does not meet the required validation protocols. The data is managed using DataShed <sup>®</sup> drill hole management software using SQL database techniques. Validation checks are conducted using SQL and DataShed <sup>®</sup> relational database standards. Data has also been checked against original hard copies for 100% of the data, and where possible, loaded from original data sources.
		Resolute completed the following basic validation checks on the data supplied prior to resource estimation:
		<ul> <li>Drill holes with overlapping sample intervals.</li> <li>Sample intervals with no assay data. Duplicate records.</li> <li>Assay grade ranges.</li> <li>Collar coordinate ranges.</li> <li>Valid hole orientation data.</li> </ul>
		There are no significant issues identified with the data.
Site visits	Comment on any site visits undertaken by the Competent Person and the outcome of those visits	The Competent Person visited site in November, 2022.
	<ul> <li>Person and the outcome of those visits.</li> <li>If no site visits have been undertaken indicate why this is the case.</li> </ul>	All aspects of drilling, sampling and mining are considered by the Competent Person to be of a high standard.
Geological interpretation	<ul> <li>Confidence in (or conversely, the uncertainty of) the geological interpretation of the mineral deposit.</li> <li>Nature of the data used and of any assumptions made.</li> <li>The effect, if any, of alternative interpretations on Mineral Resource estimation.</li> <li>The use of geology in guiding and controlling Mineral Resource estimation.</li> <li>The factors affecting continuity both of grade and geology</li> </ul>	The digital database used for the interpretation included logged intervals for the key stratigraphic zones of Syama. Detailed geological logs were available in hardcopy and digital and reviewed where necessary.
		Drill density (50m by 50m) for the majority of the Syama area allows for confident interpretation of the geology and mineralised domains. More recent grade control (gc) drilling (at 25m by 25m spacing) confirms the positions of mineralised zones. Geological and structural controls support modelled mineralised zones, which are constrained within geological units.
		Continuity of mineralisation is affected by proximity to structural conduits (allowing flow of mineralised fluids), stratigraphic position, lithology of key stratigraphic units and porosity of host lithologies.
		Wireframes used to constrain the estimation for Syama South and Nafolo are based on drill hole intercepts and geological boundaries. All wireframes at Syama South and Nafolo have been constructed to a 1g/t Au cut-off grade for shape consistency.
		The incorporation of an independent structural model (Steve King, 2019) gives limited options for large scale alternate interpretations.
Dimensions	• The extent and variability of the Mineral Resource expressed as length (along strike or otherwise), plan width, and depth below surface to the upper and lower limits of the Mineral Resource.	The Syama area extends for approximately 1,500 metres in strike and the west dipping gold mineralised zone is between 100-200 metres in horizontal width, narrowing at its southern and northern limits. The Mineral Resource is limited in depth by drilling, which extends from surface to a maximum depth of approximately 800 metres vertically.



#### Estimation and modelling techniques

- The nature and appropriateness of the estimation technique(s) applied and key assumptions, including treatment of extreme grade values, domaining, interpolation parameters and maximum distance of extrapolation from data points. If a computer assisted estimation method was chosen include a description of computer software and parameters used.
- The availability of check estimates, previous estimates and/or mine production records and whether the Mineral Resource estimate takes appropriate account of such data.
- The assumptions made regarding recovery of byproducts.
- Estimation of deleterious elements or other non-grade variables of economic significance (e.g. sulphur for acid mine drainage characterization).
- In the case of block model interpolation, the block size in relation to the average sample spacing and the search employed.
- In the case of block model interpolation, the block size in relation to the average sample spacing and the search employed.
- Any assumptions behind modelling of selective mining units.
- Any assumptions about correlation between variables.
- Description of how the geological interpretation was used to control the resource estimates.
- Discussion of basis for using or not using grade cutting or capping.
- The process of validation, the checking process used, the comparison of model data to drill hole data, and use of reconciliation data if available.

Estimation was completed in Datamine Studio RM using Categorical Indicator (CI) approach to define the mineralised blocks followed by an Ordinary Kriged (OK) model to estimate the gold grade. Grades were estimated into parent block of 5mE by 12.5mN by 5mRL for Syama underground and 10mE by 25 mN by 10mRI for Syama South and Nafolo. Sub- celling down to 5mE by 12.5mN by 5mRL was employed for resolution of the mineralisation boundary at Nafolo.

The categorical model used a cut-off of 1 g/t gold once the mineralised blocks have been identified another categorical model within this mineralisation is carried out at a cut-off of 2 g/t to identify higher grade zones. A 5mE by 12.5mN by 5mRL block size was employed during the categorical process used to delineate mineralised regions.

After this process, the model was reblocked up to 5mE by 25mN by 10mRL for Nafolo while retaining the smaller size blocks as subcells at mineralisation boundaries.

The resource model included estimates for sulphide sulphur and organic carbon which assist with metallurgical characterisation. The sulphide sulphur is estimated via a categorical indicator approach with a cut-off grade of 1% to identify the higher grade blocks and then an OK estimation was carried out within these blocks. Organic carbon was just estimated without boundaries into the block model. There are reduced assays at depth of these two elements so there is some smoothing at depth.

Kriging neighbourhood analysis was performed to optimise the block size, sample numbers and discretisation levels with the goal of minimising conditional bias in the gold grade estimates.

A larger blocks size for Nafolo and Syama South was chosen based on this analysis than was employed in the previous resource estimate and the wider drill spacing.

A total of three search passes was used, with the first search pass set to the range of the variogram for each element. A minimum of 10 and a maximum of 30 samples were used. The search stayed the same for the second pass but was increased by a factor of 2 for the third and final pass. The minimum number of samples was reduced to 8 for the second pass and 6 for the third pass.

Semi-soft boundaries were used between the higher grade and lower grade domains and between the lower grade domain and the waste domain for Syama Main. Two samples either side of the mineralisation boundary were used in the OK estimation. Hard boundaries were utilised for the domains at Nafolo, Syama South and all of the domains for sulphide sulphur.

Un-estimated blocks (less than 1% for gold) were assigned the domain average grades. No deleterious elements were found in the ore.

No selective mining units have been assumed.

No assumptions have been made regarding the correlation of variables although it is noted that a broad positive correlation exists between gold and sulphur.

Estimation searches have been orientated to respect the orientation of the Syama Formation which hosts the mineralisation.

Top cuts were applied to reduce the variability of the data and to remove the outliers.

The estimated block model grades were visually validated against the input drillhole data and comparisons were carried out against the drillhole data and by northing and elevation slices. Global comparison between the input data and the block grades for each variable is considered acceptable ( $\pm 10\%$ ).



CRITERIA	JORC CODE EXPLANATION	COMMENTARY
		Comparison with the 2020 and 2021 Mineral Resources has been carried out.
Moisture	<ul> <li>Whether the tonnages are estimated on a dry basis or with natural moisture, and the method of determination of the moisture content.</li> </ul>	All tonnages are estimated on a dry basis.
Cut-off parameters	• The basis of the adopted cut-off grade(s) or quality parameters applied.	Mineral Resources for the main part of Syama was reported within a shape generated using a MSO (Mineable Shape Optimiser) at 1.3g/t cut-off grade (equivalent to a US\$2,000 gold price) this was based on the current Sub-Level Caving (SLC) mining method. The material south of the main zone was reported within an MSO shape generated at 1.5 g/t cut-off grade (equivalent to a US\$2,000 gold price) as this is planned to be mined by Open Stoping.
Mining factors or assumptions	<ul> <li>Assumptions made regarding possible mining methods, minimum mining dimensions and internal (or, if applicable, external) mining dilution. It is always necessary as part of the process of determining reasonable prospects for eventual economic extraction to consider potential mining methods, but the assumptions made regarding mining methods and parameters when estimating Mineral Resources may not always be rigorous.</li> <li>Where this is the case, this should be reported with an explanation of the basis of the mining assumptions made.</li> </ul>	The current mining method for underground exploitation is SLC. The resource model extends from 1,250 mRL to 600 mRL. Open pit mining methods were used by Resolute to 1,120 mRL. Material testing conducted on samples of underground ore confirmed that properties such as metallurgical factors, structural trends and geological continuity remain the same as observed in the fresh rock portion of the open pit. This Mineral Resource does not account for mining recovery.
Metallurgical factors or assumptions	<ul> <li>The basis for assumptions or predictions regarding metallurgical amenability. It is always necessary as part of the process of determining reasonable prospects for eventual economic extraction to consider potential metallurgical methods, but the assumptions regarding metallurgical treatment processes and parameters made when reporting Mineral Resources may not always be rigorous. Where this is the case, this should be reported with an explanation of the basis of the metallurgical assumptions made.</li> </ul>	Resolute has conducted metallurgical testwork on variability samples taken from within the proposed underground ore zone. A testwork program was supervised by consultants MineLogix Pty Ltd based on analytical testwork completed at ALS Metallurgy Laboratory. The program included comminution, flotation, roasting and leaching assessments. The planned processing flowsheet involves crushing, milling, flotation and reacting.
		product. The Syama sulphide processing facility has been in operation in its current form since 2007.
		The various testwork programs did not identify any contrasting metallurgical behaviour from samples within the underground ore zone and the performance of the underground ore typically matches that observed for open pit ore.

At 31 December 2022



#### CRITERIA

factors

Environmental

or assumptions

#### JORC CODE EXPLANATION

COMMENTARY

 Assumptions made regarding possible waste and process residue disposal options. It is always necessary as part of the process of determining reasonable prospects for eventual economic extraction to consider the potential environmental impacts of the mining and processing operation. While at this stage the determination of potential environmental impacts, particularly for a green fields project, may not always be well advanced, the status of early consideration of these potential environmental impacts should be reported. Where these aspects have not been considered this should be reported with an explanation of the environmental assumptions made. It is a requirement of Decree No.03-594/P-RM of 31 December 2003 of Malian law that an Environmental and Social Impact Study (Étude d'Impact Environmental et Social – EIES) must be undertaken to update the potential environmental and social impacts of the mine's redevelopment. The EIES for the Syama Gold Mine was approved in November 2007 and an Environment Permit (07- 0054/MEA – SG) was issued by the Ministry of Environment and Sanitation on the 22 November 2007. The Ministry of Environment conduct timely reviews of the Syama Gold Mine to ensure that the Company maintains compliance with the EIES guidelines.

At Syama there are three key practices for disposal of wastes and residues namely, stacking of waste rock from open pit mining; storage of tailings from mineral processes; and "tallstack dispersion" of sulphur dioxide from the roasting of gold bearing concentrate. All waste disposal practices are in accordance with the guidelines in the EIES.

The Environmental and Social Impact Study – "Société des Mines de Syama, Syama Gold Mine, Mali, dated 2007 indicated there was minimal potential for acid mine drainage from waste rock due to the elevated carbonate content which buffers a potential acid generation. Resolute maintains a plan for progressive rehabilitation of waste rock landforms as part of ongoing mine development and waste rock dumping.

The landform of tailings impoundments does not have a net acid generating potential. The largest volume is flotation tailings where the sulphide minerals have already been removed from the host rock. Its mineralogy includes carbonates which further buffer any acid-formation potential from sulphides that may also be present.

Cyanide levels in the leached-calcine tailings are typically less than 50 ppm in the weak acid dissociable form. Groundwater away from the tailing's landform is intercepted by trenches and sump pumps.

Sulphur dioxide is generated from the roasting of gold concentrate so that gold can be extracted and refined. Tall-Stack "dispersion" of the sulphur dioxide emission is monitored continuously. Prevailing weather and dissipation of the sulphur dioxide is modelled daily to predict the need to pause the roasting process to meet the air quality criteria set out in the Environmental and Social Impact Study.



CRITERIA	JORC CODE EXPLANATION	COMMENTARY
Bulk density	<ul> <li>Whether assumed or determined. If assumed, the basis for the assumptions. If determined, the method used, whether wet or dry, the frequency of the measurements, the nature, size and representativeness of the samples.</li> <li>The bulk density for bulk material must have been measured by methods that adequately account for void spaces (vugs, porosity, etc), moisture and differences between rock and alteration zones within the deposit.</li> <li>Discuss assumptions for bulk density estimates used in the evaluation process of the different materials.</li> </ul>	Site personnel have completed numerous bulk density comparative estimates on HQ drill core to assess variability using the Archimedes method of dry weight versus weight in water. This method was used for 96% of the bulk density measurements. Other tests were completed by SGS using the pycnometer method. Based on the data collected the following SG estimates were applied to the model: • Syama Formation 2.82 • Sikoro Formation 2.75 • Banmbere Conglomerate 2.75 SIKORO FORMATION SYAMA FORMATION SYAMA BANMBERE CONGLOMERAT
Classification	<ul> <li>The basis for the classification of the Mineral Resources into varying confidence categories.</li> <li>Whether appropriate account has been taken of all relevant factors (i.e. relative confidence in tonnage/grade estimations, reliability of input data, confidence in continuity of geology and metal values, quality, quantity and distribution of the data).</li> <li>Whether the result appropriately reflects the Competent Person's view of the deposit.</li> </ul>	<ul> <li>The Measured Mineral Resource classification is based on good confidence in the geology and gold grade continuity with less than 25m x 25m spaced drillhole density in the central part of the deposit directly below the current pit.</li> <li>The Indicated Mineral Resource classification is based on good confidence in the geology and gold grade continuity with less than 75m x 75m spaced drillhole density in the central part of the deposit.</li> <li>The Inferred Mineral Resource classification is applied to extensions of mineralised zones on the margins of the deposit where drill spacing is more than 100m x 100m and the extents of mineralisation at depth. The Nafolo orebody to the south of Syama which is tested by wider drill spacing has also been classified as Inferred.</li> <li>The validation of the block model has confirmed satisfactory correlation of data trends.</li> <li>The Mineral Resource estimate appropriately reflects the view of the Competent Persons.</li> </ul>
Audits or reviews	<ul> <li>The results of any audits or reviews of Mineral Resource estimates.</li> </ul>	The Mineral Resource has been audited internally. There has been no external review of the Mineral Resource estimate.



CRITERIA	JORC CODE EXPLANATION	COMMENTARY
Discussion of relative accuracy/ confidence	<ul> <li>Where appropriate a statement of the relative accuracy and confidence level in the Mineral Resource estimate using an approach or procedure deemed appropriate by the Competent Person. For example, the application of statistical or geostatistical procedures to quantify the relative accuracy of the resource within stated confidence limits, or, if such an approach is not deemed appropriate, a qualitative discussion of the factors that could affect the relative accuracy and confidence of the estimate.</li> <li>The statement should specify whether it relates to global or local estimates, and, if local, state the relevant tonnages, which should be relevant to technical and economic evaluation. Documentation should include assumptions made and the procedures used.</li> <li>These statements of relative accuracy and confidence of the estimate should be compared with production data, where available.</li> </ul>	The relative accuracy of the Mineral Resource estimate is reflected in the reporting of Indicated and Inferred resource categories as defined by 2012 JORC Code guidelines. The geostatistical techniques applied to the estimate of underground resources at Syama are deemed appropriate to the estimation of Sub Level Caving (SLC) mining method and hence applicable for reserve estimation. The estimation was compared with the production history at Syama and it is within 15-20% which is within the limits for the relevant classifications.



## Section 4 Estimation and Reporting of Ore Reserves

CRITERIA	JORC CODE EXPLANATION	COMMENTARY
Mineral Resource estimate for conversion to Ore Reserves	<ul> <li>Description of the Mineral Resource estimate used as a basis for the conversion to an Ore Reserve.</li> <li>Clear statement as to whether the Mineral Resources are reported additional to, or inclusive of, the Ore Reserve.</li> </ul>	The Syama 1122 Mineral Resource is the basis for the estimation of Syama Ore Reserves. The Mineral Resources are reported inclusive of Ore Reserves.
Site visits	<ul> <li>Comment on any site visits undertaken by the Competent Person and the outcome of those visits.</li> <li>If no site visits have been undertaken indicate why this is the case.</li> </ul>	The Competent Person, Mr. Gito Patani, is a full-time employee of Resolute Mining Ltd and a Member of the Australasian Institute of Mining and Metallurgy. He recently started with the company and conducted a site visit to the project area in January 2022. Travel to site was restricted during the 2021 due to covid- 19 travel restrictions, but weekly contact with site teams was maintained throughout the period.
Study status	<ul> <li>The type and level of study undertaken to enable Mineral Resources to be converted to Ore Reserves.</li> <li>The Code requires that a study to at least Pre-Feasibility Study level has been undertaken to convert Mineral Resources to Ore Reserves. Such studies will have been carried out and will have determined a mine plan that is technically achievable and economically viable, and that material Modifying Factors have been considered.</li> </ul>	Pre-Feasibility and Feasibility studies were previously conducted for Syama. The Syama UG mine is a going concern. The Ore Reserves are derived from LOM plan maintained for the ongoing scheduling and management of Syama UG operations.
Cut-off parameters	<ul> <li>The basis of the cut-off grade(s) or quality parameters applied.</li> </ul>	The LOM plan for Syama is designed based on variable shut-off grade with dilution and recovery estimation undertaken in cave flow modelling. The shut-off grade strategy used for cave flow modelling is based on COG calculation for various years from Fy22 financial model. The COG is estimated using: a gold price of USD 1,500/oz, a metallurgical recovery of 78%, an ad valorem royalty rate of 6%.
Mining factors or assumptions	<ul> <li>The method and assumptions used as reported in the Pre- Feasibility or Feasibility Study to convert the Mineral Resource to an Ore Reserve (i.e. either by application of appropriate factors by optimization or by preliminary or detailed design).</li> <li>The choice, nature and appropriateness of the selected mining method(s) and other mining parameters including associated design issues such as pre-strip, access, etc.</li> <li>The assumptions made regarding geotechnical parameters (e.g. pit slopes, stope sizes, etc.), grade control and pre- production drilling.</li> <li>The major assumptions made and Mineral Resource model used for pit and stope optimization (if appropriate).</li> <li>The mining dilution factors used.</li> <li>Any minimum mining widths used.</li> <li>The manner in which Inferred Mineral Resources are utilized in mining studies and the sensitivity of the outcome to their inclusion.</li> <li>The infrastructure requirements of the selected mining methods.</li> </ul>	Most of mining at Syama UG is planned to be undertaken by Sub- Level Caving (SLC) mining methods. Geotechnical studies have concluded that the deposit is amenable to SLC, and that caving is likely to be induced at hydraulic radii of between 12 and 17. Observed progress from mining to date supports these conclusions. Resolute undertakes a program of grade control drilling at Syama UG to progressively upgrade its geological confidence at Syama and enable further detailed mine planning. The Ore Reserve was estimated using the block model prepared for estimating the 2021 Mineral Resource. The Syama LOM plan is prepared —from the Mineral Resource block model— using mining industry standard computer aided design and scheduling software. Initially, production rings are designed to extract ore. Subsequently, lateral development and other infrastructure are designed to access production rings and enable safe and efficient ore extraction. Mining dilution and recovery are estimated for production rings using flow modelling software, PGCA. Dilution and recovery are inversely related at Syama. In general, the greater the recovery, the higher the level of dilution that will be experienced. The Syama LOM planning process balances recovery against dilution so the cash-flow is



CRITERIA	JORC CODE EXPLANATION	COMMENTARY
		With respect to minimum mining widths, production areas at Syama are planned to ensure that minimum hydraulic radius is achieved so that caving is induced in the overlying ground.
		Inferred Mineral Resources are not included in the Syama UG mine planning. All material from Syama Underground for 2021 OR inventory is categorised as Probable; comprised mainly of Indicated material. All Inferred and Unclassified material is classified as waste and not included in ore reserves
		The infrastructure necessary to extract the Syama UG Ore Reserve is maintained by the company.
Metallurgical factors or assumptions	<ul> <li>The metallurgical process proposed and the appropriateness of that process to the style of mineralization.</li> </ul>	The Syama deposit is refractory due to locking of gold within the sulphides and variable amounts of reactive natural carbon which
	Whether the metallurgical process is well-tested technology or novel in nature.	robs cyanide leach solutions of dissolved gold. Resolute has years of operating data processing Syama ore and metallurgical tochurch data. Processing of the gra will be via the following
	<ul> <li>The nature, amount and representativeness of metallurgical test work undertaken, the nature of the metallurgical domaining applied and the corresponding metallurgical recovery factors</li> </ul>	stages:
	applied and the corresponding metallargical recovery factors applied.	Crushing and grinding.
	• Any assumptions or allowances made for deleterious elements.	Flotation to produce a sulphide rich concentrate.
	<ul> <li>The existence of any bulk sample or pilot scale test work and the degree to which such samples are considered</li> </ul>	Concentrate thickening.
	representative of the ore body as a whole.	Roasting, followed by calcine quench and wash.
	<ul> <li>For minerals that are defined by a specification, has the ore reserve estimation been based on the appropriate mineralogy to meet the specifications?</li> </ul>	CIL.
		Tailings disposal.
Environmental	<ul> <li>The status of studies of potential environmental impacts of the mining and processing operation. Details of waste rock characterization and the consideration of potential sites, status of design options considered and, where applicable, the status of approvals for process residue storage and waste dumps should be reported.</li> </ul>	The Syama Gold Mine operates in accordance with its' Environmental & Social Impact Study – "Société des Mines de Syama, Syama Gold Mine, Mali, dated 2007. Waste rock characterisation has been included in prior studies for this Environmental & Social Impact Study. Work is ongoing to optimise the mining operation and environmental management through the following :
		Drilling to investigate rock characteristics
		mineralogical assay analysis of drill core
		routine testing of rock material types for acid generating properties
		developing a sequence, rate and design optimization for open-pit mine walls, ramps and the waste rock dump landform to meet the requirements of rock characteristics.
		The outcomes of this work are part of a continuous improvement program that contributes to the waste rock dump management plans, annual reporting and consultation-committee meetings with government and community representatives.
		Tailings storage for the life of mine is forecast to be impounded over the existing footprint area approved in the Environmental & Social Impact Study. Progressive raising of the tailings impoundments will occur to contain life-of-mine storage capacity. Routine progress on the monitoring is reported to government and at stakeholder meetings in concert with routine inspections by government representatives.
		The Syama Project is mature in its operating life with environmental management permitted by an Environmental Authority and supported by an Environmental Management Plan. No impediments are anticipated to the development of the underground mine



Intrastructure         The existence of appropriate infrastructure: availability of lend, for plant divelopment, power, water, transportation (particular) of a water with substances (particular). Biology, and plant divelopment, power water, transportation (particular) of an exist with wheth the infrastructure can be provided of accessed.         The Sysme Mine and the underground mine site are located near the two major towns of Kadalian, addition, Biolian of the northing at, is the accord the sealed Silkasso to Cher divelopment, the border position is the infrastructure are be provided of accessed.           Access is via formed gravel rad of the sealed Silkasso to Cher divelopment, and though Banasso to The divelopment of administration towns of Kadalian, and the nor Fource to Silkasso. The rad ministration towns of Kadalian, and the nor Fource to Silkasso. The rad ministration towns of Kadalian, and the nor Fource to Silkasso. The rad ministructure are subject with water.           Supporting infrastructure for the current operations has included upgaring of the Zilkas, and the nor Kadolia to the silkas, refurbishing an administration towns of Kadalian, and the ministration town and the source of part and buildings, plant set buildings and the infrastructure and the source of a spring water of the current operation has a place in a dividing and the second and these second and the second and thesecond and the second a	CRITERIA	JORC CODE EXPLANATION	COMMENTARY
Costs       • The derivation of, or assumptions made, regarding projected capital costs in a study constraints and operations with respect to cost estimates. Advances made for the current or deterious power from the study inclusions power demand of costs and rouge study.         Costs       • The derivation of, or assumptions made, regarding projected capital costs in the study.         Costs       • The derivation of, or assumptions made, regarding projected capital costs in the study.         • The derivation of, or assumptions made, regarding projected capital costs in the study.       Syman is a going concern with established mining, processing and administration toperations with and opters the study of variables and opters.         • The derivation of, or assumptions made, regarding projected capital costs in the study.       Syman is a going concern with established mining, processing and administration toperations with and optersmits with respect to cost estimates.         • The derivation of, or assumptions made, regarding projected capital costs in the study.       Syman is a going concern with established mining, processing and administration opters.         • The derivation of, or assumptions made, regarding projected capital costs in the study.       Syman is a going concern with established mining, processing and administration opters.         • The derivation of, or assumptions made in the study.       Syman is a going concern with established mining, processing and administration opters.         • The derivation of, or assumptions made in the study.       Syman is a going concern with established mining, processing and administration optenestions with respect to cost estimates.	Infrastructure	• The existence of appropriate infrastructure: availability of land for plant development, power, water, transportation (particularly for bulk commodities), labour, accommodation; or the ease with which the infrastructure can be provided or accessed.	The Syama Mine and the underground mine site are located near the two major towns of Kadiola and Sikasso. Kadiola, 55km southeast, is the regional capital while Sikasso, approximately 85 km to the northeast, is the second largest city in Mali and located close to the border with Burkina Faso.
Costs       • The derivation of, or assumptions made, regarding projected capital costs in the study.       Syma is a spin considering existing or source of treatment and refiring costs are for monositing existing costs.       • The derivation of, or assumptions made, regarding projected capital costs in the study.       Syma is a spin considering existing costs.         • The derivation of, or assumptions made, regarding projected capital costs in the study.       • The derivation of, or assumptions made, regarding projected or commodity price(s), for the principal minerals and coproducts.       Syma is a spin considering existing costs.         • The derivation of, or assumptions made, regarding projected capital costs in the study.       • The derivation of, or assumptions made, regarding projected or products.       Syma is a spin considering existing costs.         • The derivation of, or assumptions made, regarding projected capital costs in the study.       • The derivation of, or assumptions made, regarding projected or products.       Syma is a spin concern with established mining, processing and administration oparations, capital and operating budgets are prepared from first principal minerals and coproducts.         • The derivation of, or assumptions made, regarding projected arrow material.       • The derivation of arrassumptions made, regarding projected arrow material.       Syma is a spin concern with respect to cost estimates. Assign on content of deleterious elements.         • The derivation of, or assumptions made of metal or commotify price(s), cort transportation charges, penalities for failure to meet specification, etc.       Syma is a baad grade, isestimate dediste. Refining costs are not material.			Access is via formed gravel road off the sealed Sikasso to Côte d'Ivoire highway through Kadiola, and then from Fourou to site. Most consumables and supplies use this route as it can be approached either from Côte d'Ivoire through the border post at Zegoua or alternatively from Burkina Faso and Togo through Sikasso. The road north through Bananso to Farakala, on the main highway from Bamako to Sikasso, provides an alternate and shorter route to Bamako. This road is generally impassable during the wet season when the low level "bridge" at Bananso is covered with water.
Costs       • The derivation of, or assumptions made, regarding projected capital costs in the study.       • The derivation of, or assumptions made, regarding projected capital costs in the study.       • Syama is a going concern with established mining, processing and administration operations, capital and operating budgets are prepared from first principles and contractual agreements.       • The derivation of assumptions made, regarding projected capital costs in the study.       • Syama is a going concern with established mining, processing and administration operations, capital and operating budgets are prepared from first principles and contractual agreements.         • The derivation of assumptions made of metal or commodity price(s), for the principal minerals and co-products.       • The source of exchange rates used in the study.       Syama is a up on to point operations, capital and operating budgets are prepared from first principles and considering existing contractual agreements.         • The derivation of assumptions made of metal or commodity price(s), for the principal minerals and co-products.       • The source of exchange rates used in the study.       Syama produces gold doré (without problematic deleterious elements) that is subsequently refined offsite. Refining costs are not material.         • The allowances made for royalties payable, both Government and private.       • The derivation of, or assumptions made or commodity price(s) exchange rates, transportation and treatment charges, penalties, net simportation and treatment charges, penalties, net simportation and commodity price(s) exchange rates, transportation and treatment charges, penalties, net simports and or commodity price(s) exchange rates is minerals and commodity price(s) exchange rates, transportation and treatment charges,			Supporting infrastructure for the current operations has included upgrading of the 70km section of road from Kadiola to the site, refurbishment of administration buildings, plant site buildings and accommodation for housing expatriate and senior national staff. The underground operations will also use this infrastructure, with additional allowance made in the study for underground specific infrastructure on surface, such as primary ventilation fan installations, additional work shops and offices, and change rooms for underground workers.
Costs       The derivation of, or assumptions made, regarding projected capital costs in the study.       Syama is a going concern with established mining, processing and administration operations with respect to cost estimates. As part of ongoing operations, capital and operating budgets are prepared from first principles and considering existing contractula agreements.            The derivation of for exasting or source of exchange rates used in the study.        Syama is a going concern with established mining, processing and administration operations with respect to cost estimates. As part of ongoing operations, capital and operating budgets are prepared from first principles and considering existing contractual agreements.             The derivation of assumptions made of metal or commodity price(s), for the principal minerals and co-products.        Syama produces gold dor (without problematic deleterious elements) that is subsequently refined offsite. Refining costs are not material.             Derivation of transportation charges.        The basis for forecasting or source of treatment and refining charges, penalties for failure to meet specification, etc.        Syama's head grade is estimated by mine planning and flow modelling from the Mineral Resource Estimate.                   Syama's head grade is estimates have been made in USD.                   Syama's head on a planning gold price of meet and the esting and comproduction.			The site is serviced by two Internet and mobile telecommunications providers (Sotelma & Orange), in addition to a point to point satellite connection to Perth.
Costs       • The derivation of, or assumptions made, regarding projected capital costs in the study.       Syama is a going concern with established mining, processing and administration operations with respect to cost estimates. As part of ongoing operations, capital and operating budgets are prepared from first principles and considering existing contractual agreements.         • The derivation of assumptions made of metal or commodity price(s), for the principal minerals and co-products.       Syama is a going concern with established mining, processing and administration operations with respect to cost estimates. As part of ongoing operations, capital and operating budgets are prepared from first principles and considering existing contractual agreements.         • The derivation of assumptions made of metal or commodity price(s) exchange rates.       Syama is a going concern with established mining, processing and administration operations with respect to cost estimates. As part of ongoing operations, capital and operating budgets are prepared from first principles and considering existing contractual agreements.         • The source of exchange rates used in the study.       Derivation of transportation charges.       Syama is a going concern with established mining, processing contractual agreements.         • The basis for forecasting or source of treatment and refining charges, penalties for failure to meet specification, etc.       Syama is a going concern with established mining, processing contractual agreements.         • The allowances made for royalties payable, both Government and private.       • The derivation of, or assumptions made regarding revenue factors including head grade, metal or commodity price(s) exchange rates, transportation and treatment charges, pe			The current operation has a peak continuous power demand of approximately 22MW with an installed power capacity of 27MW. Power is currently supplied from a diesel fired power station. Supply of power from the national grid is being considered in the near future and was incorporated into the underground study.
<ul> <li>The derivation of assumptions made of metal or commodity price(s), for the principal minerals and coproducts.</li> <li>The source of exchange rates used in the study.</li> <li>Derivation of transportation charges.</li> <li>The basis for forecasting or source of treatment and refining charges, penalties for failure to meet specification, etc.</li> <li>The allowances made for royalties payable, both Government and private.</li> <li>The derivation of, or assumptions made regarding revenue factors including head grade, metal or commodity price(s) exchange rates, transportation and treatment charges, penalties, net smelter returns, etc.</li> <li>The derivation of assumptions made of metal or commodity price(s) exchange rates, transportation and treatment charges, penalties not of assumptions made of metal or commodity price(s) for the principal metals and coperchirete</li> </ul>	Costs	<ul> <li>The derivation of, or assumptions made, regarding projected capital costs in the study.</li> <li>The methodology used to estimate operating costs.</li> <li>Allowances made for the content of deleterious elements.</li> <li>The derivation of assumptions made of metal or commodity price(s), for the principal minerals and coproducts.</li> <li>The source of exchange rates used in the study.</li> </ul>	Syama is a going concern with established mining, processing and administration operations with respect to cost estimates. As part of ongoing operations, capital and operating budgets are prepared from first principles and considering existing contractual agreements.
<ul> <li>Derivation of transportation charges.</li> <li>The basis for forecasting or source of treatment and refining charges, penalties for failure to meet specification, etc.</li> <li>The allowances made for royalties payable, both Government and private.</li> <li>Exchange rates used for planning purposes are from consensus forecasts provided by external corporate advisers. Ad valorem Government royalties of 6% are payable on gold production.</li> <li>The derivation of, or assumptions made regarding revenue factors including head grade, metal or commodity price(s) exchange rates, transportation and treatment charges, penalties, net smelter returns, etc.</li> <li>The derivation of assumptions made of metal or commodity price(s) for the principal metals, minerals and co-products</li> </ul>			Syama produces gold doré (without problematic deleterious elements) that is subsequently refined offsite. Refining costs are not material.
<ul> <li>The basis for forecasting or source of treatment and refining charges, penalties for failure to meet specification, etc.</li> <li>The allowances made for royalties payable, both Government and private.</li> <li>The derivation of, or assumptions made regarding revenue factors including head grade, metal or commodity price(s) exchange rates, transportation and treatment charges, penalties, net smelter returns, etc.</li> <li>The derivation of assumptions made of metal or commodity price(s) exchange rates, transportation and treatment charges, penalties, net smelter returns, etc.</li> <li>The derivation of assumptions made of metal or commodity price(s) exchange rates, transportation and treatment charges, penalties, net smelter returns, etc.</li> <li>The derivation of assumptions made of metal or commodity price(s) exchange rates, transportation and treatment charges, penalties, net smelter returns, etc.</li> <li>The derivation of assumptions made of metal or commodity price(s) exchange rates, transportation and treatment charges, penalties, net smelter returns, etc.</li> <li>The derivation of assumptions made of metal or commodity price(s) exchange rates minerals and co-products</li> </ul>		Derivation of transportation charges.	Exchange rates used for planning purposes are from consensus
<ul> <li>The allowances made for royalties payable, both Government and private.</li> <li>The allowances made for royalties payable, both Government and private.</li> <li>Ad valorem Government royalties of 6% are payable on gold production.</li> <li>Ad valorem Government royalties of 6% are payable on gold production.</li> <li>Syama's head grade is estimated by mine planning and flow modelling from the Mineral Resource Estimate.</li> <li>Al valorem Government royalties of 6% are payable on gold production.</li> </ul>		The basis for forecasting or source of treatment and refining     abarran popultion for failure to most appolition at-	forecasts provided by external corporate advisers.
<ul> <li>The derivation of, or assumptions made regarding revenue factors including head grade, metal or commodity price(s) exchange rates, transportation and treatment charges, penalties, net smelter returns, etc.</li> <li>The derivation of assumptions made of metal or commodity price(s)</li> <li>The derivation of assumptions made of metal or commodity price(s)</li> <li>The derivation of assumptions made of metal or commodity price(s)</li> <li>The derivation of assumptions made of metal or commodity price(s)</li> </ul>		<ul> <li>The allowances made for royalties payable, both Government and private.</li> </ul>	Ad valorem Government royalties of 6% are payable on gold production.
• The derivation of assumptions made of metal or commodity price(s) for the principal metals minerals and co-products	Revenue factors	<ul> <li>The derivation of, or assumptions made regarding revenue factors including head grade, metal or commodity price(s) exchange rates, transportation and treatment charges, penalties, net smelter returns, etc.</li> </ul>	Syama's head grade is estimated by mine planning and flow modelling from the Mineral Resource Estimate. All revenue and cost estimates have been made in USD.
LURADAL IN UNSTRUCTURATED UNSTRUST UNIVERSITIATED UNITS CONTRACTOR FORMATS		<ul> <li>The derivation of assumptions made of metal or commodity price(s) for the principal metals, minerals and co-products</li> </ul>	The Ore Reserve is based on a planning gold price of



CRITERIA	JORC CODE EXPLANATION	COMMENTARY
Market Assessment	<ul> <li>The demand, supply and stock situation for the particular commodity, consumption trends and factors likely to affect supply and demand into the future.</li> </ul>	There is a transparent quoted market for the sale of gold.
	<ul> <li>A customer and competitor analysis along with the identification of likely market windows for the product.</li> </ul>	
	Price and volume forecasts and the basis for these forecasts.	
	<ul> <li>For industrial minerals the customer specification, testing and acceptance requirements prior to a supply contract.</li> </ul>	
Economic	<ul> <li>The inputs to the economic analysis to produce the net present value (NPV) in the study, the source and confidence of these economic inputs including estimated inflation, discount rate, etc.</li> <li>NPV ranges and sensitivity to variations in the significant assumptions and inputs.</li> </ul>	The economic assessment of the project demonstrates robust economics.
Social	<ul> <li>The status of agreements with key stakeholders and matters leading to social license to operate.</li> </ul>	Resolute assumed management of Société des Mines de Syama in May 2004. The recently completed open pit operated under the 1993 Permit Syama (No.PE-93/003) and the proposed underground will do the same.
		The selected posts requiring specific skills or experience will most likely be filled by expatriates. In addition to performing their job function, expatriate personnel will be expected to transfer knowledge and expertise to develop their Malian staff's capabilities. In the longer term it is anticipated that Malian nationals will fill most operating and management positions within the company.
		It is the intention to encourage economic development within the local community. Local contracts therefore, are let wherever possible and the company works actively with existing and emerging companies to achieve this aim.
		The Syama Mine Community Consultative Committee was established in February 2001 with representatives from local villages, the Malian Government and SOMISY. Since April 2004 the Committee has met regularly as a communication forum and to address community issues and assist with community project proposals.
Other	• To the extent relevant, the impact of the following on the project and/or on the estimation and classification of the Ore Reserves:	High seasonal rain fall events present a risk for the underground operations.
	<ul> <li>Any identified material naturally occurring risks.</li> <li>The status of material legal agreements and marketing</li> </ul>	All current government agreements and approvals are in good standing and no anticipated changes are expected.
	<ul> <li>The status of governmental agreements and approvals critical to the viability of the project, such as mineral tenement status, and government and statutory approvals. There must be reasonable grounds to expect that all necessary Government approvals will be received within the timeframes anticipated in the Pre-Feasibility or Feasibility study. Highlight and discuss the materiality of any unresolved matter that is dependent on a third party on which extraction of the reserve is contingent.</li> </ul>	
Classification	The basis for the classification of the Ore Reserves into varying confidence categories.	All Measured and Indicated Resources were converted to Probable Reserves, given the sub-level caving method.
	<ul> <li>Whether the result appropriately reflects the Competent Person's view of the deposit.</li> <li>The proportion of Probable Ore Reserves that have been</li> </ul>	
	derived from Measured Mineral Resources (if any).	



CRITERIA	JORC CODE EXPLANATION	COMMENTARY
Audits or reviews	<ul> <li>The results of any audits or reviews of Ore Reserve estimates.</li> </ul>	Snowden Mining Industry Consultants completed the Syama Underground Pre-Feasibility study in 2015 and later contributed to detailed designs incorporated in the Definitive Feasibility Study. Subsequent mining studies have been conducted in conjunction with various industry experts from external companies relevant to the areas of study. No other external audits of Ore Reserves were undertaken.
Discussion of relative accuracy/ confidence	<ul> <li>Where appropriate a statement of the relative accuracy and confidence level in the Ore Reserve estimate using an approach or procedure deemed appropriate by the Competent Person. For example, the application of statistical or geostatistical procedures to quantify the relative accuracy of the reserve within stated confidence limits, or, if such an approach is not deemed appropriate, a qualitative discussion of the factors which could affect the relative accuracy and confidence of the estimate.</li> </ul>	Treatment costs and recoveries are based on the actual performance of processing underground ore and provide a high level of confidence. Resolute has extensive experience with a similar underground operation at the Company's Mt Wright mine in Australia. This experience was combined with industry average assumptions, where required, to provide a level of accuracy and confidence
	<ul> <li>The statement should specify whether it relates to global or local estimates, and, if local, state the relevant tonnages, which should be relevant to technical and economic evaluation. Documentation should include assumptions made and the procedures used.</li> <li>Accuracy and confidence discussions should extend to specific discussions of any applied Modifying Factors that may have a material impact on Ore Reserve viability, or for which there are remaining areas of uncertainty at the current study stage.</li> <li>It is recognized that this may not be possible or appropriate in all circumstances. These statements of relative accuracy and confidence of the estimate should be compared with production data whether and the statements of the scheme whether and the statements of the scheme whether and the statements of the scheme whether and the scheme and the sc</li></ul>	that falls within the required standard for a Definitive Feasibility Study and the subsequent Mining studies. All the parameters assumed and adopted including the financial modelling and analysis have been subject to internal peer review. The Ore Reserve estimate is based on the Mineral Resource estimate. Consequently, the Ore Reserve estimate accuracy is dependent on the Mineral Resource estimate accuracy.

At 31 December 2022



## Tabakoroni

## Section 1 Sampling Techniques and Data

CRITERIA	JORC CODE EXPLANATION	COMMENTARY
Sampling techniques	<ul> <li>Nature and quality of sampling (e.g. cut channels, random chips, or specific specialised industry standard measurement tools appropriate to the minerals under investigation, such as down hole gamma sondes, or handheld XRF instruments, etc.). These examples should not be taken as limiting the broad meaning of sampling.</li> <li>Include reference to measures taken to ensure sample representivity and the appropriate calibration of any measurement tools or systems used.</li> <li>Aspects of the determination of mineralisation that are Material to the Public Report.</li> <li>In cases where 'industry standard' work has been done this would be relatively simple (e.g. 'reverse circulation drilling was used to obtain 1 m samples from which 3 kg was pulverised to produce a 30 g charge for fire assay'). In other cases more explanation may be required, such as where there is coarse gold that has inherent sampling problems. Unusual commodities or mineralisation types (e.g. submarine nodules) may warrant disclosure of detailed information.</li> </ul>	The samples were collected from reverse circulation (RC) and diamond core drill holes. RC samples were collected on 1m intervals by riffle split (dry) or by scoop (wet), to obtain a 1-3kg sample which was sent to the laboratory for crushing, splitting and pulverising to provide a 30g charge for analysis. Diamond core was sampled at 1m intervals and cut in half, to provide a 2-4kg sample, which was sent to the laboratory for crushing, splitting and pulverising to provide a 30g charge for analysis. Sampling and sample preparation protocols are industry standard and are deemed appropriate by the Competent Person.
Drilling techniques	<ul> <li>Drill type (e.g. core, reverse circulation, open-hole hammer, rotary air blast, auger, Bangka, sonic, etc.) and details (e.g. core diameter, triple or standard tube, depth of diamond tails, face-sampling bit or other type, whether core is oriented and if so, by what method, etc.).</li> </ul>	Drill types used include diamond core of PQ and HQ sizes and RC. Core is oriented at 3m down hole intervals using a Reflex Act II RD Orientation Tool.
Drill sample recovery	<ul> <li>Method of recording and assessing core and chip sample recoveries and results assessed.</li> <li>Measures taken to maximise sample recovery and ensure representative nature of the samples.</li> <li>Whether a relationship exists between sample recovery and grade and whether sample bias may have occurred due to preferential loss/gain of fine/coarse material.</li> </ul>	Drill core interval recoveries are measured from core block to core block using a tape measure. Appropriate measures are taken to maximise sample recovery and ensure the representative nature of the samples. No apparent relationship is noted between sample recovery and grade.
Logging	<ul> <li>Whether core and chip samples have been geologically and geotechnically logged to a level of detail to support appropriate Mineral Resource estimation, mining studies and metallurgical studies.</li> <li>Whether logging is qualitative or quantitative in nature. Core (or costean, channel, etc.) photography.</li> <li>The total length and percentage of the relevant intersections logged.</li> </ul>	Drill holes were geologically logged by geologists for colour, grainsize, lithology, minerals, alteration and weathering on geologically-domained intervals. Geotechnical and structure orientation data was measured and logged for all diamond core intervals. Diamond core was photographed (wet and dry). Holes were logged in their entirety (100%) and this logging was considered reliable and appropriate.



CRITERIA	JORC CODE EXPLANATION	COMMENTARY
Sub-sampling techniques	If core, whether cut or sawn and whether quarter, half or all core taken.	Diamond core was sampled at 1m intervals and cut in half to obtain a 2-4kg sample.
and sample preparation	<ul> <li>If non-core, whether riffled, tube sampled, rotary split, etc. and whether sampled wet or dry.</li> </ul>	Reverse circulation samples were collected on 1m intervals by riffle split (dry) or by scoop (wet) to obtain a 1-3kg sample.
	<ul> <li>For all sample types, the nature, quality and appropriateness of the sample preparation technique.</li> </ul>	Sample preparation for diamond core and RC samples includes oven drving, crushing to 10mm, splitting and pulverising to 85%
	<ul> <li>Quality control procedures adopted for all sub-sampling stages to maximise representivity of samples.</li> </ul>	passing $-75\mu$ m. These preparation techniques are deemed to be appropriate to the material being sampled.
	<ul> <li>Measures taken to ensure that the sampling is representative of the in-situ material collected, including for instance results for field duplicate/second-half sampling.</li> <li>Whether sample size of the</li> </ul>	Drill core coarse duplicates were split by the laboratory after crushing at a rate of 1:20 samples. Reverse circulation field duplicates were collected by the Company at a rate of 1:20 company
	• When er sample sizes are appropriate to the grain size of the material being sampled.	Sampling, sample preparation and quality control protocols are of industry standard and all attempts were made to ensure an unbiased representative sample was collected. The methods applied in this process were deemed appropriate by the Competent Person.
Quality of assay data and laboratory tests	<ul> <li>The nature, quality and appropriateness of the assaying and laboratory procedures used and whether the technique is considered partial or total.</li> <li>For geophysical tools, spectrometers, handheld XRF instruments, etc., the parameters used in determining the analysis including instrument make and model, reading times, calibrations factors applied and their derivation, etc.</li> <li>Nature of quality control procedures adopted (e.g. standards, blanks, duplicates, external laboratory checks) and whether acceptable levels of accuracy (i.e. lack of bias) and precision have been established.</li> </ul>	All samples were dispatched to ALS Bamako for gold analysis by 30g fire assay fusion with AAS instrument finish (method code Au-AA25). Over-range results were re-analysed and reported by 30g fire assay fusion with gravimetric finish (method code Au- GRA21). The analytical method was appropriate for the style of mineralisation. No geophysical tools were used to determine elemental concentrations. Quality control (QC) procedures included the use of certified standards (1:40), non-certified sand blanks (1:40), diamond core coarse duplicates (1:20) and reverse circulation field duplicates (1:20). Laboratory quality control data, including laboratory standards, blanks, duplicates, repeats, grind size results and sample weights were also captured into the digital database. Analysis of the QC sample assay results indicates that an acceptable level of accuracy and precision has been achieved.
Verification of sampling and assaying	<ul> <li>The verification of significant intersections by either independent or alternative company personnel.</li> <li>The use of twinned holes.</li> <li>Documentation of primary data, data entry procedures, data verification, data storage (physical and electronic) protocols.</li> <li>Discuss any adjustment to assay data.</li> </ul>	Verification of significant intersections have been completed by the Company personnel and the Competent Person. No drill holes within the resource area were twinned. Drill holes were logged into digital templates with lookup codes, validated and then compiled into a relational SQL 2012 database using DataShed data management software. The database has verification protocols which are used to validate the data entry. The drill hole database is backed up on a daily basis to the head office server. Assay result files were reported by the laboratory in PDF and CSV format and imported into the SQL database without adjustment or modification.



CRITERIA	JORC CODE EXPLANATION	COMMENTARY
Location of data points	<ul> <li>Accuracy and quality of surveys used to locate drill holes (collar and down-hole surveys), trenches, mine workings and other locations used in Mineral Resource estimation.</li> <li>Specification of the grid system used.</li> <li>Quality and adequacy of topographic control.</li> </ul>	Collar coordinates were picked up in UTM (WGS84) by staff surveyors using an RTK DGPS with an expected accuracy of $\pm 0.05m$ ; elevations were height above EGM96 geoid.
		Down hole surveys were collected at intervals between 5m and 30m using either a Reflex EZ-Gyro north seeking instrument or a Reflex EZ-Trac magnetic instrument in single shot or multi shot mode. A time-dependent declination was applied to the magnetic readings to determine UTM azimuth.
		Coordinates and azimuths are reported in UTM WGS84 Zone 29 North.
		Coordinates were translated to local mine grid using 1 point and rotation.
		Local topographic control is via LIDAR surveys, satellite photography and drone UAV aerial survey.
Data spacing and distribution	<ul> <li>Data spacing for reporting of Exploration Results.</li> <li>Whether the data spacing and distribution is sufficient to establish the degree of geological and grade continuity appropriate for the Mineral Resource and Ore Reserve estimation procedure(s) and classifications applied.</li> <li>Whether sample compositing has been applied.</li> </ul>	Drill hole spacing was sufficient to demonstrate geological and grade continuity appropriate for a Mineral Resource and the classifications applied under the 2012 JORC Code.
		The appropriateness of the drill spacing was reviewed by the geological technical team, both on site and head office. This was also reviewed by the Competent Person.
		Samples were collected on 1m intervals; no sample compositing is applied during sampling.
Orientation of data in relation to geological structure	<ul> <li>Whether the orientation of sampling achieves unbiased sampling of possible structures and the extent to which this is known, considering the deposit type.</li> <li>If the relationship between the drilling orientation and the orientation of key mineralised structures is considered to have introduced a sampling bias, this should be assessed and reported if material.</li> </ul>	Holes were drilled predominantly perpendicular to mineralised domains where possible.
		No orientation-based sampling bias has been identified in the data.
Sample security	The measures taken to ensure sample security.	Samples were collected from the drill site and stored on site. All samples were individually bagged and labelled with unique sample identifiers, then securely dispatched to the laboratories. All aspects of sampling and dispatch process were supervised and tracked by SOMIFI personnel.
Audits or reviews	The results of any audits or reviews of sampling techniques and data.	External audits of procedures indicate protocols are within industry standards.


### **Section 2 Reporting of Exploration Results**

CRITERIA	JORC CODE EXPLANATION	COMMENTARY
Mineral tenement and land tenure status	<ul> <li>Type, reference name/number, location and ownership including agreements or material issues with third parties such as joint ventures, partnerships, overriding royalties, native title interests, historical sites, wilderness or national park and environmental settings.</li> <li>The security of the tenure held at the time of reporting along with any known impediments to obtaining a licence to operate in the area.</li> </ul>	Tabakoroni drilling was completed within the Finkolo-Tabakoroni Exploitation Licence PE 13/19. Resolute Mining Limited has an 90% interest in Exploitation Permit PE 13/19, through its Malian subsidiary, Sociêtê des Mines de Finkolo SA (SOMIFI). The Malian Government holds a free carried 10% interest in SOMIFI. The Permits are held in good standing. Malian mining law provides that all Mineral Resources are administered by DNGM (Direction Nationale de la Géologie et des Mines) or National Directorate of Geology and Mines under the Ministry of Mines, Energy and Hydrology.
Exploration done by other parties	<ul> <li>Acknowledgment and appraisal of exploration by other parties.</li> </ul>	Etruscan Resources Inc explored Tabakoroni during 2002-2003 by auger, aircore, RC and diamond drill hole tails. The Tabakoroni area was previously explored by BHP (1988-1990) and Barrick Gold (1990) by auger, pits, trenches, RAB and diamond core drilling.
Geology	• Deposit type, geological setting and style of mineralisation.	The Tabakoroni deposit is hosted in upright tightly folded greenstone rocks of the Syama Formation, comprising interbedded basalt and sediment units, and an overlying complex sequence of deep marine and turbiditic sediments. The sequence overlying the basalts contains interbedded carbonaceous units (silts and shales) that are preferentially deformed, and which form the Tabakoroni Main Shear Zone (TMSZ) that lies along the approximate contact of the greenstone-sediment sequence. Gold mineralisation occurs within the TMSZ associated with quartz vein stockworks and stylolitic quartz reefs.
Drill hole Information	<ul> <li>A summary of all information material to the understanding of the exploration results including a tabulation of the following information for all Material drill holes: <ul> <li>easting and northing of the drill hole collar</li> <li>elevation or RL (Reduced Level – elevation above sea level in metres) of the drill hole collar</li> <li>dip and azimuth of the hole</li> <li>down hole length and interception depth</li> <li>Whole length.</li> </ul> </li> <li>If the exclusion of this information is justified on the basis that the information is not Material and this exclusion does not detract from the understanding of the report, the Competent Person should clearly explain why this is the case.</li> </ul>	<ul> <li>All information, including easting, northing, elevation, dip, azimuth, coordinate system, drill hole length, intercept length and depth are measured and recorded in UTM Zone 29 WGS84.</li> <li>The Syama belt is mostly located on the Tengrela 1/200,000 topo sheet (Sheet NC 29-XVIII).</li> <li>The Tabakoroni local grid has been tied to the UTM Zone 29 WGS84 co-ordinate system.</li> <li>Spectrum Survey and Mapping from Australia established survey control at Tabakoroni using AusPos online processing to obtain an accurate UTM Zone 29 (WGS84) and 'above geoid' RL for the origin of the survey control points.</li> <li>Accuracy of the survey measurements is considered to meet acceptable industry standards.</li> <li>Drill hole information has been tabulated for this release in the intercepts table of the accompanying text.</li> <li>For completeness the following information about the drill holes is provided:</li> <li>Easting, Northing and RL of the drill hole collars are measured and recorded in UTM Zone 29 (WGS84).</li> <li>Dip is the inclination of the drill hole from horizontal. A drill hole drilled at -60° is 60° from the horizontal.</li> <li>Down hole length is the distance down the inclination of the hole and is measured as the distance from the start of the hole down the inclination of the hole to the depth of interest or assayed interval of interest.</li> </ul>



CRITERIA	JORC CODE EXPLANATION	COMMENTARY
Data aggregation methods	<ul> <li>In reporting Exploration Results, weighting averaging techniques, maximum and/or minimum grade truncations (e.g. cutting of high grades) and cut-off grades are usually Material and should be stated.</li> <li>Where aggregate intercepts incorporate short lengths of high-grade results and longer lengths of low-grade results, the procedure used for such aggregation should be stated and some typical examples of such aggregations should be shown in detail.</li> <li>The assumptions used for any reporting of metal equivalent values should be clearly stated.</li> </ul>	No new exploration results have been reported in this release. Metal equivalent values are not used in reporting.
Relationship between mineralisation widths and intercept lengths	<ul> <li>These relationships are particularly important in the reporting of Exploration Results.</li> <li>If the geometry of the mineralisation with respect to the drill hole angle is known, its nature should be reported.</li> <li>If it is not known and only the down hole lengths are reported, there should be a clear statement to this effect (e.g. 'down hole length, true width not known').</li> </ul>	The majority of the Tabakoroni mineralisation is vertical. There is one domain which dips at 45° to the west. The majority of the drill holes are planned at a general inclination of -60 degrees east and as close to perpendicular to the ore zone as possible. At the angle of the drill holes and the dip of the ore zones, the reported intercepts will be slightly more than true width.
Diagrams	<ul> <li>Appropriate maps and sections (with scales) and tabulations of intercepts should be included for any significant discovery being reported These should include, but not be limited to a plan view of drill hole collar locations and appropriate sectional views.</li> </ul>	Relevant maps, diagrams and tabulations are included in the body of text.
Balanced reporting	<ul> <li>Where comprehensive reporting of all Exploration Results is not practicable, representative reporting of both low and high grades and/or widths should be practiced to avoid misleading reporting of Exploration Results.</li> </ul>	Mineral Resources are being reported in this announcement. No new exploration results have been reported in this release.
Other substantive exploration data	<ul> <li>Other exploration data, if meaningful and material, should be reported including (but not limited to): geological observations; geophysical survey results; geochemical survey results; bulk samples – size and method of treatment; metallurgical test results; bulk density, groundwater, geotechnical and rock characteristics; potential deleterious or contaminating substances.</li> </ul>	No geophysical and geochemical data or any additional exploration information has been reported in this release, as they are not deemed relevant to the release.
Further work	<ul> <li>The nature and scale of planned further work (e.g. tests for lateral extensions or depth extensions or large-scale stepout drilling).</li> <li>Diagrams clearly highlighting the areas of possible extensions, including the main geological interpretations and future drilling areas, provided this information is not commercially sensitive.</li> </ul>	Depth extension drilling is planned to test the down-dip potential of the Tabakoroni ore body at depth, and beneath the current limit of drilling.



### Section 3 Estimation and Reporting of Mineral Resources

CRITERIA	JORC CODE EXPLANATION	COMMENTARY
Database integrity	<ul> <li>Measures taken to ensure that data has not been corrupted by, for example, transcription or keying errors, between its initial collection and its use for Mineral Resource estimation purposes.</li> <li>Data validation procedures used.</li> </ul>	Data has been compiled into a relational SQL database; the setup of this database precludes the loading of data which do not meet the required validation protocols. The data is managed using DataShed <sup>©</sup> drill hole management software using SQL database techniques. Validation checks are conducted using SQL and DataShed <sup>©</sup> relational database standards. Data has also been checked against original hard copies for 100% of the data, and where possible, loaded from original data sources.
		Resolute completed the following basic validation checks on the data supplied prior to resource estimation:
		<ul> <li>Drill holes with overlapping sample intervals.</li> <li>Sample intervals with no assay data or duplicate records.</li> <li>Assay grade ranges.</li> <li>Collar coordinate ranges.</li> <li>Valid hole orientation data.</li> </ul>
		There are no significant issues identified with the data.
Site visits	<ul> <li>Comment on any site visits undertaken by the Competent Person and the outcome of those visits.</li> <li>If no site visits have been undertaken indicate why this is the case.</li> </ul>	Mrs Susan Havlin, an employee of Snowden Optiro Pty Ltd and a Member of the Australasian Institute of Mining and Metallurgy is the Competent Person who has visited this site in February and October 2019.
		All aspects of drilling, sampling and mining are considered by the Competent Persons to be of a high industry standard.
Geological interpretation	<ul> <li>Confidence in (or conversely, the uncertainty of) the geological interpretation of the mineral deposit.</li> <li>Nature of the data used and of any assumptions made.</li> <li>The effect, if any, of alternative interpretations on Mineral Resource estimation.</li> <li>The use of geology in guiding and controlling Mineral Resource estimation.</li> <li>The factors affecting continuity both of grade and geology.</li> </ul>	The digital database used for the interpretation included logged intervals for the key stratigraphic zones of Tabakoroni. Detailed geological logs were available in hardcopy and digital and reviewed where necessary.
		There is a high level of confidence for the interpretation of the Tabakoroni Main Shear Zone (TMSZ) due to the close-spaced grade control drilling at surface and the confirmation of the position in the current oxide pits. Since an independent structural model was created there is high level of confidence in the geological interpretation of the minor lodes adjacent to the TMSZ.
		Wireframes used to constrain the estimation are based on drill hole intercepts and geological boundaries. All wireframes at Tabakoroni have been constructed to a 1g/t Au cut-off grade for shape consistency.
		The mineralisation in the TMSZ is generally quite consistent and drill intercepts clearly define the shape of the mineralised zones with limited options for large scale alternate interpretations.
Dimensions	<ul> <li>The extent and variability of the Mineral Resource expressed as length (along strike or otherwise), plan width, and depth below surface to the upper and lower limits of the Mineral Resource.</li> </ul>	The mineral resource at Tabakoroni comprises four individual domains. The main zone is the TMSZ, which extends for approximately 1,800 metres along strike; the sub-vertical dipping gold mineralised zone width varies between 1.5 and 15 metres, with an average thickness of 5 metres. The Mineral Resource is limited in depth by drilling, which extends from surface to a maximum depth of approximately 450 metres vertically.
		There is a zone parallel to the TMSZ which is generally at depth and not as consistent; this is dominantly in the central part of the deposit. The northeast (NE) domain is a zone which is striking at 20° and is sub vertical in the north of the deposit. The southern lode is shallow westerly-dipping lodes in the southern and central



CRITERIA	JORC CODE EXPLANATION	COMMENTARY
		portion of the deposit. The whole of the Tabakoroni deposit, including domains additional to the TMSZ, extends for 450 metres in the horizontal plane.
Estimation and modelling techniques	<ul> <li>The nature and appropriateness of the estimation technique(s) applied and key assumptions, including treatment of extreme grade values, domaining, interpolation parameters and maximum distance of extrapolation from data points. If a computer assisted estimation method was chosen include a description of computer software and parameters used.</li> <li>The availability of check estimates, previous estimates and/or mine production records and whether the Mineral Resource estimate takes appropriate account of such data.</li> <li>The assumptions made regarding recovery of by products</li> </ul>	Estimation was completed in Datamine Studio RM using an Ordinary Kriged model to estimate the gold grade. Grades were estimated into parent block of 5 mE by 10 mN by 5 mRL with sub- celling down to 1mE by 2 mN by 1 mRL was employed for resolution of the mineralisation boundaries as defined by wireframes. The drill spacing at Tabakoroni varies from 12.5 by 12.5 metres for grade control to between 25 and 50 metres for the exploration holes. Drillhole sample data was flagged using domain codes
	<ul> <li>Estimation of deleterious elements or other non-grade variables of economic significance (e.g. sulphur for acid mine drainage characterization)</li> </ul>	generated from three-dimensional mineralisation domains. The grade control samples and exploration samples were composited to 1 metre intervals.
	<ul> <li>In the case of block model interpolation, the block size in relation to the average sample spacing and the search employed.</li> </ul>	Variogram orientations were largely controlled by the strike of the mineralisation and downhole variography. Variograms for estimation purposes were determined for each domain.
	<ul> <li>In the case of block model interpolation, the block size in relation to the average sample spacing and the search employed.</li> </ul>	Kriging neighbourhood analysis was performed to optimise the block size, sample numbers and discretisation levels with the goal of minimising conditional bias in the gold grade estimates.
	Any assumptions behind modelling of selective mining units.	Mineralisation domains were treated as hard boundaries in the
	<ul> <li>Any assumptions about correlation between variables.</li> <li>Description of how the geological interpretation was used to control the resource estimates.</li> </ul>	estimation process while oxidation surfaces were treated as soft boundaries for gold, sulphide sulphur and organic carbon. A hard boundary was utilised in the estimation of arsenic between
	<ul> <li>Discussion of basis for using or not using grade cutting or capping</li> </ul>	fresh material and transitional material following a boundary analysis review.
	<ul> <li>The process of validation, the checking process used, the comparison of model data to drill hole data, and use of reconciliation data if available.</li> </ul>	Three search passes were used, with the first search pass set to the range of the variogram for each element. A minimum of 8 and a maximum of 30 samples were used. The search stayed the same for the second pass but was increased by a factor of 2 for the third and final pass. The minimum number of samples was reduced to 6 for the second pass and 4 for the third pass.
		No deleterious elements were found in the ore.
		No selective mining units have been assumed.
		Top cuts were applied to reduce the variability of the data and to remove the outliers.
		The estimated block model grades were visually validated against the input drillhole data and comparisons were carried out against the drillhole data and by northing and elevation slices. Global comparison between the input data and the block grades for each variable is considered acceptable (±10%).
		Comparison with the mine production to date was carried out and was within an acceptable limit.
Moisture	<ul> <li>Whether the tonnages are estimated on a dry basis or with natural moisture, and the method of determination of the moisture content.</li> </ul>	All tonnages have been estimated on a dry basis.
Cut-off parameters	<ul> <li>The basis of the adopted cut-off grade(s) or quality parameters applied.</li> </ul>	Mineral Resources for open pit extraction have been reported at a 1 g/t Au grade cut-off and above a US\$2000/oz optimised shell.
		The Mineral Resources for underground mining are undiluted and the mineralised blocks (within the mineralisation wireframes) have been reported within MSO wireframes created at



CRITERIA	JORC CODE EXPLANATION	COMMENTARY
		US\$2,000/oz which is equivalent to 1.75 g/t Au cut-off grade.
Mining factors or assumptions	• Assumptions made regarding possible mining methods, minimum mining dimensions and internal (or, if applicable, external) mining dilution. It is always necessary as part of the process of determining reasonable prospects for eventual economic extraction to consider potential mining methods, but the assumptions made regarding mining methods and parameters when estimating Mineral Resources may not always be rigorous. Where this is the case, this should be reported with an explanation of the basis of the mining assumptions made.	A Pre-Feasibility study determined the mining method would be by long hole open stoping. No Mineral Resource margin (external) dilution has been modelled. A minimum stope dip of 30 degrees on the footwall was applied. More rigorous mining assumptions and parameters will be applied during the conversion to Ore Reserves.
Metallurgical factors or assumptions	• The basis for assumptions or predictions regarding metallurgical amenability. It is always necessary as part of the process of determining reasonable prospects for eventual economic extraction to consider potential metallurgical methods, but the assumptions regarding metallurgical treatment processes and parameters made when reporting Mineral Resources may not always be rigorous. Where this is the case, this should be reported with an explanation of the basis of the metallurgical assumptions made.	No metallurgical factors or assumptions have been made during the resource estimation process as these will be addressed during the conversion to Ore Reserves.
Environmental factors or assumptions	<ul> <li>Assumptions made regarding possible waste and process residue disposal options. It is always necessary as part of the process of determining reasonable prospects for eventual economic extraction to consider the potential environmental impacts of the mining and processing operation. While at this stage the determination of potential environmental impacts, particularly for a green fields project, may not always be well advanced, the status of early consideration of these potential environmental impacts should be reported. Where these aspects have not been considered this should be reported with an explanation of the</li> </ul>	It is a requirement of Decree No.03-594/P-RM of 31 December 2003 of Malian law that an Environmental and Social Impact Study (Étude d'Impact Environmental et Social – EIES) must be undertaken to update the potential environmental and social impacts of the mine's redevelopment. The EIES for the Syama Gold Mine (including Tabakoroni) was approved in November 2007 and an Environment Permit (07- 0054/MEA – SG) was issued by the Ministry of Environment and Sanitation on 22 November 2007. The Ministry of Environment conducts timely reviews of the Syama Gold Mine to ensure that Company maintains compliance with the EIES guidelines.
	environmental assumptions made.	At Syama and Tabakoroni, there are three key practices for disposal of wastes and residues namely, stacking of waste rock from open pit mining; storage of tailings from mineral processes; and "tall-stack dispersion" of sulphur dioxide from the roasting of gold bearing concentrate. All waste disposal practices are in accordance with the guidelines in the EIES.
		The Environmental and Social Impact Study – "Société des Mines de Syama, Syama Gold Mine, Mali", dated 2007 indicated there was minimal potential for acid mine drainage from waste rock due to the elevated carbonate content which buffers a potential acid generation. Resolute maintains a plan for progressive rehabilitation of waste rock landforms as part of ongoing mine development and waste rock dumping.
		The landform of tailings impoundments does not have a net acid generating potential. The largest volume is flotation tailings where the sulphide minerals have already been removed from the host rock. Its mineralogy includes carbonates which further buffer any acid-formation potential from sulphides that may also be present.
		Cyanide levels in the leached-calcine tailings are typically less than 50 ppm in the weak acid dissociable form. Groundwater away from the tailings landform is intercepted by trenches and sump pumps.
		Sulphur dioxide is generated from the roasting of gold concentrate so that gold can be extracted and refined. Tall-Stack "dispersion" of the sulphur dioxide emission is monitored continuously. Prevailing weather and dissipation of the sulphur dioxide is modelled daily to predict the need to pause the



CRITERIA	JORC CODE EXPLANATION	COMMENTARY
		roasting process to meet the air quality criteria set out in the Environmental and Social Impact Study.
Bulk density	<ul> <li>Whether assumed or determined. If assumed, the basis for the assumptions. If determined, the method used, whether wet or dry, the frequency of the measurements, the nature, size and representativeness of the samples.</li> <li>The bulk density for bulk material must have been measured by methods that adequately account for void spaces (vugs, porosity, etc), moisture and differences between rock and alteration zones within the deposit.</li> <li>Discuss assumptions for bulk density estimates used in the evaluation process of the different materials.</li> </ul>	Site personnel have completed numerous bulk density comparative estimates on HQ drill core to assess variability using the Archimedes method of dry weight versus weight in water. This method was used for 76% of the bulk density measurements. The other 34% is by unknown method. On the basis of the data collected the following SG estimates were applied to the model by weathering type: • Oxide 2.12 t/m <sup>3</sup> • Transitional 2.38 t/m <sup>3</sup> • Fresh 2.72 t/m <sup>3</sup>
Classification	<ul> <li>The basis for the classification of the Mineral Resources into varying confidence categories.</li> <li>Whether appropriate account has been taken of all relevant factors (i.e. relative confidence in tonnage/grade estimations, reliability of input data, confidence in continuity of geology and metal values, quality, quantity and distribution of the data).</li> <li>Whether the result appropriately reflects the Competent Person's view of the deposit.</li> </ul>	The Measured Mineral Resource classification is based on good confidence in the geology and gold grade continuity with 12.5 m x 12.5 m spaced drillhole density in the central part of the deposit. The Indicated Mineral Resource classification is based on good confidence in the geology and gold grade continuity with less than 50 m x 50 m spaced drillhole density in the central part of the deposit. The Inferred Mineral Resource classification is applied to extensions of mineralised zones on the margins of the deposit where drill spacing is more than 50 m x 50 m and the extents of mineralisation at depth. The validation of the block model has confirmed satisfactory correlation of the input data to the estimated grades and reproduction of data trends.
Audits or reviews	<ul> <li>The results of any audits or reviews of Mineral Resource estimates.</li> </ul>	The Mineral Resource has been audited internally and in conjunction with resource consultants at Snowden Optiro Pty Ltd as part of the routine validation process. There has been an external review of the Mineral Resource estimation completed by Cube Consulting Pty Ltd in February 2022.
Discussion of relative accuracy/ confidence	<ul> <li>Where appropriate a statement of the relative accuracy and confidence level in the Mineral Resource estimate using an approach or procedure deemed appropriate by the Competent Person. For example, the application of statistical or geostatistical procedures to quantify the relative accuracy of the resource within stated confidence limits, or, if such an approach is not deemed appropriate, a qualitative discussion of the factors that could affect the relative accuracy and confidence of the estimate.</li> <li>The statement should specify whether it relates to global or local estimates, and, if local, state the relevant tonnages, which should be relevant to technical and economic evaluation. Documentation should include assumptions made and the procedures used.</li> <li>These statements of relative accuracy and confidence of the estimate should be compared with production data, where available.</li> </ul>	The relative accuracy of the Mineral Resource estimate is reflected in the reporting of Measured, Indicated and Inferred resource categories as defined by 2012 JORC Code guidelines. The estimate is considered to be relevant to an annual level of reporting of tonnage and grade. The estimation was compared with the production history at Tabakoroni and it is within 15%, which is within the limits for the relevant classifications.



### Section 4 Estimation and Reporting of Ore Reserves

CRITERIA	JORC CODE EXPLANATION	COMMENTARY
Mineral Resource estimate for conversion to Ore Reserves	<ul> <li>Description of the Mineral Resource estimate used as a basis for the conversion to an Ore Reserve.</li> <li>Clear statement as to whether the Mineral Resources are reported additional to, or inclusive of, the Ore Reserve.</li> </ul>	The Ore Reserves are based on the Mineral Resource estimate detailed in the ASX release dated December 2021, prepared by Optiro Pty Ltd. The resource was reported above a 1.75 g/t gold grade cut-off, based on an equivalent gold price of US\$2,000/oz and an underground mining method utilising long hole stoping mining methods with paste fill. Material below this cut-off is not included in the Mineral Resource.
		Ore Reserves are the material reported as a sub-set of the resource, that which can be extracted from the mine and processed with an economically acceptable outcome. The resource is depleted for open pit material already mined and future cut back planned for Taba North.
		Mineral Resources are reported inclusive of Ore Reserves.
Site visits	<ul> <li>Comment on any site visits undertaken by the Competent Person and the outcome of those visits.</li> <li>If no site visits have been undertaken indicate why this is the case.</li> </ul>	The Competent Person, Mr Gito Patani, is a full-time employee of Resolute Mining Ltd and a Member of the Australasian Institute of Mining and Metallurgy. He conducted a site visit to the project area in January 2022. Travel to site was restricted during the 2021 due to covid-19 travel restrictions, but weekly contact with site teams was maintained throughout the period.
		The site visit reviewed the project site and proposed portal location in the mined out Namakan Pit western wall, a review of current operations at both Syama and Tabakoroni, existing open pit infrastructure available for immediate underground use, a review of selected drill core and various meetings were held with site personnel and key stakeholders to the study. A pit wall failure was noticed in the eastern wall of the Namakan pit. This failure was monitored since then through the past wet season and have stabilised at its natural angle of repose and does not pose further material risk to the proposed underground portal location.

At 31 December 2022



CRITERIA	JORC CODE EXPLANATION	COMMENTARY
Study status	<ul> <li>The type and level of study undertaken to enable Mineral Resources to be converted to Ore Reserves.</li> </ul>	A Pre-Feasibility Study was completed on Tabakoroni Underground in late 2020.
	<ul> <li>The Code requires that a study to at least Pre-Feasibility Study level has been undertaken to convert Mineral Resources to Ore Reserves. Such studies will have been carried out and will have determined a mine plan that is technically achievable and economically viable, and that material Modifying Factors have been considered.</li> </ul>	Tabakoroni open pit has been in continuous mining operation since August 2018. During this time the performance of the open pit has shown a positive reconciliation between mineral resources and gold production and delivered positive cashflows. Data from the current open pit operations which also applies to the intended underground operation, such as existing infrastructure and ore haulage cost, were used as part of the underground study. The open pit reconciliation data was not considered as it relates to oxide ore only and the underground will focus on fresh ore only.
		No underground operations have been undertaken at Tabakoroni yet. However, underground operations and processing of similar underground material have been undertaken for several years at the nearby Syama Mine where the Tabakoroni Underground ore will also be processed under the current toll treatment agreement, providing actual data to further support the Tabakoroni study assumptions.
		<ul> <li>Primary contributors to the study were:</li> <li>Optiro Pty Ltd – Mineral Resources.</li> <li>Solid Geology Pty Ltd – Structural Model.</li> <li>AMC Consultants – mining geotechnical study and portal review.</li> <li>Piteau – dewatering.</li> <li>Digby Wells – environmental and social impact assessment.</li> <li>Outotec – backfill, concentrate roasting, floatation plant.</li> <li>Osprey – security assessment.</li> <li>Practara – economic evaluation.</li> <li>ALS – metallurgical variability testing.</li> <li>Resolute Mining Ltd – mine design and scheduling, processing and overall study management.</li> </ul>
Cut-off parameters	<ul> <li>The basis of the cut-off grade(s) or quality parameters applied.</li> </ul>	A marginal cut-off grade (COG) of 2.5g/t gold has been applied for Tabakoroni Underground. This is based on long hole open stoping with paste fill at a gold price of U\$1,500/oz, metallurgical recovery of 78%, and includes royalties of 6%.
		Individual underground zones and levels were further tested to confirm each area achieves the required financial returns to offset the capital investment required to access that zone or level. Sub-economical areas were removed from the reserves.

At 31 December 2022



#### Mining factors or assumptions

- The method and assumptions used as reported in the Pre-Feasibility or Feasibility Study to convert the Mineral Resource to an Ore Reserve (i.e. either by application of appropriate factors by optimization or by preliminary or detailed design).
- The choice, nature and appropriateness of the selected mining method(s) and other mining parameters including associated design issues such as pre-strip, access, etc.
- The assumptions made regarding geotechnical parameters (e.g. pit slopes, stope sizes, etc.), grade control and pre-production drilling.
- The major assumptions made and Mineral Resource model used for pit and stope optimization (if appropriate).
- The mining dilution factors used.
- The mining recovery factors used.
- Any minimum mining widths used.
- The manner in which Inferred Mineral Resources are utilized in mining studies and the sensitivity of the outcome to their inclusion.
- The infrastructure requirements of the selected mining methods.

The Tabakoroni mineralisation is mostly steeply dipping, between 80 to 90°, with an average width of 4m to 15m. Some mineralisation is located parallel to, and adjacent to the main Tabakoroni mineralisation. These shallower dipping zones are located predominantly in a competent basalt zone, ranging in dip between 40° and 80°, with an average width of 2m to 10m.

Long hole open stoping is considered the most suitable mining method to extract the underground deposit. Long term support will be providing by backfilling the stopes with cemented paste in the main mineralised zone, create by adding binder to a large supply of highly weathered oxide waste already available on site from the previous open pit mines. Shallower dipping zones in the competent basalt zones will also use open stoping with pillars, where appropriate.

Longitudinal sub-level caving and open stoping with rock fill were also reviewed but not considered appropriate methods. The mineralisation is too long and narrow to use sub-level caving and it would result in caving breaking through into the current open pit, increasing inrush risk for the underground. Paste fill was selected over waste fill as it provides a better cashflow with a top-down mining method, provides improved stability and in general there is a lack of suitable fresh rock to use as backfill material. It also improves the extraction of parallel mineralised zones which was not possible with open stopes and loose rock fill.

The reported Ore Reserve estimates for Tabakoroni are based on Deswik.SO (Mineable Shape Optimiser / MSO) results, followed by detailed mine design in Deswik.CAD and activity-based task and resource scheduling in Deswik.Sched. Economic modelling was performed in consultation with an external financial consultant experienced in Malian mining economic modelling.

Stope dilution is considered separately for hangingwall and footwall conditions as part of the MSO optimisation. Equivalent Linear Overbreak Slough (ELOS) is applied based on geotechnical domaining, resulting in 0.5m dilution in competent (basalt) ground to 2.0m in poor, highly structured zones. The average dilution considered is 0.5 to 1.0m, applied individually to both hangingwall and footwall conditions. A global mine recovery of 90% was applied.

Minimum Mining Width used was 3.0m, but average stoping widths range between 4.5m and 10.0m. Level spacings are selected at 20m vertical, floor to floor. Stope lengths of 10m to 50m are recommended based on the geotechnical modelling and chosen level spacing. The study conservatively limited stope lengths to 20m, which will be further optimised during actual operations. For the shallower dipping stopes a minimum footwall dip of 40° was selected to ensure blasted material can be moved effectively to the drawpoint for loading during production.

Costs are based on existing contract mining rates from the nearby Syama Operation with a contract proposal provided for the study to account for potential changes expected at Tabakoroni, contract haulage rates to the Syama process plant from the current Tabakoroni open pit operation, processing costs are based on the current Syama process plant and site costs which are understood with a high degree of accuracy from current operations.

Equipment for the underground were selected considering the selected mining method, planned production rate, existing experience and equipment in operation at Syama Underground. Loading will be done by 21t loaders from the development headings and stopes and hauled by 63t trucks to surface via a decline. From surface stockpiles ore will be hauled to the process plant at Syama using the current open pit truck haulage fleet and waste will dumped directly onto the existing open pit waste dumps.

The mine plan includes an insignificant amount of Inferred Resources, which is not material to the outcome of the Ore Reserves. Inferred Resources were considered when positioning life

mineralogy to meet the specifications?

At 31 December 2022



CRITERIA	JORC CODE EXPLANATION	COMMENTARY
		of mine infrastructure but does not materially influence the outcome of the current reserves.
		<ul> <li>Existing open pit infrastructure and a dedicated haul road to Syama is available for immediate use by the underground operation. The only additional infrastructure consists of:</li> <li>A power shed to house diesel generators for power generation. Existing diesel generators will be relocated from the current Syama operation as part of their power upgrades and the power shed is just for weather protection.</li> <li>Paste plant for paste fill generations.</li> <li>Explosives magazine (open pit operations did minimal blasting and did not establish an explosive magazine).</li> <li>Underground primary ventilation fans.</li> <li>Upgraded security control facilities.</li> <li>Minor fit-out to the existing open pit offices and workshops to comply with underground requirements (change house, lamp room, etc).</li> <li>Float circuit modifications to allow the existing Syama Oxide plant to process sulphide ore.</li> </ul>
Metallurgical factors or assumptions	<ul> <li>The metallurgical process proposed and the appropriateness of that process to the style of mineralization.</li> <li>Whether the metallurgical process is well-tested</li> </ul>	Metallurgical test work was conducted on multiple samples, representative of the spatial and mineralogical distribution of the deposit. The tests indicated that, similarly to the Syama ore, the Tabakoroni ore can be double refractory in nature due to locking
	technology or novel in nature.	of gold within the sulphides and organic carbon. Processing of
	<ul> <li>The nature, amount and representativeness of metallurgical test work undertaken, the nature of the metallurgical domaining applied and the corresponding</li> </ul>	has been in operation for several years and is well understood, consisting of the following stages:
	metallurgical recovery factors applied. <ul> <li>Any assumptions or allowances made for deleterious</li> </ul>	<ul> <li>Crushing and grinding utilising the existing oxide process plant infrastructure</li> </ul>
	elements.	<ul> <li>Gravity gold recovery utilising the existing oxide gravity circuit</li> </ul>
	<ul> <li>The existence of any bulk sample or pilot scale test work and the degree to which such samples are considered representative of the ore body as a whole.</li> </ul>	<ul> <li>Flotation to produce a sulphide rich concentrate through a new flotation circuit, prior to blending with the current Syama concentrate circuit for further;</li> </ul>
	<ul> <li>For minerals that are defined by a specification, has the ore reserve estimation been based on the appropriate</li> </ul>	Concentrate thickening.     Concentrate thickening.

- Roasting, followed by calcine quench and wash. 0
  - Carbon-in-leach (CIL).
  - 0 Tailings disposal. 0

The oxide crushing and grinding circuit has an oxide capacity of 1.5Mtpa, with a modelled sulphide throughput capacity of up to 1.0Mtpa. The Syama roaster, CIL circuit and tailings storage facility has enough capacity to process the additional concentrate.

A number of metallurgical test work programmes have been conducted on a range of Tabakoroni ore samples to date. The most recent variability test programme, conducted as part of the PFS, focussed on optimising the flowsheet to then assess the metallurgical performance of the various mineralised domains to be encountered. A total gold recovery of 83% has been assumed based on test results to date. This is in line with similar ore being processed at Syama.



CRITERIA	JORC CODE EXPLANATION	COMMENTARY
Environmental	<ul> <li>The status of studies of potential environmental impacts of the mining and processing operation. Details of waste rock characterization and the consideration of potential sites, status of design options considered and, where applicable, the status of approvals for process residue storage and waste dumps should be reported.</li> </ul>	The Tabakoroni mining area and haul road to Syama are covered under current environmental approval and permitting. An ESIA update and approval for the changes brought about by the new underground operation is currently being conducted by an experienced local consultant as per Malian regulations, with external specialist consultant as per Malian regulations, with only considers the changes due to the existing Tabakoroni operation going underground as the current open pit operations and processing at Syama is already covered under existing approvals (Refer Section 3). A draft ESIA report for the changes has been submitted for approval and is pending government approval. No reasons are known to the Competent Person why this approval will not be granted.
		An active waste rock characterisation program has been put in place for Tabakoroni open pit operation. Underground waste will be co-disposed underground with paste fill where possible, with the remainder being stored on the current open pit waste dump under the current waste rock management protocols to prevent potentially acid forming waste rock from contaminating water sources. The current waste dump has much more space than is required by the underground operation.
		Ore Reserves from Tabakoroni will be processed at Syama and tailings storage will be impounded in existing footprint area approved in the current ESIA. Progressive raising of the tailings occurs regularly with the 9th lift completed in 2019. Routine progress on the monitoring is reported to government and at stakeholder meetings in concert with routine inspections by government representatives.
		Arsenic is naturally occurring in the Tabakoroni mineralisation. A groundwater characterisation programme was conducted as part of the ESIA submission and did not identify any adverse impacts on water being discharged to the environment.



CRITERIA	JORC CODE EXPLANATION	COMMENTARY
Infrastructure	<ul> <li>The existence of appropriate infrastructure: availability of land for plant development, power, water, transportation (particularly for bulk commodities), labour, accommodation; or the ease with which the infrastructure can be provided or accessed</li> </ul>	All required mining infrastructure is already in place at the Tabakoroni open pit mine and processing and camp facilities at Syama Mine, except for the additions required specifically for the Tabakoroni underground, consisting of:
		<ul> <li>A power shed to house diesel generators for power generation. Existing diesel generators will be relocated from the current Syama operation as part of their power upgrades.</li> <li>Paste plant for paste fill generation.</li> <li>Explosives magazine.</li> <li>Upgraded security control facilities.</li> <li>Minor fit-out to the existing open pit offices and workshops to comply with underground requirements, such as change rooms and lamp rooms.</li> <li>Float circuit modifications to allow the existing Syama Oxide plant to process Tabakoroni sulphide ore.</li> </ul>
		Tabakoroni is linked to the Syama Mine through a purpose built 35km haul road. The Syama Mine is located near the two major towns of Kadiola and Sikasso. Kadiola, 55km southeast, is the regional capital while Sikasso, approximately 85km to the northeast, is the second largest city in Mali and located close to the border with Burkina Faso.
		Access is via formed gravel road off the sealed Sikasso to Côte d'Ivoire highway through Kadiola, and then from Fourou to site. Most consumables and supplies use this route as it can be approached either from Côte d'Ivoire through the border post at Zegoua or alternatively from Burkina Faso and Togo through Sikasso. The road north through Bananso to Farakala, on the main highway from Bamako to Sikasso, provides an alternate and shorter route to Bamako. This road is generally impassable during the wet season when the low level "bridge" at Bananso is covered with water.
		The 70km section of road from Kadiola to the site was upgraded for the Syama Mine. In addition to the current open pit infrastructure left behind by open pit operations at Tabakoroni, the Syama Mine provides access to administration buildings, plant site buildings and accommodation for housing expatriate and senior national staff.
		Tabakoroni site is serviced through a local telecommunications provider Orange. Provision is made in the study to allow have a dedicated link to Syama Mine, from where two Internet and mobile telecommunications providers (Sotelma & Orange) are available, in addition to a point to point satellite connection to Perth.



CRITERIA	JORC CODE EXPLANATION	COMMENTARY
Costs	<ul> <li>The derivation of, or assumptions made, regarding projected capital costs in the study.</li> <li>The methodology used to estimate operating costs.</li> <li>Allowances made for the content of deleterious elements.</li> <li>The derivation of assumptions made of metal or commodity price(s), for the principal minerals and coproducts.</li> <li>The source of exchange rates used in the study.</li> <li>Derivation of transportation charges.</li> <li>The basis for forecasting or source of treatment and refining charges, penalties for failure to meet specification, etc.</li> <li>The allowances made for royalties payable, both Government and private.</li> </ul>	<ul> <li>Cost estimates are based mostly on existing operations at Syama and Tabakoroni, with modifications where identified in the study. Current operations, and existing costs were used for:</li> <li>Ore haulage to Syama for processing under the current open pit haulage contract.</li> <li>Owner-operated processing, general and administration costs are shared between the oxide plant and the sulphide plant at Syama, which processes the current Syama UG orebody. These costs are well understood, and minor changes were included based on Tabakoroni specific metallurgical variability test work results.</li> <li>Power generation cost utilising the current Syama diesel generators.</li> <li>Development and production rates are based on the current Syama mining contract schedule of rates, with updated quotes provided by the contractor as required for mining method changes expected at Tabakoroni.</li> <li>Ground support consumables, fuel, explosives, bulk cement based on current Syama mining contract.</li> <li>Mine closure costs (existing open pit component).</li> <li>PFS level cost estimates were calculated for: <ul> <li>Paste fill cost – based on locally supplied bulk cement prices and an independent paste fill study to determine consumption rate.</li> <li>Environmental and mine closure costs specific to underground.</li> </ul> </li> <li>The oxide plant produces gold doré (without problematic deleterious elements) that is subsequently refined offsite. Refining costs are allowed for as per current Syama Mine, but are not material.</li> <li>Ad valorem Government royalties of 6% are payable on gold production.</li> </ul>
Revenue factors	<ul> <li>The derivation of, or assumptions made regarding revenue factors including head grade, metal or commodity price(s) exchange rates, transportation and treatment charges, penalties, net smelter returns, etc.</li> <li>The derivation of assumptions made of metal or commodity price(s), for the principal metals, minerals and co-products.</li> </ul>	A gold price of US\$1,500/oz formed the basis of the Ore Reserves. Gold price used for planning purposes is from consensus forecasts provided by external corporate advisers. No penalties are incurred, nor is any revenue received from co- products.
Market assessment	<ul> <li>The demand, supply and stock situation for the particular commodity, consumption trends and factors likely to affect supply and demand into the future.</li> <li>A customer and competitor analysis along with the identification of likely market windows for the product.</li> <li>Price and volume forecasts and the basis for these forecasts.</li> <li>For industrial minerals the customer specification, testing and acceptance requirements prior to a supply contract.</li> </ul>	The market for gold is robust with prevailing gold price being well above US\$1,500/oz. Supply and demand are not considered material to the Ore Reserve calculations.



CRITERIA	JORC CODE EXPLANATION	COMMENTARY
Economic	<ul> <li>The inputs to the economic analysis to produce the net present value (NPV) in the study, the source and confidence of these economic inputs including estimated inflation, discount rate, etc.</li> <li>NPV ranges and sensitivity to variations in the significant assumptions and inputs.</li> </ul>	<ul> <li>The financial evaluation undertaken as part of the evaluation indicated a positive net present value (NPV) at a 7% annual discount rate. The following major economic inputs were used:</li> <li>Costs as previous described.</li> <li>Gold price of US\$1500/oz.</li> <li>Royalties of 6%.</li> <li>Effective tax rate of 25% (Corporate tax rate of 30% with 5% discount provided by the Malian government to Tabakoroni).</li> <li>Discount rate of 7% per annum for real, post-tax cash flows.</li> <li>A Statistical PERT sensitivity (SPERT) analysis was conducted</li> </ul>
		as part of the PFS. The NPV is most sensitive to revenue contributors, i.e. gold grade and gold price. This is expected as the study covered all the upfront costs in establishing the underground mine, but only considered the upper Measured and Indicated components of the Mineral Resource. It is expected that this sensitivity will greatly improve once the large Inferred Resource, open both along strike and at depth, has been drilled and confidence increased to be included in future Ore Reserves.
Social	<ul> <li>The status of agreements with key stakeholders and matters leading to social license to operate.</li> </ul>	Tabakoroni falls under the SOMIFI exploitation permit and is managed by SOMISY under Management and Toll Treatment agreements lodged with the Government of Mali.
		It is the intention to encourage economic development within the local community. During the operation of Tabakoroni open pit focus has been on improving farming and health care plus providing access to water; this will continue to remain a focus.
		The Syama Mine Community Consultative Committee, which includes representation from Tabakoroni and the villages adjacent to the Syama Satellites, was established in February 2001 with representatives from local villages, the Malian Government and SOMISY. Since April 2004 the Committee has met regularly as a communication forum and to address community issues and assist with community project proposals; it continues to meet on the first or second Tuesday of each month. Initial consultation as part of the underground updates to the ESIA indicated no major concerns with the underground operation.
Other	<ul> <li>To the extent relevant, the impact of the following on the project and/or on the estimation and classification of the Ore Reserves:</li> <li>Any identified material naturally occurring risks.</li> <li>The status of material legal agreements and marketing arrangements.</li> <li>The status of governmental agreements and approvals critical to the viability of the project, such as mineral tenement status, and government and statutory</li> </ul>	All current government agreements and approvals are in good standing and no anticipated changes are expected. Political instability is a potential risk in Mali, but the owner has many years operating experience in this environment through the current Syama and Tabakoroni operations. The current Malian government is supportive of mining operations and the current Syama and Tabakoroni operations are in good standing with the authorities. There are no current unresolved matters affecting this project.
	approvals. There must be reasonable grounds to expect that all necessary Government approvals will be received within the timeframes anticipated in the Pre- Feasibility or Feasibility study. Highlight and discuss the materiality of any unresolved matter that is dependent on a third party on which extraction of the reserve is contingent.	It is expected that the updated ESIA for moving the Tabakoroni operations underground will be approved by the Malian government and will not affect the viability of the project.



CRITERIA	JORC CODE EXPLANATION	COMMENTARY
Classification	<ul> <li>The basis for the classification of the Ore Reserves into varying confidence categories.</li> </ul>	Proved and Probable Ore Reserves were declared based on the Measured and Indicated Mineral Resources.
	Whether the result appropriately reflects the Competent Person's view of the deposit.	The Ore Reserve estimate appropriately reflects the Competent Person's view of the deposit.
	<ul> <li>The proportion of Probable Ore Reserves that have been derived from Measured Mineral Resources (if any).</li> </ul>	None of the Measured Mineral Resource was converted to Proven Ore Reserves. The Measured Resource component is located below the previous open pit and forms part of the crown pillar to be extracted at the end of the underground mine life. Due to the inherent risk of extracting the crown pillar at a much later stage in the mine's life, it is appropriate in the Competent Person's opinion to classify this material as Probable Ore Reserves and not Proved Ore Reserves.
Audits or reviews	The results of any audits or reviews of Ore Reserve estimates.	Major parts of the study were completed by external, independent contributors and were internally reviewed by each contributor prior to submission to Resolute. These inputs were then further reviewed by Resolute Corporate and Site operational teams prior to inclusion in the PFS. The combined PFS and Ore Reserves output was then internally reviewed, but no external review of the combine PFS and Ore Reserves has been conducted yet.
Discussion of relative accuracy/ confidence	<ul> <li>Where appropriate a statement of the relative accuracy and confidence level in the Ore Reserve estimate using an approach or procedure deemed appropriate by the Competent Person. For example, the application of statistical or geostatistical procedures to quantify the relative accuracy of the reserve within stated confidence limits, or, if such an approach is not deemed appropriate, a qualitative discussion of the factors which could affect the relative accuracy and confidence of the estimate.</li> <li>The statement should specify whether it relates to global</li> </ul>	The relative accuracy and confidence of the Ore Reserve estimate is inherent in the Ore Reserve Classification. The mine design and schedule were prepared to a PFS level of accuracy. Conservative mining modifying factors were used to account for potential variations in ground and geotechnical conditions. The open pit operations had a slight positive reconciliation, but this was not considered material to the underground project as the open pit operations only focused on oxide material, and the
	or local estimates, and, if local, state the relevant tonnages, which should be relevant to technical and economic evaluation. Documentation should include assumptions made and the procedures used.	underground will be focusing on fresh, sulphide ore. Reconciliation procedures will be implemented as part of the underground operation and will be considered in future Ore Reserve updates.
	<ul> <li>Accuracy and confidence discussions should extend to specific discussions of any applied Modifying Factors that may have a material impact on Ore Reserve viability, or for which there are remaining areas of uncertainty at the current study stage.</li> </ul>	Costs are at PFS level of confidence or better due to existing capital infrastructure and open pit operations at Tabakoroni, and existing underground operations and processing at Syama, which will be re-used for the Tabakoroni underground project.
	<ul> <li>It is recognized that this may not be possible or appropriate in all circumstances. These statements of relative accuracy and confidence of the estimate should be compared with production data, where available.</li> </ul>	Metallurgical results are in line with Syama parameters for similar ore, and are consistent between various test programmes, providing confidence in the assumptions used for the study.



### Syama Satellite Deposits – Cashew NE, Paysans, and Tellem

#### **CRITERIA** JORC CODE EXPLANATION COMMENTARY Sampling The samples were collected from reverse circulation (RC) and • Nature and quality of sampling (e.g. cut channels, random techniques diamond core drill holes. chips, or specific specialised industry standard measurement tools appropriate to the minerals under investigation, such as RC samples were collected on 1m intervals by riffle split (dry) or down hole gamma sondes, or handheld XRF instruments, etc.). by scoop (wet), to obtain These examples should not be taken as limiting the broad a 1-3kg sample which was sent to the laboratory for crushing, meaning of sampling splitting and pulverising to provide a 30g charge for analysis. Include reference to measures taken to ensure sample Diamond core was sampled at 1m intervals and cut in half, to representivity and the appropriate calibration of any provide a 2-4kg sample, measurement tools or systems used. which was sent to the laboratory for crushing, splitting and Aspects of the determination of mineralisation that are Material pulverising to provide a 30g charge for analysis. to the Public Report. Sampling and sample preparation protocols are industry • In cases where 'industry standard' work has been done this standard and are deemed appropriate by the Competent Person. would be relatively simple (e.g. 'reverse circulation drilling was used to obtain 1 m samples from which 3 kg was pulverised to produce a 30 g charge for fire assay'). In other cases more explanation may be required, such as where there is coarse gold that has inherent sampling problems. Unusual commodities or mineralisation types (e.g. submarine nodules) may warrant disclosure of detailed information. **Drilling techniques** • Drill type (e.g. core, reverse circulation, open-hole hammer, Drill types used include diamond core of PQ and HQ sizes and rotary air blast, auger, Bangka, sonic, etc.) and details (e.g. RC. core diameter, triple or standard tube, depth of diamond tails, Core is oriented at 3m down hole intervals using a Reflex Act II face-sampling bit or other type, whether core is oriented and if RD Orientation Tool. so, by what method, etc.). **Drill sample** Method of recording and assessing core and chip sample Drill core interval recoveries are measured from core block to recovery recoveries and results assessed. core block using a tape measure. Measures taken to maximise sample recovery and ensure Appropriate measures are taken to maximise sample recovery representative nature of the samples. and ensure the representative nature of the samples. Whether a relationship exists between sample recovery and No apparent relationship is noted between sample recovery and grade and whether sample bias may have occurred due to arade. preferential loss/gain of fine/coarse material

### Section 1 Sampling Techniques and Data

		с -
Logging	• Whether core and chip samples have been geologically and geotechnically logged to a level of detail to support appropriate Mineral Resource estimation, mining studies and metallurgical	Drill holes were geologically logged by geologists for colour, grainsize, lithology, minerals, alteration and weathering on geologically-domained intervals.
	<ul> <li>Whether logging is qualitative or quantitative in nature. Core (or costean, channel, etc.) photography.</li> </ul>	Geotechnical and structure orientation data was measured and logged for all diamond core intervals.
	The total length and percentage of the relevant intersections	Diamond core was photographed (wet and dry).
	logged.	Holes were logged in their entirety (100%) and this logging was considered reliable and appropriate.



CRITERIA	JORC CODE EXPLANATION	COMMENTARY
Sub-sampling techniques	<ul> <li>If core, whether cut or sawn and whether quarter, half or all core taken.</li> <li>If non-core, whether riffled, tube sampled, rotary split, etc. and whether sampled wet or dry.</li> <li>For all sample types, the nature, quality and appropriateness of the sample preparation technique.</li> <li>Quality control procedures adopted for all sub-sampling stages to maximise representivity of samples.</li> <li>Measures taken to ensure that the sampling is representative of the in-situ material collected, including for instance results for field duplicate/second-half sampling.</li> <li>Whether sample sizes are appropriate to the grain size of the material being sampled.</li> </ul>	Diamond core was sampled at 1m intervals and cut in half to obtain a 2-4kg sample.
and sample preparation		Reverse circulation samples were collected on 1m intervals by riffle split (dry) or by scoop (wet) to obtain a 1-3kg sample.
		Sample preparation for diamond core and RC samples includes oven drying, crushing to 10mm, splitting and pulverising to 85% passing -75µm. These preparation techniques are deemed to be appropriate to the material being sampled.
		Drill core coarse duplicates were split by the laboratory after crushing at a rate of 1:20 samples. Reverse circulation field duplicates were collected by the Company at a rate of 1:20 samples.
		Sampling, sample preparation and quality control protocols are of industry standard and all attempts were made to ensure an unbiased representative sample was collected. The methods applied in this process were deemed appropriate by the Competent Person.
Quality of assay data and laboratory tests	<ul> <li>The nature, quality and appropriateness of the assaying and laboratory procedures used and whether the technique is considered partial or total.</li> <li>For geophysical tools, spectrometers, handheld XRF instruments, etc., the parameters used in determining the analysis including instrument make and model, reading times, calibrations factors applied and their derivation, etc.</li> <li>Nature of quality control procedures adopted (e.g. standards, blanks, duplicates, external laboratory checks) and whether acceptable levels of accuracy (i.e. lack of bias) and precision have been established.</li> </ul>	All samples were dispatched to ALS Bamako for gold analysis by 30g fire assay fusion with AAS instrument finish (method code Au-AA25). Over-range results were re-analysed and reported by 30g fire assay fusion with gravimetric finish (method code Au- GRA21). The analytical method was appropriate for the style of mineralisation.
		No geophysical tools were used to determine elemental concentrations.
		Quality control (QC) procedures included the use of certified standards (1:40), non-certified sand blanks (1:40), diamond core coarse duplicates (1:20) and reverse circulation field duplicates (1:20).
		Laboratory quality control data, including laboratory standards, blanks, duplicates, repeats, grind size results and sample weights were also captured into the digital database.
		Analysis of the QC sample assay results indicates that an acceptable level of accuracy and precision has been achieved.
Verification of sampling and	<ul> <li>The verification of significant intersections by either independent or alternative company personnel.</li> </ul>	Verification of significant intersections have been completed by Company personnel and the Competent Person.
assaying	<ul> <li>The use of twinned holes.</li> <li>Decumpotation of primary data data entry procedures data</li> </ul>	No drill holes within the resource area were twinned.
	<ul> <li>verification, data storage (physical and electronic) protocols.</li> <li>Discuss any adjustment to assay data.</li> </ul>	Drill holes were logged into digital templates with lookup codes, validated and then compiled into a relational SQL 2012 database using DataShed data management software. The database has verification protocols which are used to validate the data entry. The drill hole database is backed up on a daily basis to the head office server.
		Assay result files were reported by the laboratory in PDF and CSV format and imported into the SQL database without adjustment or modification.



CRITERIA	JORC CODE EXPLANATION	COMMENTARY
Location of data points	<ul> <li>Accuracy and quality of surveys used to locate drill holes (collar and down-hole surveys), trenches, mine workings and other locations used in Mineral Resource estimation.</li> </ul>	Collar coordinates were picked up in UTM (WGS84) by staff surveyors using an RTK DGPS with an expected accuracy of $\pm 0.05m$ ; elevations were height above EGM96 geoid.
	<ul> <li>Specification of the grid system used.</li> <li>Quality and adequacy of topographic control.</li> </ul>	Down hole surveys were collected at intervals between 5m and 30m using either a Reflex EZ-Gyro north seeking instrument or a Reflex EZ-Trac magnetic instrument in single shot or multi shot mode. A time-dependent declination was applied to the magnetic readings to determine UTM azimuth.
		Coordinates and azimuths are reported in UTM WGS84 Zone 29 North.
		Coordinates were translated to local mine grid using 1 point and rotation.
		Local topographic control is via LIDAR surveys, satellite photography and drone UAV aerial survey.
Data spacing and distribution	<ul> <li>Data spacing for reporting of Exploration Results.</li> <li>Whether the data spacing and distribution is sufficient to establish the degree of geological and grade continuity</li> </ul>	Drill hole spacing was sufficient to demonstrate geological and grade continuity appropriate for a Mineral Resource and the classifications applied under the 2012 JORC Code.
	<ul><li>appropriate for the Mineral Resource and Ore Reserve estimation procedure(s) and classifications applied.</li><li>Whether sample compositing has been applied.</li></ul>	The appropriateness of the drill spacing was reviewed by the geological technical team, both on site and head office. This was also reviewed by the Competent Person.
		Samples were collected on 1m intervals; no sample compositing is applied during sampling.
Orientation of data in relation to	<ul> <li>Whether the orientation of sampling achieves unbiased sampling of possible structures and the extent to which this is known, considering the denosit time.</li> </ul>	Holes were drilled predominantly perpendicular to mineralised domains where possible.
structure	<ul> <li>If the relationship between the drilling orientation and the orientation of key mineralised structures is considered to have introduced a sampling bias, this should be assessed and reported if material.</li> </ul>	No orientation-based sampling bias has been identified in the data.
Sample security	• The measures taken to ensure sample security.	Samples were collected from the drill site and stored on site. All samples were individually bagged and labelled with unique sample identifiers, then securely dispatched to the laboratories. All aspects of sampling and dispatch process were supervised and tracked by SOMIFI personnel.
Audits or reviews	• The results of any audits or reviews of sampling techniques and data.	External audits of procedures indicate protocols are within industry standards.



### Section 2 Reporting of Exploration Results

CRITERIA	JORC CODE EXPLANATION	COMMENTARY
Mineral tenement and land tenure	<ul> <li>Type, reference name/number, location and ownership including agreements or material issues with third parties such as joint ventures, partnerships, overriding royalties</li> </ul>	Drilling at Syama was conducted within the Malian Exploitation Concession Permit PE 93/003 which covers an area of 200.6km2.
	<ul> <li>The security of the tenure held at the time of reporting along with any known impediments to obtaining a licence to opport in the security of the tenure held at the time of reporting along with any known impediments to obtaining a licence to opport in the security.</li> </ul>	Resolute Mining Limited has an 80% interest in the Syama project and the Exploitation Permit PE 93/003, on which it is based, through its Malian subsidiary, Sociêtê des Mines de Syama SA (SOMISY). The Malian Government holds a free carried 20% interest in SOMISY.
	to operate in the area.	The Permits are held in good standing. Malian mining law provides that all Mineral Resources are administered by DNGM (Direction Nationale de la Géologie et des Mines) or National Directorate of Geology and Mines under the Ministry of Mines, Energy and Hydrology.
Exploration done by other parties	<ul> <li>Acknowledgment and appraisal of exploration by other parties.</li> </ul>	The Syama deposit was originally discovered by a regional geochemical survey undertaken by the Direction National de Géologie et des Mines (DNGM) with assistance from the United Nations Development Program (UNDP) in 1985. There had also been a long history of artisanal activities on the hill where an outcropping chert horizon originally marked the present-day position of the open pit.
		BHP during 1987-1996 sampled pits, trenches, auger, RC and diamond drill holes across Syama prospects. Randgold Resources Ltd during 1996-2000 sampled pits, trenches, auger, RAB, RC and diamond drill holes across Syama prospects.
		Etruscan Resources Inc explored Tabakoroni during 2002- 2003 by auger, aircore, RC and diamond drill hole tails. The Tabakoroni area was previously explored Barrick Gold (1990) by auger, pits, trenches, RAB and diamond core drilling.
Geology	• Deposit type, geological setting and style of mineralisation.	The Syama Project is found on the northern margin of the Achaean-Proterozoic Leo Shield which forms the southern half of the West African Craton. The project area straddles the boundary between the Kadiana–Madinani terrane and the Kadiolo terrane. The Kadiana-Madinani terrane is dominated by greywackes and a narrow belt of interbedded basalt and argillite. The Kadiolo terrane comprises polymictic conglomerate and sandstone that were sourced from the Kadiana-Madinani terrane and deposited in a late- to syntectonic basin.
		Prospects are centred on the NNE striking, west dipping, Syama-Bananso Fault Zone and Birimian volcano- sedimentary units of the Syama Formation. The major commodity being sought is gold.



CRITERIA	JORC CODE EXPLANATION	COMMENTARY
Drill hole Information	<ul> <li>A summary of all information material to the understanding of the exploration results including a tabulation of the following information for all Material drill holes:         <ul> <li>easting and northing of the drill hole collar</li> <li>elevation or RL (Reduced Level – elevation above sea level in metres) of the drill hole collar</li> <li>dip and azimuth of the hole</li> <li>down hole length and interception depth</li> <li>Whole length.</li> </ul> </li> </ul>	All information, including easting, northing, elevation, dip, azimuth, coordinate system, drill hole length, intercept length and depth are measured and recorded in UTM Zone 29 WGS84. The Syama belt is mostly located on the Tengrela 1/200,000 topo sheet (Sheet NC 29-XVIII). Spectrum Survey & Mapping from Australia established survey control at Tabakoroni using AusPos online processing to obtain an accurate UTM Zone 29 (WGS84) and 'above geoid' RL for the origin of the survey control points.
	<ul> <li>If the exclusion of this information is justified on the basis that the information is not Material and this exclusion does not detract from the understanding of the report, the Competent Person should clearly explain why this is</li> </ul>	Accuracy of the survey measurements is considered to meet acceptable industry standards. Drill hole information has been tabulated for this release in the intercepts table of the accompanying text.
	the case.	<ul> <li>For completeness the following information about the drill holes is provided:</li> <li>Easting, Northing and RL of the drill hole collars are measured and recorded in UTM Zone 29 (WGS84).</li> <li>Dip is the inclination of the drill hole from horizontal. A drill hole drilled at -60° is 60° from the horizontal.</li> <li>Down hole length is the distance down the inclination of the hole and is measured as the distance from the horizontal to end of hole.</li> <li>Intercept depth is the distance from the start of the hole down the inclination of the hole to the depth of interest or assayed interval of interest.</li> </ul>
Data aggregation methods	<ul> <li>In reporting Exploration Results, weighting averaging techniques, maximum and/or minimum grade truncations (e.g. cutting of high grades) and cut-off grades are usually Material and should be stated.</li> <li>Where aggregate intercepts incorporate short lengths of high-grade results and longer lengths of low-grade results, the procedure used for such aggregation should be stated and some typical examples of such aggregations should be shown in detail.</li> <li>The assumptions used for any reporting of metal equivalent values should be clearly stated.</li> </ul>	<ul> <li>Exploration results are tabulated using the following parameters:</li> <li>Grid coordinates are WGS84 Zone 29 North.</li> <li>Cut-off grade for reporting of intercepts is &gt;=1g/t Au.</li> <li>No top cut of individual assays prior to length weighted compositing of the reported intercept has been applied.</li> <li>Maximum 3m consecutive internal dilution included within the intercept.</li> <li>Metal equivalent values are not used in reporting.</li> </ul>
Relationship between mineralisation widths and intercept lengths	<ul> <li>These relationships are particularly important in the reporting of Exploration Results.</li> <li>If the geometry of the mineralisation with respect to the drill hole angle is known, its nature should be reported.</li> <li>If it is not known and only the down hole lengths are reported, there should be a clear statement to this effect (e.g. 'down hole length, true width not known').</li> </ul>	<ul> <li>The Cashew NE, and Paysans mineralisation is shallowly dipping at about 30 degrees to the west (local grid).</li> <li>The majority of the Tellem mineralisation is narrow and sub vertical.</li> <li>The majority of the drill holes are planned at a general inclination of -60 degrees east and as close to perpendicular to the ore zone as possible.</li> <li>At the angle of the drill holes and the dip of the ore zones, the reported intercepts will be slightly more than true width.</li> </ul>
Diagrams	<ul> <li>Appropriate maps and sections (with scales) and tabulations of intercepts should be included for any significant discovery being reported These should include, but not be limited to a plan view of drill hole collar locations and appropriate sectional views.</li> </ul>	No exploration results have been reported in this release.



CRITERIA	JORC CODE EXPLANATION	COMMENTARY
Balanced reporting	• Where comprehensive reporting of all Exploration Results is not practicable, representative reporting of both low and high grades and/or widths should be practiced to avoid misleading reporting of Exploration Results.	Significant intercepts of new drill holes have not been reported in this release.
Other substantive exploration data	<ul> <li>Other exploration data, if meaningful and material, should be reported including (but not limited to): geological observations; geophysical survey results; geochemical survey results; bulk samples – size and method of treatment; metallurgical test results; bulk density, groundwater, geotechnical and rock characteristics; potential deleterious or contaminating substances.</li> </ul>	No geophysical and geochemical data or any additional exploration information has been reported in this release, as they are not deemed relevant to the release.
Further work	<ul> <li>The nature and scale of planned further work (e.g. tests for lateral extensions or depth extensions or large-scale step-out drilling).</li> <li>Diagrams clearly highlighting the areas of possible extensions, including the main geological interpretations and future drilling areas, provided this information is not commercially sensitive.</li> </ul>	Further drilling is planned.



### **Section 3 Estimation and Reporting of Mineral Resources**

CRITERIA	JORC CODE EXPLANATION	COMMENTARY
Database integrity	<ul> <li>Measures taken to ensure that data has not been corrupted by, for example, transcription or keying errors, between its initial collection and its use for Mineral Resource estimation purposes.</li> <li>Data validation procedures used.</li> </ul>	r Cashew NE, Paysans and Tellem Data has been compiled into a relational SQL database; the setup of this database precludes the loading of data which do not meet the required validation protocols. The data is managed using DataShed <sup>®</sup> drill hole management software using SQL database techniques. Validation checks are conducted using SQL and DataShed <sup>®</sup> relational database standards. Data has also been checked against original hard copies for 100% of the data, and where possible, loaded from original data sources.
		Resolute completed the following basic validation checks on the data supplied prior to resource estimation:
		<ul> <li>Drill holes with overlapping sample intervals.</li> <li>Sample intervals with no assay data or duplicate records.</li> <li>Assay grade ranges.</li> <li>Collar coordinate ranges.</li> <li>Valid hole orientation data.</li> </ul>
		There are no significant issues identified with the data.
Site visits	<ul> <li>Comment on any site visits undertaken by the Competent Person and the outcome of those visits.</li> <li>If no site visits have been undertaken indicate why this is the case</li> </ul>	<u>Cashew NE and Paysans</u> Mr Bruce Mowat, a full-time employee of Resolute Mining Ltd and a Member of the Australasian Institute of Mining and Metallurgy is the Competent Person who has visited this site multiple times.
		<u>Tellem</u> Mr Nicholas Johnson, as employee of MPR Geological Consultants Pty Ltd and a Member of the Geological Institute of Geoscientists is the Competent Person who has visited this site on numerous occasions, the most recent being May 2014 to review the grade control protocols ad review the Mineral Resource estimates at Syama.
		All aspects of drilling, sampling and mining are considered by the Competent Persons to be of a high industry standard.
Geological interpretation	<ul> <li>Confidence in (or conversely, the uncertainty of) the geological interpretation of the mineral deposit.</li> <li>Nature of the data used and of any assumptions made.</li> <li>The effect, if any, of alternative interpretations on Mineral Resource estimation</li> </ul>	<u>Cashew NE and Paysans</u> The digital database used for the interpretation included logged intervals for the key stratigraphic zones of Cashew NE, Paysans and Tellem. Detailed geological logs were available in hardcopy and digital and reviewed where necessary.
	<ul> <li>The use of geology in guiding and controlling Mineral Resource estimation.</li> <li>The factors affecting continuity both of grade and geology.</li> </ul>	Wireframes used to constrain the estimation are based on drill hole intercepts and geological boundaries. All wireframes at Cashew NE and Paysans have been constructed to a 0.3g/t Au cut-off grade for shape consistency. At Tellem they were constructed at nominal 0.1g/t Au mineralised envelope.
		There is a moderate level of confidence for the interpretation at Cashew NE, Paysans, and Tellem due to the relatively close- spaced drilling at surface. The mineralisation is generally quite consistent and drill intercepts clearly define the shape of the mineralised zones with limited options for large scale alternate interpretations.

At 31 December 2022



### CRITERIA JORC CODE EXPLANATION

Dimensions

#### The extent and variability of the Mineral Resource expressed as length (along strike or otherwise), plan width, and depth below surface to the upper and lower limits of the Mineral Resource.

#### COMMENTARY

### Cashew NE

The mineral resource at Cashew comprises three individual domains they all dip at about 30 degrees to the west (local grid) from surface and extend 200 metres down dip. The three domains extend for approximately 350 metres along strike and the gold mineralised zone width varies between 1.5 and 20 metres, with an average thickness of 7 metres.

#### Paysans

Three domains have been identified at Paysans. The three domains all dip at about 30 degrees to the west (local grid) and extend for 300 metres down dip. The mineralised zone width varies between 1.5 and 10 metres with an average thickness of 3 metres. They strike north-south (local grid) for approximately 1,700 metres. The deposit has been divided into three areas by two faults which run east-west (local grid).

### Tellem

There are three mineralised domains at Tellem. The three domains are narrow sub vertical zone of stockwork veins modelled to be between a few metres to 1.5 metres in thickness. The strike length is approximately 4.3 kilometres and covers a vertal extent of 270 metres.

At 31 December 2022



#### Estimation and modelling techniques

The nature and appropriateness of the estimation technique(s) applied and key assumptions, including treatment of extreme grade values, domaining, interpolation parameters and maximum distance of extrapolation from data points. If a computer assisted estimation method was chosen include a description of computer software and parameters used.

- The availability of check estimates, previous estimates and/or mine production records and whether the Mineral Resource estimate takes appropriate account of such data.
- The assumptions made regarding recovery of by- products.
- Estimation of deleterious elements or other non-grade variables of economic significance (e.g. sulphur for acid mine drainage characterization).
- In the case of block model interpolation, the block size in relation to the average sample spacing and the search employed.
- In the case of block model interpolation, the block size in relation to the average sample spacing and the search employed.
- Any assumptions behind modelling of selective mining units.
- Any assumptions about correlation between variables.
- Description of how the geological interpretation was used to control the resource estimates.
- Discussion of basis for using or not using grade cutting or capping.
- The process of validation, the checking process used, the comparison of model data to drill hole data, and use of reconciliation data if available.

#### Cashew NE

Estimation was completed in Datamine Studio RM using an Ordinary Kriged model to estimate the gold, sulphide sulphur and organic carbon grades. Grades were estimated into parent block of 5mE by 5mN by 2.5mRL with sub- celling down to 2.5mE by 2.5mN by 2.5mRL was employed for resolution of the mineralisation boundaries as defined by wireframes. The drill spacing at Cashew is a nominal 25 by 25 metres for the exploration holes for the majority of the deposits and 50 by 50 metres around the periphery. The main part of the deposit has been gc drilled out to 12.5 by 5 metres.

Drillhole sample data was flagged using domain codes generated from three-dimensional mineralisation domains. The samples were composited to 1 metre intervals.

Variogram orientations were largely controlled by the strike of the mineralisation and downhole variography. One set of variograms was generated for all the mineralisation due to similar orientation of each of the domains.

Kriging neighbourhood analysis was performed to optimise the block size, sample numbers and discretisation levels with the goal of minimising conditional bias in the gold grade estimates.

The mineralisation domains were treated as hard boundaries in the estimation process while oxidation surfaces were treated as soft boundaries.

Three search passes were used, with the first search pass set to the range of the variogram for each domain. A minimum of 8 and a maximum of 30 samples were used. The search stayed the same for the second pass but was increased by a factor of 2 for the third and final pass. The minimum number of samples was reduced to six for the second pass and for the third pass.

No deleterious elements were found in the ore.

No selective mining units have been assumed.

Top cuts were applied to reduce the variability of the data and to remove the outliers.

The estimated block model grades were visually validated against the input drillhole data and comparisons were carried out against the drillhole data and by northing and elevation slices. Global comparison between the input data and the block grades for each variable is considered acceptable (±10%)

### Paysans 1 4 1

Estimation was completed in Datamine Studio RM using an Ordinary Kriged model to estimate the gold grade. Grades were estimated into parent block of 10mE by 20mN (at Cashew, 25mN at Paysans) by 5mRL with sub- celling down to 2.5mE by 2.5mN by 2.5mRL was employed for resolution of the mineralisation boundaries as defined by wireframes. The drill spacing at Paysans is a nominal 25 by 25 metres for the exploration holes for the majority of the deposits and 50 by 50 metres around the periphery.

Drillhole sample data was flagged using domain codes generated from three-dimensional mineralisation domains. The samples were composited to one metre intervals.

Variogram orientations were largely controlled by the strike of the mineralisation and downhole variography. One set of variograms was generated for all the mineralisation due to similar orientation of each of the domains and sometimes lack of composites. Kriging neighbourhood analysis was performed to optimise the block size, sample numbers and discretisation levels with the goal of minimising conditional bias in the gold grade estimates.

At Cashew mineralisation domains were treated as hard boundaries in the estimation process while oxidation surfaces were treated as soft boundaries. At Paysans the mineralisation

At 31 December 2022



domains were treated as hard boundaries as well as the boundary between the transitional and fresh material within each domain.

The boundary between the oxide and transitional is treated as a soft boundary. Three search passes were used, with the first search pass set to the range of the variogram for each domain. A minimum of eight and a maximum of 30 samples were used. The search stayed the same for the second pass but was increased by a factor of three for the third and final pass. The minimum number of samples was reduced to six for the second pass and four for the third pass.

No deleterious elements were found in the ore.

No selective mining units have been assumed.

Top cuts were applied to reduce the variability of the data and to remove the outliers.

The estimated block model grades were visually validated against the input drillhole data and comparisons were carried out against the drillhole data and by northing and elevation slices. Global comparison between the input data and the block grades for each variable is considered acceptable (±10%).

#### Tellem

Multiple Indicator Kriging (MIK) with block support adjustment to estimate gold resources into blocks with dimensions of 10mE by 25mN by 5mRL. MIK of gold grades used indicator variography based on the two metre resource composite sample grades. Gold grade continuity was characterised by indicator variograms at 14 indicator thresholds spanning the global range of grades. A block support adjustment was used to estimate the recoverable gold resources at each deposit. The shape of the local block gold grade distribution has been assumed lognormal and an additional adjustment for the "Information Effect" has been applied to arrive at the final Mineral Resource estimates.

MIK was used as the preferred method for estimation of gold resources at Tellem as the approach has been demonstrated to work well in a large number of deposits of diverse geological styles. The gold mineralisation seen at the Tellem deposit is typical of that seen in most structurally controlled gold deposits where the MIK method has been found to be of most benefit.

Data viewing, compositing and wire-framing were performed using Micromine software. Exploratory data analysis, variogram calculation and modelling, and resource estimation have been performed using FSSI Consultant (Australia) Pty Ltd GS3M software. GS3M is designed specifically for estimation of recoverable resources using MIK methodology.

The sample data set containing all available assaying were composited to two metre intervals each located by their mid-point co-ordinates and assigned a length weighted average gold grade. The composite length of two metres was chosen because it is a multiple of the most common sampling interval (1.0 metre) and is also an appropriate choice for the kriging of gold into the model blocks where open pit mining is undertaken on 2.5 metre benches.

Block dimensions are 10mE by 25mN by 5mRL and was chosen as it approximates the average drill hole spacing in the horizontal direction, with the 5m elevation being a multiple of the mining bench height of 2.5m. The interpolation utilised a 3 pass octant search strategy with search radii generally in the order of category 1 searching 15m in the x, 25m in the y and 15m in the z direction, 16 minimum composites used, a maximum of four composites per octant and a minimum of four octants with data.

Category 2 uses a 50% search distance increase but otherwise the same parameters and category 3 uses the same search distance as category 2 but only requires eight minimum composites and only 2 octants require data. The search ellipse on each category is consistently orientated orthogonal to



CRITERIA	JORC	CODE EXPLANATION	COMMENTARY
			modelling grid.
			The 2m resource composites were initially coded by the mineralisation domain interpretation and the resultant primary domain coding further subdivided using the weathering surfaces to form sub-domains. Sample composites in each primary and sub-domain combination were reviewed for their univariate and indicator statistics and spatial continuity and were the basis of grade modelling.
			A combination of outlier high grade composites being ignored for each sub-domain for the generation of the indicator statistics, and selection of the median instead of mean for the highest indicator threshold were used to guard against a few higher grades within the population from having a disproportional influence on the gold estimation.
			A block support adjustment was used to estimate the recoverable gold resources. The shape of the local block gold grade distribution has been assumed lognormal and an additional adjustment for the "Information Effect" has been applied to arrive at the final Resource estimates. Selective mining unit assumed to be in the general range 4mE by 8mN by 2.5mRL.
			Visual validation of grade trends and gold distributions was carried out.
			These is no mine production, so no comparisons were carried out.
Moisture	•	Whether the tonnages are estimated on a dry basis or with natural moisture, and the method of determination of the moisture content.	<u>Cashew NE, Paysans, and Tellem</u> All tonnages have been estimated on a dry basis.
Cut-off parameters	•	The basis of the adopted cut-off grade(s) or quality parameters applied.	<u>Cashew NE, Paysans and Tellem</u> Mineral Resources for open pit extraction have been reported at a 1g/t Au grade cut-off.
Mining factors or assumptions	•	Assumptions made regarding possible mining methods, minimum mining dimensions and internal (or, if applicable, external) mining dilution. It is always necessary as part of the process of determining reasonable prospects for eventual economic extraction to consider potential mining methods, but the assumptions made regarding mining methods and parameters when estimating Mineral Resources may not always be rigorous. Where this is the case, this should be reported with an explanation of the basis of the mining assumptions made.	Cashew NE, Paysans, and Tellem The Resource models assume that a moderate level of mining selectivity is achieved in open pit mining. It has been assumed that high quality grade control will be applied to ore/waste delineation processes using RC drilling, or similar, at a nominal (and no greater) spacing of 5 metre by 12.5 metre and applying a pattern sufficient to ensure adequate coverage of the mineralisation zones. This is consistent with current mining practises at Syama.
Metallurgical factors or assumptions	•	The basis for assumptions or predictions regarding metallurgical amenability. It is always necessary as part of the process of determining reasonable prospects for eventual economic extraction to consider potential metallurgical methods, but the assumptions regarding metallurgical treatment processes and parameters made when reporting Mineral Resources may not always be rigorous. Where this is the case, this should be reported with an explanation of the basis of the metallurgical assumptions made.	<u>Cashew NE, Paysans, and Tellem</u> No metallurgical factors or assumptions have been made during the resource estimation process as these will be addressed during the conversion to Ore Reserves.



CRITERIA	JORC CODE EXPLANATION	COMMENTARY
Environmental factors or assumptions	• Assumptions made regarding possible waste and process residue disposal options. It is always necessary as part of the process of determining reasonable prospects for eventual economic extraction to consider the potential environmental impacts of the mining and processing operation. While at this stage the determination of potential environmental impacts, particularly for a green fields project, may not always be well advanced, the status of early consideration of these potential environmental impacts should be reported. Where these aspects have not been considered this should be reported with an explanation of the environmental assumptions made.	Cashew NE, Paysans, and Tellem It is a requirement of Decree No.03-594/P-RM of 31 December 2003 of Malian law that an Environmental and Social Impact Stud (Étude d'Impact Environmental et Social – EIES) must be undertaken to update the potential environmental and social impacts of the mine's redevelopment. The EIES for the Syama Gold Mine (including Tabakoroni) was approved in November 2007 and an Environment Permit (07- 0054/MEA – SG) was issued by the Ministry of Environment and Sanitation on 22 November 2007. The Ministry of Environment conducts timely reviews of the Syama Gold Mine to ensure that the Company maintains compliance with the EIES guidelines. At Syama, there are three key practices for disposal of wastes ar residues namely, stacking of waste rock from open pit mining; storage of tailings from mineral processes; and "tall-stack dispersion" of sulphur dioxide from the roasting of gold bearing concentrate. All waste disposal practices are in accordance with the guidelines in the EIES.
		The Environmental and Social Impact Study – "Société des Mines de Syama, Syama Gold Mine, Mali", dated 2007 indicated there was minimal potential for acid mine drainage from waste rock due to the elevated carbonate content which buffers a potential acid generation. Resolute maintains a plan for progressive rehabilitation of waste rock landforms as part of ongoing mine development and waste rock dumping.
		The landform of tailings impoundments does not have a net acid generating potential. The largest volume is flotation tailings where the sulphide minerals have already been removed from the host rock. Its mineralogy includes carbonates which further buffer any acid-formation potential from sulphides that may also be present.
		Cyanide levels in the leached-calcine tailings are typically less than 50ppm in the weak acid dissociable form. Groundwater awa from the tailings landform is intercepted by trenches and sump pumps.
		Sulphur dioxide is generated from the roasting of gold concentrat so that gold can be extracted and refined. Tall-Stack "dispersion" of the sulphur dioxide emission is monitored continuously. Prevailing weather and dissipation of the sulphur dioxide is modelled daily to predict the need to pause the roasting process meet the air quality criteria set out in the Environmental and Social Impact Study.
Bulk density	• Whether assumed or determined. If assumed, the basis for the assumptions. If determined, the method used, whether wet or dry, the frequency of the measurements, the nature, size and representativeness of the samples.	Paysans and Tellem No bulk density measurements have been taken at Paysans. An average SG was applied to the model by weathering type based on similar deposits at Syama:
	<ul> <li>The bulk density for bulk material must have been measured by methods that adequately account for void spaces (vugs, porosity, etc), moisture and differences between rock and alteration zones within the deposit.</li> </ul>	Oxide1.80 t/m³Transitional2.40 t/m³Fresh2.70 t/m³
	Discuss assumptions for bulk density estimates used in the evaluation process of the different materials.	<u>Cashew NE</u> One hole had density measurements at Cashew. The average density was adjusted to reflect the density of this hole. The densit was assigned based on weathering:
		Oxide2.00 t/m³Transitional2.56 t/m³Fresh2.75 t/m³



CRITERIA	JORC CODE EXPLANATION	COMMENTARY
Classification	<ul> <li>The basis for the classification of the Mineral Resources into varying confidence categories.</li> <li>Whether appropriate account has been taken of all relevant factors (i.e. relative confidence in tonnage/grade estimations, reliability of input data, confidence in continuity of geology and metal values, quality, quantity and distribution of the data).</li> <li>Whether the result appropriately reflects the Competent Person's view of the deposit.</li> </ul>	<ul> <li><u>Cashew NE and Paysans</u></li> <li>The Indicated Mineral Resource classification is based on moderate confidence in the geology and gold grade continuity with 25m x 25m spaced drillhole density or less.</li> <li>The Inferred Mineral Resource classification is applied to extensions of mineralised zones on the margins of the deposit where drill spacing is more than 50m x 50m and the extents of mineralisation at depth.</li> <li>The validation of the block model has confirmed satisfactory correlation of the input data to the estimated grades and reproduction of data trends.</li> <li><u>Tellem</u></li> <li>The Resource model uses a classification scheme producing a resource code based on the number and location of gold composites used to estimate proportions and gold grade of each block. This is based on the principle that larger numbers of composites, which are more evenly distributed within the search neighbourhood, will provide a more reliable estimate.</li> <li>The strategy adopted in the current study uses category 1 and 2 from the 3 pass octant search strategy as Indicated and category 3 as Inferred. This results in a geologically sensible classification whereby Category 3 blocks may occur on the peripheries of drilling but are still related to drilling data within reasonable distances.</li> <li>The Mineral Resource estimates appropriately reflects the view of the Competent Persons.</li> </ul>
Audits or reviews	<ul> <li>The results of any audits or reviews of Mineral</li> <li>Resource estimates.</li> </ul>	<u>Cashew NE, Paysans, and Tellem</u> There has been no external review of the Mineral Resource estimate.
Discussion of relative accuracy/ confidence	<ul> <li>Where appropriate a statement of the relative accuracy and confidence level in the Mineral Resource estimate using an approach or procedure deemed appropriate by the Competent Person. For example, the application of statistical or geostatistical procedures to quantify the relative accuracy of the resource within stated confidence limits, or, if such an approach is not deemed appropriate, a qualitative discussion of the factors that could affect the relative accuracy and confidence of the estimate.</li> <li>The statement should specify whether it relates to global or local estimates, and, if local, state the relevant tonnages, which should be relevant to technical and economic evaluation. Documentation should include assumptions made and the procedures used.</li> <li>These statements of relative accuracy and confidence of the estimate should be compared with production data, where available.</li> </ul>	<u>Cashew NE, Paysans, and Tellem</u> The Mineral Resource estimate has been classified based on the quality of the data collected, the density of data, the confidence of the geological models and mineralisation models, and the grade estimation quality. This has been applied to a relative confidence based on data density and zone confidence for resource classification. No relative statistical or geostatistical confidence or risk measure has been generated or applied. The relative accuracy of the Mineral Resource estimate is reflected in the reporting of Indicated and Inferred resource categories as defined by 2012 JORC Code guidelines. The estimate is considered to be relevant to an annual level of reporting of tonnage and grade. No production data available for comparison.



### Section 4 Estimation and Reporting of Ore Reserves

CRITERIA	JORC CODE EXPLANATION	COMMENTARY
Mineral Resource estimate for conversion to Ore Reserves	<ul> <li>Description of the Mineral Resource estimate used as a basis for the conversion to an Ore Reserve.</li> <li>Clear statement as to whether the Mineral Resources are reported additional to, or inclusive of, the Ore Reserve.</li> </ul>	Cashew South, Paysans, Folona and Tellem
		Resources and Reserves at Cashew South, Paysans, Folona and Tellem are reported above a 1 g/t cut-off. This was calculated as a marginal cut-off utilising open pit mining methods. Material below this cut-off is not included in the mineral resource.
		Ore Reserves are the material reported as a sub-set of the resource, that which can be extracted from the mine and processed with an economically acceptable outcome.
		Mineral Resources are reported inclusive of Ore Reserves.
Site visits	<ul> <li>Comment on any site visits undertaken by the Competent Person and the outcome of those visits.</li> <li>If no site visits have been undertaken indicate why this is the case.</li> </ul>	Cashew South. Paysans, Folona and Tellem Mr Kitwa Ndjibu a member of the Australasian Institute of Mining and Metallurgy and is a Competent Person who has visited the site the project is in the year 2022
Study status	<ul> <li>The type and level of study undertaken to enable Mineral Resources to be converted to Ore Reserves.</li> <li>The Code requires that a study to at least Pre-Feasibility Study level has been undertaken to convert Mineral Resources to Ore Reserves. Such studies will have been carried out and will have determined a mine plan that is technically achievable and economically viable, and that material Modifying Factors have been considered.</li> </ul>	Cashew South, Paysans, Folona and Tellem Feasibility studies were completed for mining of open satellite deposits in 2009 and mining of satellite pits has been occurring since 2014. Further optimisations have been undertaken in 2022 given the change in gold price and other inputs such as mining and processing costs. The above-mentioned optimisations resulted in new pit designs at all sites, Cashew South, Paysans, Folona and Tellem.
Cut-off parameters	• The basis of the cut-off grade(s) or quality parameters applied.	Cashew South, Paysans, Folona and Tellem Cashew South, Paysans, Folona and Tellem. use a cut-off of 0.8 g/t, based on the economic parameters described in subsequent sections.



CRITERIA	JORC CODE EXPLANATION	COMMENTARY
Mining factors or assumptions	<ul> <li>The method and assumptions used as reported in the Pre-Feasibility or Feasibility Study to convert the Mineral Resource to an Ore Reserve (i.e. either by application of appropriate factors by optimization or by preliminary or detailed design).</li> <li>The choice, nature and appropriateness of the selected mining method(s) and other mining parameters including associated design issues such as pre-strip, access, etc.</li> <li>The assumptions made regarding geotechnical parameters (e.g. pit slopes, stope sizes, etc.), grade control and pre-production drilling.</li> <li>The major assumptions made and Mineral Resource model used for pit and stope optimization (if appropriate).</li> <li>The mining dilution factors used.</li> <li>Any minimum mining widths used.</li> <li>The manner in which Inferred Mineral Resources are utilized in mining studies and the sensitivity of the outcome to their inclusion.</li> <li>The infrastructure requirements of the selected mining methods.</li> </ul>	<ul> <li><u>Cashew South, Paysans, Folona and Tellem</u></li> <li>The reported Ore Reserve estimates Cashew NE, Tellem and Paysans are based on pit optimisations conducted using the Lerchs-Grossman (LG) algorithm utilizing the Whittle to determine the optimal pit at specific input parameters and pit designs. Costs are based on existing contract mining and haulage rates and site costs which are understood with a high degree of accuracy.</li> <li>Mining is planned to be undertaken by conventional open pit methods of drill and blast, followed by load and haul.</li> <li>Detailed pit design work was completed based on pit optimisations using Whittle Four-X optimisation software. Only Measured and Indicated Resources were used in the pit optimisation.</li> <li>Overall slope angles are approximately 40° based on empirical experience from the mining other similar satellite pits</li> <li>Grade control consists of RC drilling, based on a 5.0mE x 12.5mN drill pattern</li> <li>A 5 % dilution factor and 10% mining loss factors have been applied to all satellite Cashew South, Paysans, Folona and Tellem.</li> <li>Minimum Mining Width used is 15m</li> </ul>
Metallurgical factors or assumptions	<ul> <li>The metallurgical process proposed and the appropriateness of that process to the style of mineralization.</li> <li>Whether the metallurgical process is well-tested technology or novel in nature.</li> <li>The nature, amount and representativeness of metallurgical test work undertaken, the nature of the metallurgical domaining applied and the corresponding metallurgical recovery factors applied.</li> <li>Any assumptions or allowances made for deleterious elements.</li> <li>The existence of any bulk sample or pilot scale test work and the degree to which such samples are considered representative of the ore body as a whole.</li> <li>For minerals that are defined by a specification, has the ore reserve estimation been based on the appropriate mineralogy to meet the specifications?</li> </ul>	Cashew South, Paysans, Folona and Tellem Processing is by conventional primary crushing followed by single stage SAG milling. Gold recovery is by means of a gravity recovery circuit and carbon in leach process. Processing recoveries used are 90%, 80% and 65% for Oxide, Transitional and Fresh material respectively. Mine is operational with good reconciliation between predicted recoveries and actuals. Allowances are made in the recovery estimates for Transitional and Fresh ore as the Au recovery is impacted by some of the gold being hosted in refractory sulphide and preg-robbing carbon
Environmental	The status of studies of potential environmental impacts of the mining and processing operation. Details of waste rock characterization and the consideration of potential sites, status of design options considered and, where applicable, the status of approvals for process residue storage and waste dumps should be reported.	Cashew South, Paysans, Folona and Tellem An active waste rock characterisation program has been put in place for Tabakoroni and will extend to this satellite open pit deposits Ore from these pits will be processed at Syama and tailings storage will be impounded in existing footprint area approved in the Environmental & Social Impact Study. Progressive raising of the tailings occurs regularly with the 9th lift completed in 2019. Routine progress on the monitoring is reported to government and at stakeholder meetings in concert with routine inspections by government representatives.



CRITERIA	JORC CODE EXPLANATION	COMMENTARY
Infrastructure	<ul> <li>The existence of appropriate infrastructure: availability of land for plant development, power, water, transportation (particularly for bulk commodities), labour, accommodation; or the ease with which the infrastructure can be provided, or accessed.</li> </ul>	Cashew South, Paysans, Folona and Tellem These pits will be supported by existing infrastructure at Syama as they are close to the main facility. Folona ore is hauled to the Syama infrastructure.
Costs	<ul> <li>The derivation of, or assumptions made, regarding projected capital costs in the study.</li> <li>The methodology used to estimate operating costs.</li> <li>Allowances made for the content of deleterious elements.</li> <li>The derivation of assumptions made of metal or commodity price(s), for the principal minerals and coproducts.</li> <li>The source of exchange rates used in the study.</li> <li>Derivation of transportation charges.</li> <li>The basis for forecasting or source of treatment and refining charges, penalties for failure to meet specification, etc.</li> <li>The allowances made for royalties payable, both</li> <li>Government and private.</li> </ul>	<ul> <li><u>Cashew South, Paysans, Folona and Tellem</u></li> <li>The Cashew South, Paysan, Folona and Tellem pits are located within approximately 10km of Syama. Ore is trucked to Syama where it is processed at Syama's oxide circuit. General and administration costs are shared between the oxide plant and the sulphide plant which treats the Syama UG orebody. As part of ongoing operations, capital and operating budgets are prepared from first principles and considering existing contractual agreements.</li> <li>The oxide plant produces gold doré (without problematic deleterious elements) that is subsequently refined offsite. Refining costs are not material.</li> <li>Exchange rates used for planning purposes are from consensus forecasts provided by external corporate advisers.</li> <li>Ad valorem Government royalties of 6% are payable on gold production</li> </ul>
Revenue factors	<ul> <li>The derivation of, or assumptions made regarding revenue factors including head grade, metal or commodity price(s) exchange rates, transportation and treatment charges, penalties, net smelter returns, etc.</li> <li>The derivation of assumptions made of metal or commodity price(s), for the principal metals, minerals and co-products.</li> </ul>	Cashew South, Paysans, Folona and Tellem A gold price of US\$1,500/oz formed the basis of the Ore Reserves.
Market assessment	<ul> <li>The demand, supply and stock situation for the particular commodity, consumption trends and factors likely to affect supply and demand into the future.</li> <li>A customer and competitor analysis along with the identification of likely market windows for the product.</li> <li>Price and volume forecasts and the basis for these forecasts.</li> <li>For industrial minerals the customer specification, testing and acceptance requirements prior to a supply contract.</li> </ul>	Cashew South, Paysans, Folona and Tellem The market for gold is robust with prevailing gold price being around US\$1,850/oz. Supply and demand are not considered material to the Ore Reserve calculations.
Economic	<ul> <li>The inputs to the economic analysis to produce the net present value (NPV) in the study, the source and confidence of these economic inputs including estimated inflation, discount rate, etc.</li> <li>NPV ranges and sensitivity to variations in the significant assumptions and inputs.</li> </ul>	Cashew South, Paysans, Folona and Tellem The financial evaluation undertaken as part of the evaluation of these open pits indicated a positive net present value (NPV) at 7% discount rate and operating results to date have exceeded production and NPV forecasts.



CRITERIA	JORC CODE EXPLANATION	COMMENTARY
Social	• The status of agreements with key stakeholders and	Cashew South, Paysans, Folona and Tellem
	matters leading to social license to operate.	The Southern Satellite Pits fall within the Syama exploitation permit and will be managed and operated by SOMISY SA.
		Development of the Southern Satellite pits has required updating of the SOMISY ESIA which has been lodged with the Government of Mali since December 2019. The ESIA process has required consultation with local community and local government leadership plus other relevant stakeholders. Engagement will continue up to and during operations including the payment of compensation to farmers whose fields are disturbed as per Malian legal requirements.
		It is anticipated that Malian nationals will fill most operating and management positions related to the Southern Satellite open pits.
		It is the intention to encourage economic development within the local community
		The Syama Mine Community Consultative Committee, which includes representation from Tabakoroni and the villages adjacent to the Southern Satellites, was established in February 2001 with representatives from local villages, the Malian Government and SOMISY. Since April 2004 the Committee has met regularly as a communication forum and to address community issues and assist with community project proposals; it continues to meet on the first or second Tuesday of each month.
Other	<ul> <li>To the extent relevant, the impact of the following on the project and/or on the estimation and classification of the Ore Reserves:</li> <li>Any identified material naturally occurring risks.</li> <li>The status of material legal agreements and marketing arrangements.</li> <li>The status of governmental agreements and approvals critical to the viability of the project, such as mineral tenement status, and government and statutory approvals. There must be reasonable grounds to expect that all necessary Government approvals will be received within the timeframes anticipated in the Pre-Feasibility or Feasibility study. Highlight and discuss the materiality of any unresolved matter that is dependent on a third party on which extraction of the reserve is contingent.</li> </ul>	Cashew South, Paysans and Tellem All current government agreements and approvals are in good standing and no anticipated changes are expected.
Classification	<ul> <li>The basis for the classification of the Ore Reserves into varying confidence categories.</li> <li>Whether the result appropriately reflects the Competent Person's view of the deposit.</li> <li>The proportion of Probable Ore Reserves that have been derived from Measured Mineral Resources (if any).</li> </ul>	Cashew South, Paysans, Folona and Tellem Probable Ore Reserves were declared based on the Indicated Mineral Resources and Measured Resources considering the uncertainty of the Modifying Factors such as geotechnical inputs. Nevertheless, since Folona is an operating mine, the uncertainties are reduced resulting in Measures Resources conversion into Proved Reserve.
		The Ore Reserve estimate appropriately reflects the Competent Person's view of the deposit
Audits or reviews	• The results of any audits or reviews of Ore Reserve estimates.	Cashew, Paysans, Folona and Tellem No external audits of resources/reserves were undertaken.



CRITERIA	JORC CODE EXPLANATION	COMMENTARY
Discussion of relative accuracy/ confidence	<ul> <li>Where appropriate a statement of the relative accuracy and confidence level in the Ore Reserve estimate using an approach or procedure deemed appropriate by the Competent Person. For example, the application of statistical or geostatistical procedures to quantify the relative accuracy of the reserve within stated confidence limits, or, if such an approach is not deemed appropriate, a qualitative discussion of the factors which could affect the relative accuracy and confidence of the estimate.</li> <li>The statement should specify whether it relates to global or local estimates, and, if local, state the relevant tonnages, which should be relevant to technical and economic evaluation. Documentation should include assumptions made and the procedures used.</li> <li>Accuracy and confidence discussions should extend to specific discussions of any applied Modifying Factors tha may have a material impact on Ore Reserve viability, or for which there are remaining areas of uncertainty at the current study stage.</li> <li>It is recognized that this may not be possible or appropriate in all circumstances. These statements of relative accuracy and confidence of the estimate should be compared with production data, where available.</li> </ul>	Cashew South, Paysans, Folona and Tellem The relative accuracy and confidence of the Ore Reserve estimate is inherent in the Ore Reserve Classification. All the parameters assumed and adopted along with financial modelling and analysis have been subject to internal peer review.



### Tabakoroni Satellite Deposits – Porphyry Zone (Splay)

### Section 1 Sampling Techniques and Data

CRITERIA	JORC CODE EXPLANATION	COMMENTARY
Sampling techniques	<ul> <li>Nature and quality of sampling (e.g. cut channels, random chips, or specific specialised industry standard measurement tools appropriate to the minerals under investigation, such as down hole gamma sondes, or handheld XRF instruments, etc.). These examples should not be taken as limiting the broad meaning of sampling.</li> </ul>	The samples were collected from reverse circulation (RC) and diamond core drill holes.
		RC samples were collected on 1m intervals by riffle split (dry) or by scoop (wet), to obtain a 1-3kg sample which was sent to the laboratory for crushing, splitting and pulverising to provide a 30g charge for analysis
	<ul> <li>Include reference to measures taken to ensure sample representivity and the appropriate calibration of any measurement tools or systems used.</li> </ul>	Diamond core was sampled at 1m intervals and cut in half, to provide a 2-4kg sample, which was sent to the laboratory for
	<ul> <li>Aspects of the determination of mineralisation that are Material to the Public Report.</li> </ul>	crusning, splitting and pulverising to provide a 30g charge for analysis.
	<ul> <li>In cases where 'industry standard' work has been done this would be relatively simple (e.g. 'reverse circulation drilling was used to obtain 1 m samples from which 3 kg was pulverised to produce a 30 g charge for fire assay'). In other cases more explanation may be required, such as where there is coarse gold that has inherent sampling problems. Unusual commodities or mineralisation types (e.g. submarine nodules) may warrant disclosure of detailed information.</li> </ul>	Sampling and sample preparation protocols are industry standard and are deemed appropriate by the Competent Person.
Drilling techniques	<ul> <li>Drill type (e.g. core, reverse circulation, open-hole hammer, rotary air blast, auger, Bangka, sonic, etc.) and details (e.g. core diameter, triple or standard tube, depth of diamond tails, face-sampling bit or other type, whether core is oriented and if so, by what method, etc.).</li> </ul>	Drill types used include diamond core of PQ and HQ sizes and RC. Core is oriented at 3m down hole intervals using a Reflex Act II RD Orientation Tool.
Drill sample recovery	<ul> <li>Method of recording and assessing core and chip sample recoveries and results assessed.</li> <li>Measures taken to maximise sample recovery and ensure representative nature of the samples.</li> <li>Whether a relationship exists between sample recovery and grade and whether sample bias may have occurred due to preferential loss/gain of fine/coarse material.</li> </ul>	Drill core interval recoveries are measured from core block to core block using a tape measure.
		Appropriate measures are taken to maximise sample recovery and ensure the representative nature of the samples.
		No apparent relationship is noted between sample recovery and grade.
Logging	<ul> <li>Whether core and chip samples have been geologically and geotechnically logged to a level of detail to support appropriate Mineral Resource estimation, mining studies and metallurgical studies.</li> <li>Whether logging is qualitative or quantitative in nature. Core (or costean, channel, etc.) photography.</li> <li>The total length and percentage of the relevant</li> </ul>	Drill holes were geologically logged by geologists for colour, grainsize, lithology, minerals, alteration and weathering on geologically-domained intervals.
		Geotechnical and structure orientation data was measured and logged for all diamond core intervals.
		Diamond core was photographed (wet and dry).
	intersections logged.	Holes were logged in their entirety (100%) and this logging was considered reliable and appropriate.



CRITERIA	JORC CODE EXPLANATION	COMMENTARY
Sub-sampling techniques and sample preparation	<ul> <li>If core, whether cut or sawn and whether quarter, half or all core taken.</li> <li>If non-core, whether riffled, tube sampled, rotary split, etc. and whether sampled wet or dry.</li> <li>For all sample types, the nature, quality and appropriateness of the sample preparation technique.</li> <li>Quality control procedures adopted for all sub-sampling stages to maximise representivity of samples.</li> <li>Measures taken to ensure that the sampling is representative of the in-situ material collected, including for instance results for field duplicate/second-half sampling.</li> <li>Whether sample sizes are appropriate to the grain size of the material being sampled.</li> </ul>	Diamond core was sampled at 1m intervals and cut in half to obtain a 2-4kg sample.
		Reverse circulation samples were collected on 1m intervals by riffle split (dry) or by scoop (wet) to obtain a 1-3kg sample.
		Sample preparation for diamond core and RC samples includes oven drying, crushing to 10mm, splitting and pulverising to 85% passing -75µm. These preparation techniques are deemed to be appropriate to the material being sampled.
		Drill core coarse duplicates were split by the laboratory after crushing at a rate of 1:20 samples. Reverse circulation field duplicates were collected by the Company at a rate of 1:20 samples.
		Sampling, sample preparation and quality control protocols are of industry standard and all attempts were made to ensure an unbiased representative sample was collected. The methods applied in this process were deemed appropriate by the Competent Person.
Quality of assay data and laboratory tests	<ul> <li>The nature, quality and appropriateness of the assaying and laboratory procedures used and whether the technique is considered partial or total.</li> <li>For geophysical tools, spectrometers, handheld XRF instruments, etc., the parameters used in determining the analysis including instrument make and model, reading times, calibrations factors applied and their derivation, etc.</li> <li>Nature of quality control procedures adopted (e.g. standards, blanks, duplicates, external laboratory checks) and whether acceptable levels of accuracy (i.e. lack of bias) and precision have been established.</li> </ul>	All samples were dispatched to ALS Bamako for gold analysis by 30g fire assay fusion with AAS instrument finish (method code Au-AA25). Over-range results were re-analysed and reported by 30g fire assay fusion with gravimetric finish (method code Au- GRA21). The analytical method was appropriate for the style of mineralisation.
		No geophysical tools were used to determine elemental concentrations.
		Quality control (QC) procedures included the use of certified standards (1:40), non-certified sand blanks (1:40), diamond core coarse duplicates (1:20) and reverse circulation field duplicates (1:20).
		Laboratory quality control data, including laboratory standards, blanks, duplicates, repeats, grind size results and sample weights were also captured into the digital database.
		Analysis of the QC sample assay results indicates that an acceptable level of accuracy and precision has been achieved.
Verification of sampling and assaying	<ul> <li>The verification of significant intersections by either independent or alternative company personnel.</li> <li>The use of twinned holes.</li> <li>Documentation of primary data, data entry procedures, data verification, data storage (physical and electronic) protocols.</li> <li>Discuss any adjustment to assay data.</li> </ul>	Verification of significant intersections have been completed by Company personnel and the Competent Person.
		No drill holes within the resource area were twinned.
		Drill holes were logged into digital templates with lookup codes, validated and then compiled into a relational SQL 2012 database using DataShed data management software. The database has verification protocols which are used to validate the data entry. The drill hole database is backed up on a daily basis to the head office server.
		Assay result files were reported by the laboratory in PDF and CSV format and imported into the SQL database without adjustment or modification.



CRITERIA	JORC CODE EXPLANATION	COMMENTARY
Location of data points	<ul> <li>Accuracy and quality of surveys used to locate drill holes (collar and down-hole surveys), trenches, mine workings and other locations used in Mineral Resource estimation.</li> <li>Specification of the grid system used.</li> <li>Quality and adequacy of topographic control.</li> </ul>	Collar coordinates were picked up in UTM (WGS84) by staff surveyors using an RTK DGPS with an expected accuracy of ±0.05m; elevations were height above EGM96 geoid. Down hole surveys were collected at intervals between 5m and 30m using either a Reflex EZ-Gyro north seeking instrument or a Reflex EZ-Trac magnetic instrument in single shot or multi shot mode. A time-dependent declination was applied to the magnetic readings to determine UTM azimuth. Coordinates and azimuths are reported in UTM WGS84 Zone 29 North. Coordinates were translated to local mine grid using 1 point and rotation. Local topographic control is via LIDAR surveys, satellite photography and drone UAV aerial survey.
Data spacing and distribution	<ul> <li>Data spacing for reporting of Exploration Results.</li> <li>Whether the data spacing and distribution is sufficient to establish the degree of geological and grade continuity appropriate for the Mineral Resource and Ore Reserve estimation procedure(s) and classifications applied.</li> <li>Whether sample compositing has been applied.</li> </ul>	Drill hole spacing was sufficient to demonstrate geological and grade continuity appropriate for a Mineral Resource and the classifications applied under the 2012 JORC Code. The appropriateness of the drill spacing was reviewed by the geological technical team, both on site and head office. This was also reviewed by the Competent Person. Samples were collected on 1m intervals; no sample compositing is applied during sampling.
Orientation of data in relation to geological structure	<ul> <li>Whether the orientation of sampling achieves unbiased sampling of possible structures and the extent to which this is known, considering the deposit type.</li> <li>If the relationship between the drilling orientation and the orientation of key mineralised structures is considered to have introduced a sampling bias, this should be assessed and reported if material.</li> </ul>	Holes were drilled predominantly perpendicular to mineralised domains where possible. No orientation-based sampling bias has been identified in the data.
Sample security	• The measures taken to ensure sample security.	Samples were collected from the drill site and stored on site. All samples were individually bagged and labelled with unique sample identifiers, then securely dispatched to the laboratories. All aspects of sampling and dispatch process were supervised and tracked by SOMIFI personnel.
Audits or reviews	The results of any audits or reviews of sampling techniques and data.	External audits of procedures indicate protocols are within industry standards.


#### **Section 2 Reporting of Exploration Results**

CRITERIA	JORC CODE EXPLANATION	COMMENTARY
Mineral tenement and land tenure status	<ul> <li>Type, reference name/number, location and ownership including agreements or material issues with third parties such as joint ventures, partnerships, overriding royalties, native title interests, historical sites, wilderness or national park and environmental settings.</li> </ul>	Porphyry Zone drilling was completed within the Finkolo-Tabakoroni Exploitation Licence PE 13/19. Resolute Mining Limited has an 90% interest in Exploitation Permit PE 13/19, through its Malian subsidiary, Sociêtê des Mines de Finkolo SA (SOMIFI). The Malian Government holds a free carried 10% interest in SOMIFI.
	<ul> <li>The security of the tenure held at the time of reporting along with any known impediments to obtaining a licence to operate in the area.</li> </ul>	The Permits are held in good standing. Malian mining law provides that all Mineral Resources are administered by DNGM (Direction Nationale de la Géologie et des Mines) or National Directorate of Geology and Mines under the Ministry of Mines, Energy and Hydrology.
Exploration done by other parties	<ul> <li>Acknowledgment and appraisal of exploration by other parties.</li> </ul>	Etruscan Resources Inc explored Tabakoroni during 2002-2003 by auger, aircore, RC and diamond drill hole tails. The Tabakoroni area was previously explored by BHP (1988-1990) and Barrick Gold (1990) by auger, pits, trenches, RAB and diamond core drilling.
Geology	• Deposit type, geological setting and style of mineralisation.	The Tabakoroni Porphyry Zone is located on a NNE trending splay of the NNW oriented Main Tabakoroni Shear Zone.
		Host rocks are comprised of interbedded greywacke and shale with small intrusions of quartz feldspar phyric dacite porphyry. Ductile shearing affects all units and is particularly focussed within the shale units.
		Mineralisation occurs as quartz-pyrite veins and sulphidic shears within shale units. Visible gold is commonly seen in vein quartz.
		The gold mineralisation at the 'Porphyry Zone" is somewhat erratic with more coherent zones striking NNE and dipping shallowly and steeply west.
Drill hole Information	<ul> <li>A summary of all information material to the understanding of the exploration results including a tabulation of the following information for all Material drill holes: <ul> <li>easting and northing of the drill hole collar</li> <li>elevation or RL (Reduced Level – elevation above sea level in metres) of the drill hole collar</li> <li>dip and azimuth of the hole</li> <li>down hole length and interception depth</li> <li>Whole length.</li> </ul> </li> <li>If the exclusion of this information is justified on the basis that the information is not Material and this exclusion does not detract from the understanding of the report, the Competent Person should clearly explain why this is the case.</li> </ul>	<ul> <li>No exploration results have been reported in this release.</li> <li>All information, including easting, northing, elevation, dip, azimuth, coordinate system, drill hole length, intercept length and depth are measured and recorded in UTM Zone 29 WGS84.</li> <li>The Syama belt is mostly located on the Tengrela 1/200,000 topo sheet (Sheet NC 29-XVIII).</li> <li>The Tabakoroni local grid has been tied to the UTM Zone 29 WGS84 co-ordinate system.</li> <li>Spectrum Survey &amp; Mapping from Australia established survey control at Tabakoroni using AusPos online processing to obtain an accurate UTM Zone 29 (WGS84) and 'above geoid' RL for the origin of the survey control points.</li> <li>Accuracy of the survey measurements is considered to meet acceptable industry standards.</li> <li>Drill hole information has been tabulated for this release in the intercepts table of the accompanying text.</li> <li>For completeness the following information about the drill holes is provided:</li> <li>Easting, Northing and RL of the drill hole collars are measured and recorded in UTM Zone 29 (WGS84).</li> <li>Dip is the inclination of the drill hole from horizontal. A drill hole drilled at -60° is 60° from the horizontal.</li> </ul>



CRITERIA	JORC CODE EXPLANATION	COMMENTARY
		<ul> <li>Intercept depth is the distance from the start of the hole down the inclination of the hole to the depth of interest or assayed interval of interest.</li> </ul>
Data aggregation methods	<ul> <li>In reporting Exploration Results, weighting averaging techniques, maximum and/or minimum grade truncations (e.g. cutting of high grades) and cut-off grades are usually Material and should be stated.</li> <li>Where aggregate intercepts incorporate short lengths of high grade results and longer lengths of low grade results, the procedure used for such aggregation should be stated and some typical examples of such aggregations should be shown in detail.</li> <li>The assumptions used for any reporting of metal equivalent values should be clearly stated.</li> </ul>	<ul> <li>Exploration results are tabulated using the following parameters:</li> <li>Grid coordinates are WGS84 Zone 29 North.</li> <li>Cut-off grade for reporting of intercepts is &gt;=1g/t Au.</li> <li>No top cut of individual assays prior to length weighted compositing of the reported intercept has been applied.</li> <li>Maximum 3m consecutive internal dilution included within the intercept.</li> </ul>
Relationship between mineralisation widths and intercept lengths	<ul> <li>These relationships are particularly important in the reporting of Exploration Results.</li> <li>If the geometry of the mineralisation with respect to the drill hole angle is known, its nature should be reported.</li> <li>If it is not known and only the down hole lengths are reported there should be a clear statement to this effect (e.g. 'down hole length, true width not known').</li> </ul>	<ul><li>The majority of the drill holes are planned at a general inclination of -60 degrees east and as close to perpendicular to the ore zone as possible.</li><li>At the angle of the drill holes and the dip of the ore zones, the reported intercepts will be slightly more than true width.</li></ul>
Diagrams	<ul> <li>Appropriate maps and sections (with scales) and tabulations of intercepts should be included for any significant discovery being reported These should include, but not be limited to a plan view of drill hole collar locations and appropriate sectional views.</li> </ul>	No exploration results have been reported in this release.
Balanced reporting	<ul> <li>Where comprehensive reporting of all Exploration Results is not practicable, representative reporting of both low and high grades and/or widths should be practiced to avoid misleading reporting of Exploration Results.</li> </ul>	Significant intercepts of new drill holes have not been reported in this release.
Other substantive exploration data	<ul> <li>Other exploration data, if meaningful and material, should be reported including (but not limited to): geological observations; geophysical survey results; geochemical survey results; bulk samples – size and method of treatment; metallurgical test results; bulk density, groundwater, geotechnical and rock characteristics; potential deleterious of contaminating substances.</li> </ul>	No geophysical and geochemical data or any additional exploration information has been reported in this release, y as they are not deemed relevant to the release.
Further work	<ul> <li>The nature and scale of planned further work (e.g. tests for lateral extensions or depth extensions or large-scale step-out drilling).</li> <li>Diagrams clearly highlighting the areas of possible extensions, including the main geological interpretations and future drilling areas, provided this information is not commercially sensitive.</li> </ul>	Further drilling is planned.



### Section 3 Estimation and Reporting of Mineral Resources

CRITERIA	JORC CODE EXPLANATION	COMMENTARY
Database integrity	<ul> <li>Measures taken to ensure that data has not been corrupted by, for example, transcription or keying errors, between its initial collection and its use for Mineral Resource estimation purposes.</li> <li>Data validation procedures used.</li> </ul>	Data has been compiled into a relational SQL database; the setup of this database precludes the loading of data which do not meet the required validation protocols. The data is managed using DataShed <sup>®</sup> drill hole management software using SQL database techniques. Validation checks are conducted using SQL and DataShed <sup>®</sup> relational database standards. Data has also been checked against original hard copies for 100% of the data, and where possible, loaded from original data sources.
		<ul> <li>Resolute completed the following basic validation checks on the data supplied prior to resource estimation:</li> <li>Drill holes with overlapping sample intervals.</li> <li>Sample intervals with no assay data or duplicate records.</li> <li>Assay grade ranges.</li> <li>Collar coordinate ranges.</li> <li>Valid hole orientation data.</li> </ul> There are no significant issues identified with the data.
Site visits	<ul> <li>Comment on any site visits undertaken by the Competent Person and the outcome of those visits.</li> <li>If no site visits have been undertaken indicate why this is the case.</li> </ul>	Mr Bruce Mowat, a fulltime employee of Resolute Mining Limited and a Member of the Australasian Institute of Mining and Metallurgy is the Competent Person who has visited this site on multiple occasions. All aspects of drilling, sampling and mining are considered by the Competent Persons to be of a high industry standard.
Geological interpretation	<ul> <li>Confidence in (or conversely, the uncertainty of) the geological interpretation of the mineral deposit.</li> <li>Nature of the data used and of any assumptions made.</li> <li>The effect, if any, of alternative interpretations on Mineral Resource estimation.</li> <li>The use of geology in guiding and controlling Mineral Resource estimation.</li> <li>The factors affecting continuity both of grade and geology.</li> </ul>	The digital database used for the interpretation included logged intervals for the key stratigraphic zones of the Porphyry Zone. Detailed geological logs were available in hardcopy and digital and reviewed where necessary. A wireframe was used to constrain the estimation is based on drill hole intercepts and geological boundaries. The wireframe has been constructed to a 0.5g/t Au cut-off grade for shape consistency. Only one wireframe was constructed in the closely spaced drilled area and the remaining mineralisation was in the wider spaced drilling area and an alternate estimation method was used. The confidence in the geological interpretation is a moderate level and is based on good quality drilling and ongoing drill hole logging. The main zone has been gc drilled and therefore is considered robust, the area outside the gc drilling has a lower confidence give the sparse drilling. There could be alternative interpretations in this area which is reflected in the classification. The logging in the geological database of lithology and weathering were considered during the mineralisation domain interpretations, and where available.
Dimensions	<ul> <li>The extent and variability of the Mineral Resource expressed as length (along strike or otherwise), plan width, and depth below surface to the upper and lower limits of the Mineral Resource.</li> </ul>	The Porphyry Zone Mineral Resource area extends over a strike length of 700 metres (from 1,164,600 mN to 1,165,300 mN) and includes the 175 metre vertical interval from 345mRL to 170mRL. The overall plan width of the mineralised lodes varies between a few metres to 20 metres in thickness and is 600 metres wide (from 810,265 mE to 810,865 mE).



CRITERIA	JORC CODE EXPLANATION	COMMENTARY
Estimation and modelling techniques	<ul> <li>The nature and appropriateness of the estimation technique(s) applied and key assumptions, including treatment of extreme grade values, domaining, interpolation parameters and maximum distance of extrapolation from data points. If a computer assisted estimation method was chosen include a description of computer software and parameters used.</li> <li>The availability of check estimates, previous estimates and/or mine production records and whether the Mineral Resource estimate takes appropriate account of such data.</li> <li>The assumptions made regarding recovery of by-products.</li> <li>Estimation of deleterious elements or other non-grade variables of economic significance (e.g. sulphur for acid mine drainage characterization).</li> <li>In the case of block model interpolation, the block size in relation to the average sample spacing and the search employed.</li> <li>In the case of block model interpolation, the block size in relation to the average sample spacing and the search employed.</li> <li>Any assumptions about correlation between variables.</li> <li>Description of how the geological interpretation was used to control the resource estimates.</li> <li>Discussion of basis for using or not using grade cutting or capping.</li> <li>The process of validation, the checking process used, the comparison of model data to drill hole data, and use of reconciliation data if available.</li> </ul>	Estimation was completed in Datamine Studio RM using two estimation methods. Gold was estimation into a three-dimensional block model by dynamic anisotropy using ordinary kriging (OK) into the main domain (Domain 10). A hard boundary was used between the oxide and transitional and a hard boundary between transitional and fresh within the main domain. To capture the complex low angled surrounding mineralisation an unconstrained inverse distance cubed (ID <sup>3</sup> ) estimation technique was used. The drill spacing at The Porphyry Zone is a nominal 25 by 25 metres for the exploration holes for the majority of the deposits and 50 by 50 metres around the periphery. The main part of the deposit has been gc drilled out to 12.5 by 10 metres. Parent blocks of 4mE by 10mN by 5mRI were used for the block model to tie in with the existing grade control model. Sub blocking down to 1mE by 2.5mN by 1.25mRI was employed for resolution of the mineralisation boundaries as define by wireframes Drillhole sample data was flagged using domain codes generated from three-dimensional mineralisation domains. The samples were composited to 1 metre intervals. Variogram orientations were largely controlled by the strike of the mineralisation and downhole variography. The search ellipse for the background mineralisation is orientated striking towards the north and dipping 30° to the west. Kriging neighbourhood analysis was performed to optimise the block size, sample numbers and discretisation levels with the goal of minimising conditional bias in the gold grade estimates. Three search passes were used, with the first search pass set to the range of the variogram for each domain. A minimum of eight and a maximum of 30 samples were used. The search stayed the same for the second pass but was increased by a factor of two for the third and final pass. The minimum number of samples was reduced to 6 for the second pass and four for the third pass. No deleterious elements were found in the ore. No selective mining units have been assumed. Top cuts were
Moisture	• Whether the tonnages are estimated on a dry basis or with natural moisture, and the method of determination of the moisture content.	All tonnages have been estimated on a dry basis.
Cut-off parameters	The basis of the adopted cut-off grade(s) or quality parameters applied.	The cut-off grade of 1g/t for the stated open pit Mineral Resource estimate is determined from economic parameters that reflect geotechnical, mining and processing parameters and costs for an open pit mining operation.
Mining factors or assumptions	<ul> <li>Assumptions made regarding possible mining methods, minimum mining dimensions and internal (or, if applicable, external) mining dilution. It is always</li> </ul>	The Resource models assume that a moderate level of mining selectivity is achieved in open pit mining. It has been assumed



CRITERIA	JORC CODE EXPLANATION	COMMENTARY
	necessary as part of the process of determining reasonable prospects for eventual economic extraction to consider potential mining methods, but the assumptions made regarding mining methods and parameters when estimating Mineral Resources may not always be rigorous. Where this is the case, this should be reported with an explanation of the basis of the mining coumptings made	that high quality grade control will be applied to ore/waste delineation processes using RC drilling, or similar, at a nominal (and no greater) spacing of 10 metre by 12.5 metre and applying a pattern sufficient to ensure adequate coverage of the mineralisation zones. This is consistent with current mining practises at Syama.
	assumptions made.	
Metallurgical factors or assumptions	• The basis for assumptions or predictions regarding metallurgical amenability. It is always necessary as part of the process of determining reasonable prospects for eventual economic extraction to consider potential metallurgical methods, but the assumptions regarding metallurgical treatment processes and parameters made when reporting Mineral Resources may not always be rigorous. Where this is the case, this should be reported with an explanation of the basis of the metallurgical assumptions made.	No metallurgical factors or assumptions have been made during the resource estimation process as these will be addressed during the conversion to Ore Reserves.
Environmental factors or assumptions	<ul> <li>Assumptions made regarding possible waste and process residue disposal options. It is always necessary as part of the process of determining reasonable prospects for eventual economic extraction to consider the potential environmental impacts of the mining and processing operation. While at this stage the determination of potential environmental impacts, particularly for a green fields project, may not always be well advanced, the status of early consideration of these potential environmental impacts should be reported. Where these aspects have not been considered this should be reported with an explanation of the</li> </ul>	It is a requirement of Decree No.03-594/P-RM of 31 December 2003 of Malian law that an Environmental and Social Impact Study (Étude d'Impact Environmental et Social – EIES) must be undertaken to update the potential environmental and social impacts of the mine's redevelopment. The EIES for the Syama Gold Mine (including Tabakoroni) was approved in November 2007 and an Environment Permit (07- 0054/MEA – SG) was issued by the Ministry of Environment and Sanitation on 22 November 2007. The Ministry of Environment conducts timely reviews of the Syama Gold Mine to ensure that the Company maintains compliance with the EIES guidelines.
	environmental assumptions made.	At Syama and Tabakoroni, there are three key practices for disposal of wastes and residues namely, stacking of waste rock from open pit mining; storage of tailings from mineral processes; and "tall-stack dispersion" of sulphur dioxide from the roasting of gold bearing concentrate. All waste disposal practices are in accordance with the guidelines in the EIES.
		The Environmental and Social Impact Study – "Société des Mines de Syama, Syama Gold Mine, Mali", dated 2007 indicated there was minimal potential for acid mine drainage from waste rock due to the elevated carbonate content which buffers a potential acid generation. Resolute maintains a plan for progressive rehabilitation of waste rock landforms as part of ongoing mine development and waste rock dumping.
		The landform of tailings impoundments does not have a net acid generating potential. The largest volume is flotation tailings where the sulphide minerals have already been removed from the host rock. Its mineralogy includes carbonates which further buffer any acid-formation potential from sulphides that may also be present.
		Cyanide levels in the leached-calcine tailings are typically less than 50ppm in the weak acid dissociable form. Groundwater away from the tailings landform is intercepted by trenches and sump pumps.
		Sulphur dioxide is generated from the roasting of gold concentrate so that gold can be extracted and refined. Tall- Stack "dispersion" of the sulphur dioxide emission is monitored continuously. Prevailing weather and dissipation of the sulphur dioxide is modelled daily to predict the need to pause the roasting process to meet the air quality criteria set out in the Environmental & Social Impact Study.



CRITERIA	JORC CODE EXPLANATION	COMMENTARY
Bulk density	<ul> <li>Whether assumed or determined. If assumed, the basis for the assumptions. If determined, the method used, whether wet or dry, the frequency of the measurements, the nature, size and representativeness of the samples.</li> <li>The bulk density for bulk material must have been measured by methods that adequately account for void spaces (vugs, porosity, etc), moisture and differences between rock and alteration zones within the deposit.</li> <li>Discuss assumptions for bulk density estimates used in the evaluation process of the different materials.</li> </ul>	No bulk density measurements have been taken at the Porphyry Zone. An average SG was applied to the model by weathering types based on similar deposits at Syama: • Oxide 2.12 t/m <sup>3</sup> • Transitional 2.38 t/m <sup>3</sup> • Fresh 2.72 t/m <sup>3</sup>
Classification	<ul> <li>The basis for the classification of the Mineral Resources into varying confidence categories.</li> <li>Whether appropriate account has been taken of all relevant factors (i.e. relative confidence in tonnage/ grade estimations, reliability of input data, confidence in continuity of geology and metal values, quality, quantity and distribution of the data).</li> <li>Whether the result appropriately reflects the Competent Person's view of the deposit.</li> </ul>	In general, the Inferred Mineral Resource classification is applied to extensions of mineralised zones on the margins of the deposit where drill spacing is more than 50m x 50m and the extents of mineralisation at depth. However, due to the complexity of the surrounding mineralisation and the low confidence in the geological interpretation in addition to the estimation method being unconstrained. The competent person decided to classify the whole of the deposit to Inferred until more drilling can be carried out. The validation of the block model has confirmed satisfactory correlation of the input data to the estimated grades and reproduction of data trends. The Mineral Resource estimates appropriately reflects the view
		of the Competent Person.
Audits or reviews	<ul><li>The results of any audits or reviews of Mineral</li><li>Resource estimates.</li></ul>	There has been no external review of the Mineral Resource estimate.
Discussion of relative accuracy/ confidence	<ul> <li>Where appropriate a statement of the relative accuracy and confidence level in the Mineral Resource estimate using an approach or procedure deemed appropriate by the Competent Person. For example, the application of statistical or geostatistical procedures to quantify the relative accuracy of the resource within stated confidence limits, or, if such an approach is not deemed appropriate, a qualitative discussion of the factors that could affect the relative accuracy and confidence of the estimate.</li> <li>The statement should specify whether it relates to global or local estimates, and, if local, state the relevant tonnages, which should be relevant to technical and economic evaluation. Documentation should include assumptions made and the procedures used.</li> <li>These statements of relative accuracy and confidence of the estimate should be compared with production data, where available.</li> </ul>	The Mineral Resource estimate has been classified based on the quality of the data collected, the density of data, the confidence of the geological models and mineralisation models, and the grade estimation quality. This has been applied to a relative confidence based on data density and zone confidence for resource classification. No relative statistical or geostatistical confidence or risk measure has been generated or applied. Mine production data was used in the validation process and showed to be within 20% of the estimated tonnes, grade and ounces within the mined area.



#### Section 4 Estimation and Reporting of Ore Reserves

CRITERIA	JORC CODE EXPLANATION	COMMENTARY
Mineral Resource estimate for conversion to Ore Reserves	<ul> <li>Description of the Mineral Resource estimate used as a basis for the conversion to an Ore Reserve.</li> <li>Clear statement as to whether the Mineral Resources are reported additional to, or inclusive of, the Ore Reserve.</li> </ul>	Resources at Porphyry Zone are reported above a 1g/t cut-off. This was calculated as a marginal cut-off utilising open pit mining methods. Material below this cut-off is not included in the Mineral Resource.
		Ore Reserves are the material reported as a sub-set of the resource, that which can be extracted from the mine and processed with an economically acceptable outcome.
		Mineral Resources are reported inclusive of Ore Reserves.
Site visits • Comment on any site visits undertaken by the Competent Mr Kitwa I and Meta	Mr Kitwa Ndjibu is member of the Australasian Institute of Mining and Metallurgy and is a Competent Person who has visited the	
	<ul> <li>If no site visits have been undertaken indicate why this is the case.</li> </ul>	site the project is located.
Study status	<ul> <li>The type and level of study undertaken to enable Mineral Resources to be converted to Ore Reserves.</li> <li>The Code requires that a study to at least Pre-Feasibility Durate level the theorem is to be a study to at least Pre-Feasibility</li> </ul>	The Porphyry Zone deposit is adjacent to the Tabakoroni mine which had a Feasibility study was completed in 2009 with updates in 2012 and 2016.
	Study level has been undertaken to convert Mineral Resources to Ore Reserves. Such studies will have been carried out and will have determined a mine plan that is technically achievable and economically viable, and that material Modifying Factors have been considered.	Tabakoroni has been in continuous mining operation since August 2018. During this time the performance the project has shown a positive reconciliation between mineral resources and gold production and delivered positive cashflows.
Cut-off parameters	• The basis of the cut-off grade(s) or quality parameters applied.	A cut-off of 0.8 g/t has been applied for Tabakoroni Oxide ore.
Mining factors or assumptions	<ul> <li>The method and assumptions used as reported in the Pre-Feasibility or Feasibility Study to convert the Mineral Resource to an Ore Reserve (i.e. either by application of appropriate factors by optimization or by preliminary or detailed design).</li> </ul>	The reported Ore Reserve estimate for Porphyry Zone is based on pit optimisations conducted using the Lerchs-Grossman (LG) algorithm of the Whittle software to calculate the optimal pit at specific input parameters and pit designs. Costs are based on existing contract mining and haulage rates and site costs which
	<ul> <li>The choice, nature and appropriateness of the selected mining method(s) and other mining parameters including associated design issues such as pre-strip, access, etc.</li> </ul>	are understood with a high degree of accuracy. Mining is undertaken by conventional open pit methods of drill
	<ul> <li>The assumptions made regarding geotechnical parameters (e.g. pit slopes, stope sizes, etc.), grade control and pre-production drilling.</li> </ul>	and blast, followed by load and haul, utilising mining equipment comprising 120t – 230t diesel hydraulic excavators and 90t off-highway dump trucks.
	<ul> <li>The major assumptions made and Mineral Resource model used for pit and stope optimization (if appropriate).</li> </ul>	Detailed pit design work was completed based on pit optimisations using Whittle Four-X optimisation software. Only
	The mining dilution factors used.	Indicated Resources were used in the pit optimisation.
	The mining recovery factors used.	Pit slope parameters for Porphyry Zone were based on a
	Any minimum mining widths used.	geotechnical assessment that included a total of seven specific
	<ul> <li>The manner in which Inferred Mineral Resources are utilized in mining studies and the sensitivity of the outcome to their inclusion.</li> </ul>	geotechnical holes. Overall slopes angles are approximately 40°. All other pits adopt similar overall slope angles.
	The infrastructure requirements of the selected mining methods.	Grade control consists of RC drilling, based on a 5.0mE x 12.5mN drill pattern
		The MIK resource estimation technique used for the Porphyry Zone implicitly incorporates internal mining dilution at the scale of the assessed SMU so no additional modifying factor was applied.



CRITERIA	JORC CODE EXPLANATION	COMMENTARY
Metallurgical factors or assumptions	<ul> <li>The metallurgical process proposed and the appropriateness of that process to the style of mineralization.</li> </ul>	Processing is by conventional primary crushing followed by single stage SAG milling. Gold recovery is by means of a gravity recovery circuit and carbon in leach process.
	<ul> <li>Whether the metallurgical process is well-tested technology or novel in nature.</li> </ul>	Processing recoveries used are 90%, 80% and 65% for Oxide, Transitional and fresh material respectively.
	<ul> <li>The nature, amount and representativeness of metallurgical test work undertaken, the nature of the metallurgical domaining applied and the corresponding metallurgical recovery factors applied.</li> </ul>	Mine is operational with good reconciliation between predicted recoveries and actual
	<ul> <li>Any assumptions or allowances made for deleterious elements.</li> </ul>	Allowances are made in the recovery estimates for transitional and fresh ore as the Au recovery is impacted by some of the
	<ul> <li>The existence of any bulk sample or pilot scale test work and the degree to which such samples are considered representative of the ore body as a whole.</li> </ul>	gold being hosted in refractory sulphide and preg-robbing carbon.
	<ul> <li>For minerals that are defined by a specification, has the ore reserve estimation been based on the appropriate mineralogy to meet the specifications?</li> </ul>	
Environmental	<ul> <li>The status of studies of potential environmental impacts of the mining and processing operation. Details of waste</li> </ul>	An active waste rock characterisation program has been put in place for Porphyry Zone.
	rock characterization and the consideration of potential sites, status of design options considered and, where applicable, the status of approvals for process residue storage and waste dumps should be reported.	Ore Reserves from Porphyry Zone will be processed at Syama and tailings storage will be impounded in existing footprint area approved in the Environmental & Social Impact Study. Progressive raising of the tailings occurs regularly with the 9th lift completed in 2019. Routine progress on the monitoring is reported to government and at stakeholder meetings in concert with routine inspections by government representatives.
Infrastructure	• The existence of appropriate infrastructure: availability of land for plant development, power, water, transportation (particularly for bulk commodities), labour, accommodation; or the ease with which the infrastructure can be provided, or accessed.	All required infrastructure is already in place for the Porphyry Zone deposit which is within the current the Tabakoroni mine footprint
Costs	The derivation of, or assumptions made, regarding	The Porphyry Zone deposit is adjacent to the Tabakoroni mine,
	projected capital costs in the study.	with established mining operations. Ore is trucked to Syama where it is processed at Syama's oxide circuit. General and
	The methodology used to estimate operating costs.	administration costs are shared between the oxide plant and the
	Allowances made for the content of deleterious elements.     The derivation of economytican mode of motel or	sulphide plant which treats the Syama UG orebody. The
	<ul> <li>The derivation of assumptions made of metal of commodity price(s), for the principal minerals and co- products.</li> </ul>	the Tabakoroni pits using the same mining and haulage fleet. The mining and haulage rates are based on known contract
	• The source of exchange rates used in the study.	rates.
	Derivation of transportation charges.	The oxide plant produces gold doré (without problematic
	<ul> <li>The basis for forecasting or source of treatment and refining charges, penalties for failure to meet specification, etc.</li> </ul>	deleterious elements) that is subsequently refined offsite. Refining costs are not material.
	The allowances made for royalties payable, both     Government and private.	Exchange rates used for planning purposes are from consensus forecasts provided by external corporate advisers.
		Ad valorem Government royalties of 6% are payable on gold production.



CRITERIA	JORC CODE EXPLANATION	COMMENTARY
Revenue factors	<ul> <li>The derivation of, or assumptions made regarding revenue factors including head grade, metal or commodity price(s) exchange rates, transportation and treatment charges, penalties, net smelter returns, etc.</li> <li>The derivation of assumptions made of metal or commodity price(s), for the principal metals, minerals and co-products.</li> </ul>	A gold price of US\$1,500/oz formed the basis of the Ore Reserves.
Market assessment	<ul> <li>The demand, supply and stock situation for the particular commodity, consumption trends and factors likely to affect supply and demand into the future.</li> <li>A customer and competitor analysis along with the identification of likely market windows for the product.</li> <li>Price and volume forecasts and the basis for these forecasts.</li> <li>•or industrial minerals the customer specification, testing and acceptance requirements prior to a supply contract.</li> </ul>	The market for gold is robust with prevailing gold price being around US\$1,850/oz. Supply and demand are not considered material to the Ore Reserve calculations.
Economic	<ul> <li>The inputs to the economic analysis to produce the net present value (NPV) in the study, the source and confidence of these economic inputs including estimated inflation, discount rate, etc.</li> <li>NPV ranges and sensitivity to variations in the significant assumptions and inputs.</li> </ul>	The financial evaluation undertaken as part of the evaluation of these open pits indicated a positive net present value (NPV) at a 5% discount rate and operating results to date have exceeded production and NPV forecasts.
Social	The status of agreements with key stakeholders and matters leading to social license to operate.	The Porphyry Zone falls under the SOMIFI exploitation permit and is managed by SOMISY SA under Management and Toll Treatment agreements lodged with the Government of Mali. It is the intention to encourage economic development within the local community. During the operation of Tabakoroni and its satellite deposits the focus has been on improving farming and health care plus providing access to water; this will continue to remain a focus. The Syama Mine Community Consultative Committee, which includes representation from Tabakoroni and the villages adjacent to the Syama Satellites, was established in February 2001 with representatives from local villages, the Malian Government and SOMISY. Since April 2004 the Committee has met regularly as a communication forum and to address community issues and assist with community project proposals; it continues to meet on the first or second Tuesday of each month.
Other	<ul> <li>To the extent relevant, the impact of the following on the project and/or on the estimation and classification of the Ore Reserves:</li> <li>Any identified material naturally occurring risks.</li> <li>The status of material legal agreements and marketing arrangements.</li> <li>The status of governmental agreements and approvals critical to the viability of the project, such as mineral tenement status, and government and statutory approvals. There must be reasonable grounds to expect that all necessary Government approvals will be received within th timeframes anticipated in the Pre-Feasibility or Feasibility study. Highlight and discuss the materiality of any unresolved matter that is dependent on a third party on which extraction of the reserve is contingent.</li> </ul>	All current government agreements and approvals are in good standing and no anticipated changes are expected.



CRITERIA	JORC CODE EXPLANATION	COMMENTARY
Classification	<ul> <li>The basis for the classification of the Ore Reserves intraversing confidence categories.</li> <li>Whether the result appropriately reflects the Competer Person's view of the deposit.</li> <li>The proportion of Probable Ore Reserves that have be derived from Measured Mineral Resources (if any).</li> </ul>	<ul> <li>Proved and Probable Ore Reserves were declared based on the Measured and Indicated Mineral Resources.</li> <li>The Ore Reserve estimate appropriately reflects the Competent Person's view of the deposit.</li> </ul>
Audits or reviews	The results of any audits or reviews of Ore Reserve estimates.	
Discussion of relative accuracy/ confidence	<ul> <li>Where appropriate a statement of the relative accurace and confidence level in the Ore Reserve estimate using an approach or procedure deemed appropriate by the Competent Person. For example, the application of statistical or geostatistical procedures to quantify the relative accuracy of the reserve within stated confiden limits, or, if such an approach is not deemed appropria a qualitative discussion of the factors which could affer the relative accuracy and confidence of the estimate.</li> </ul>	<i>y</i> The relative accuracy and confidence of the Ore Reserve estimate is inherent in the Ore Reserve Classification.
	<ul> <li>The statement should specify whether it relates to glob or local estimates, and, if local, state the relevant tonnages, which should be relevant to technical and economic evaluation. Documentation should include assumptions made and the procedures used.</li> </ul>	bal
	<ul> <li>Accuracy and confidence discussions should extend to specific discussions of any applied Modifying Factors may have a material impact on Ore Reserve viability, for which there are remaining areas of uncertainty at th current study stage.</li> </ul>	o that or he
	<ul> <li>It is recognized that this may not be possible or appropriate in all circumstances. These statements of relative accuracy and confidence of the estimate shou be compared with production data, where available.</li> </ul>	ld

At 31 December 2022



#### Mako

### **Section 1 Sampling Techniques and Data**

CRITERIA	JORC CODE EXPLANATION	COMMENTARY
Sampling techniques	<ul> <li>Nature and quality of sampling (e.g. cut channels, random chips, or specific specialised industry standard measurement tools appropriate to the minerals under investigation, such as down hole gamma sondes, or handheld XRF instruments, etc.). These examples should not be taken as limiting the broad meaning of sampling.</li> <li>Include reference to measures taken to ensure sample representivity and the appropriate calibration of any measurement tools or systems used.</li> <li>Aspects of the determination of mineralisation that are Material to the Public Report.</li> <li>In cases where 'industry standard' work has been done this would be relatively simple (e.g. 'reverse circulation drilling was used to obtain 1 m samples from which 3 kg was pulverised to produce a 30 g charge for fire assay'). In other cases more explanation may be required, such as where there is coarse gold that has inherent sampling problems. Unusual commodities or mineralisation types (e.g. submarine nodules) may warrant disclosure of detailed information</li> </ul>	Sampling has been by diamond drill coring and reverse circulation chip techniques with minor trench and surface sampling. Diamond core is geologically logged and sampled to geological contacts with nominal sample lengths between 0.3m and 4.5m (most commonly 1.5m). Core selected for assay is systematically cut lengthwise into half core by diamond blade rock saw, numbered and bagged before dispatch to the laboratory for analysis. All core is photographed, wet and dry. Reverse circulation chips are geologically logged and sampled on regular lengths of 1m. Chip material selected for assay is systematically divided to a 1/8 proportion using a rotary splitter attached to the cyclone sample recovery system, numbered and bagged before dispatch to the laboratory for analysis.
Drilling techniques	<ul> <li>Drill type (e.g. core, reverse circulation, open-hole hammer, rotary air blast, auger, Bangka, sonic, etc.) and details (e.g. core diameter, triple or standard tube, depth of diamond tails, face-sampling bit or other type, whether core is oriented and if so, by what method, etc.).</li> </ul>	Diamond core drilling with standard inner tubes. NTW diameter (57.1 mm) to target depth where possible with some smaller NQ2 intervals as tails. Core is marked and oriented. Reverse Circulation drilling with 4" or 4.5" hammer and 4" rod string to target depth.
Drill sample recovery	<ul> <li>Method of recording and assessing core and chip sample recoveries and results assessed.</li> <li>Measures taken to maximise sample recovery and ensure representative nature of the samples.</li> <li>Whether a relationship exists between sample recovery and grade and whether sample bias may have occurred due to preferential loss/gain of fine/coarse material.</li> </ul>	Diamond core recoveries are measured in the core trays and recorded as recovered metres and recovered % as part of the geological logging process. Diamond core drilling prior to the latest deep diamond drilling had just over 96% of core sample intervals measured (28,701 measurements totalling 46,200m of core) with core recoveries of 75% or better. Approximately 85% of core sample intervals measured had core recoveries of 100%. The percentage core recovery data was examined graphically against the gold grades and Cube established that no relationship is evident between core loss and gold grade in the regions of low core recovery. In 2016 % core recovery data was examined graphically against the gold grades and no relationship is evident between core loss and gold grade in the regions of low sample recovery. RC recoveries are monitored by chip sample weight recording. Of 43 RC holes reviewed by Cube in 2016 all recorded weight/m in consolidated rock material ranged from 19 to 38kg/m (mode=25; mean=25; median=25kg/m) which equates to rock densities between 2 and 3gcm3.
Logging	<ul> <li>Whether core and chip samples have been geologically and geotechnically logged to a level of detail to support appropriate Mineral Resource estimation, mining studies and metallurgical studies.</li> <li>Whether logging is qualitative or quantitative in nature. Core (or costean, channel, etc.) photography.</li> <li>The total length and percentage of the relevant intersections logged.</li> </ul>	Diamond core has been geologically and geotechnically logged to a level of detail to support appropriate classification and reporting of a Mineral Resource. Reverse circulation chip samples have been geologically logged to a level of detail to support appropriate classification and reporting of a Mineral Resource. Total length of DD logged data is 69,728.01m from total 70,527.01m drilled.
Sub-sampling techniques and	If core, whether cut or sawn and whether quarter, half or all core taken.	Core is systematically cut lengthwise into half core with a diamond saw.



RITERIA	JORC CODE EXPLANATION	COMMENTARY
sample preparation	<ul> <li>If non-core, whether riffled, tube sampled, rotary split, etc. and whether sampled wet or dry.</li> <li>For all sample types, the nature, quality and appropriateness</li> </ul>	In the initial drill phases between 2kg and 6kg of broken core sample was dispatched by contracted truck transport to SGS Mali (Phase 1- 90 holes) or ALS Mali (Phases 2 and 3 – 88 holes) for sample preparation.
	<ul> <li>of the sample preparation technique.</li> <li>Quality control procedures adopted for all sub-sampling stages to maximise representivity of samples.</li> <li>Measures taken to ensure that the sampling is representative of the in situ material collected, including for instance results for field duplicate/second-half sampling.</li> <li>Whether sample sizes are appropriate to the grain size of the material being sampled.</li> </ul>	<ul> <li>More recent samples (Phase 3 to 5 and the 2018 deep diamond holes) have undergone sample preparation at the site sample prep laboratory.</li> <li>The 2018 deep diamond programme (PWD362 to 420) was prepared onsite with assay pulps analysed by ALS Loughrea (Ireland).</li> <li>RC samples representing a 1/8 split are taken directly from the rig mounted cyclone by rotary splitter, sample weight is recorded sample is bagged in pre numbered plastic and sample tickets ar inserted and bag is sealed for transport to preparation facility.</li> <li>Generally, one of each of the two control samples (blank or CRN standard) is inserted into the sample stream every tenth sample Over the 2018 deep diamond programme A total of 4,582 samples have had 249 CRM and 260 blanks inserted, sufficient as per industry standards. An industry standard, documented process of sample mark-up, core splitting, bagging and ticketing and recording is in place at the Mako site. The laboratories sample preparation followed a standard documented process flow with whole sample crushing (better than 70% passing 2mm followed by a 1kg riffle split for pulverisation to 75 micron (better than 85% pass).</li> <li>Master pulps of 250g were split and placed in airtight, sealed bags and sent by courier to the assaying laboratory for analysis. For the majority of the Phase 1 drilling the mineralised interval sample preparation done at SGS Mali has been repeated and re assayed. As a result the nature, quality and appropriateness of the sample preparation technique are to industry standard.</li> </ul>
Quality of assay data and laboratory tests	<ul> <li>The nature, quality and appropriateness of the assaying and laboratory procedures used and whether the technique is considered partial or total.</li> </ul>	Au assays are determined by fire assay with AAS finish. Laboratory and assay procedures are appropriate for Mineral Resource estimation.
	<ul> <li>For geophysical tools, spectrometers, handheld XRF instruments, etc., the parameters used in determining the analysis including instrument make and model, reading times, calibrations factors applied and their derivation, etc.</li> </ul>	QAQC consisted of standards, blanks and laboratory duplicates (both coarse and pulp). The QAQC sample results showed acceptable levels of accuracy and precision.
	<ul> <li>Nature of quality control procedures adopted (e.g. standards, blanks, duplicates, external laboratory checks) and whether acceptable levels of accuracy (i.e. lack of bias) and precision have been established.</li> </ul>	The assay data is considered by Cube to be suitable for Mineral Resource estimation.
Verification of sampling and assaying	<ul> <li>The verification of significant intersections by either independent or alternative company personnel.</li> <li>The use of twinned holes.</li> </ul>	All aspects of the core sampling, assay procedures and QA/QC program have been reviewed by Cube and were judged to be of industry standard and suitable for use in the estimation of Mineral Resources.
	Documentation of primary data, data entry procedures, data verification, data storage (physical and electronic) protocols.	Independent sampling has been undertaken by Cube and the results closely match the original data.
	Discuss any adjustment to assay data.	Drill hole assay result data has been checked against the origina hardcopy laboratory assay reports by Cube for a representative number of holes.
		Cube has in 2014 undertaken site based checks of the raw assay data to verify grade intersections were consistent with a visual inspection of mineralisation in the core.
		Below detection limit values (negatives) have been replaced by



CRITERIA	JORC CODE EXPLANATION	COMMENTARY
		Un-sampled intervals have been retained as un-sampled (null or blank). The majority of these intervals occur within the waste domain and have no material impact on the estimate.
Location of data points	<ul> <li>Accuracy and quality of surveys used to locate drill holes (collar and down-hole surveys), trenches, mine workings and other locations used in Mineral Resource estimation.</li> </ul>	Drill holes have been surveyed by a contract surveyor (P.C. Drysdale Land and Engineering Surveyor) using a Leica GS12 GNSS (GPS) survey system.
	<ul><li>Specification of the grid system used.</li><li>Quality and adequacy of topographic control.</li></ul>	Down hole surveys were undertaken by the drilling contractor using a Reflex Ex-Trac tool with a reading taken approx. every 50m down the hole.
		During the August 2018 site visit Cube made independent verification of the collar surveys of three diamond core in progress holes (PWD409, 408 and 407) which were all found to be within an acceptable tolerance of the planned and reported coordinates. Cube also verified the coordinated positions of laid out grade control planned holes on the pit floor.
		Grid system is based on the UTM28N grid on the WGS84 ellipsoid. Survey heights are based on PRS097 (with independent checks on AusPos) and are orthometric (i.e. msl).
		A topographic surface was provided based on a one metre resolution satellite DTM surface of Central Mako, including the Petowal prospect area, and a number of smaller resolution (10m x 10m) data files derived from the one metre source data. Cube utilised the smaller resolution data (10m x 10m) for all validation and estimation purposes.
Data spacing and distribution	<ul> <li>Data spacing for reporting of Exploration Results.</li> <li>Whether the data spacing and distribution is sufficient to establish the degree of geological and grade continuity appropriate for the Mineral Resource and Ore Reserve estimation procedure(s) and classifications applied.</li> <li>Whether sample compositing has been applied.</li> </ul>	Data spacing is variable being in the range of 80m x 40m to 20m x 20m. Additionally, a significant area of grade control drilling at 10m x 10m has been completed defining a volume of approximately four million BCM. This spacing is adequate to determine the geological and grade continuity for reporting of Measured, Indicated and Inferred Mineral Resources. Drill samples were composited to 3m for use in the estimate.
Orientation of data in relation to geological structure	<ul> <li>Whether the orientation of sampling achieves unbiased sampling of possible structures and the extent to which this is known, considering the deposit type.</li> <li>If the relationship between the drilling orientation and the orientation of key mineralised structures is considered to have introduced a sampling bias, this should be assessed and reported if material</li> </ul>	The drill hole orientation was designed to intersect the mineralisation orthogonal to dip and strike of the major mineralisation bodies. The majority of drill hole azimuths were between 140° and 160° with dips varying from -50 to -80° below horizontal. For a small number of holes, different orientations were selected to target different portions of the mineralisation depending on localised mineralised structures or features.
		The preliminary RC grade control programme drilling was all vertical (azimuth of 0° and dip of -90°). Mine grade control during 2017 and 2018 was primarily drilled on azimuth 140° dipping -60°.
		Drilling primarily targeted the FEL unit which contained the most significant mineralisation and dipped at about 20-30° to the northwest near surface, steepening to about 45° dip at depth. The drilling orientation is adequate for a non-biased assessment of the orebody with respect to interpreted structures and interpreted controls on mineralisation.
Sample security	• The measures taken to ensure sample security.	Labelling and submission of samples complies with industry standard.
Audits or reviews	The results of any audits or reviews of sampling techniques and data.	An independent audit of the sample preparation laboratory has been undertaken in 2018 (Fis, 2018) and the review undertaken at the project by Cube in August 2018 and both found no material issues with the sampling methods or data.



#### **Section 2 Reporting of Exploration Results**

CRITERIA	JORC CODE EXPLANATION	COMMENTARY
Mineral tenement and land tenure status	<ul> <li>Type, reference name/number, location and ownership including agreements or material issues with third parties such as joint ventures, partnerships, overriding royalties, native title interests, historical sites, wilderness or national park and environmental settings.</li> <li>The security of the tenure held at the time of reporting along with any known impediments to obtaining a licence to operate in the area.</li> </ul>	To date no exploration results have been reported on a granted exploration permit, owned 100% by Petowal Mining Company SA (Petowal). The permit is in good standing.
Exploration done by other parties	<ul> <li>Acknowledgment and appraisal of exploration by other parties.</li> </ul>	Exploration has been performed by Mako Exploration Company SARL ("MEC"), 100% owned by TORO.
Geology	Deposit type, geological setting and style of mineralisation.	It is currently interpreted that the northeast striking structure controlled the flow of the gold bearing hydrothermal fluids, with the preferential chemistry/rheology of the felsic volcanic horizon acting as a favourable horizon for silicification and the deposition of the gold-pyrite mineral assemblage. Intensity of gold mineralisation appears to correlate with the intensity of pyrite development and exhibits good lateral and vertical continuity through the mineralised zone. Mineralisation has a relatively simple geometry comprising a zone that varies from 30 to 60m in width, along the 1,700m strike length drilled to date. The zone dips approximately 20-30° to the northwest near surface, steepening to approximately 45° dip at depth.
Drill hole Information	<ul> <li>A summary of all information material to the understanding of the exploration results including a tabulation of the following information for all Material drill holes: <ul> <li>easting and northing of the drill hole collar</li> <li>elevation or RL (Reduced Level – elevation above sea level in metres) of the drill hole collar</li> <li>dip and azimuth of the hole</li> <li>down hole length and interception depth</li> <li>Whole length.</li> </ul> </li> <li>If the exclusion of this information is justified on the basis that the information is not Material and this exclusion does not detract from the understanding of the report, the Competent Person should clearly explain why this is the case.</li> </ul>	Easting, Northing and RL of the drill hole collars are based on the UTM28N grid on the WGS84 ellipsoid. Survey heights are based on PRS097 (with independent checks on AusPos) and are orthometric (i.e. msl). The MRE has used drill hole collar RL derived from the topographical surface. Dip is the inclination of the hole from the horizontal. For example, a vertically down drilled hole from the surface is -90°. Azimuth is reported in degrees as the grid direction toward which the hole is drilled. Down hole length of the hole is the distance from the surface to the end of the hole, as measured along the drill trace. Intersection depth is the distance down the hole as measured along the drill trace. Drill hole length is the distance from the surface to the end of the drill trace.
Data aggregation methods	<ul> <li>In reporting Exploration Results, weighting averaging techniques, maximum and/or minimum grade truncations (e.g. cutting of high grades) and cut-off grades are usually Material and should be stated.</li> <li>Where aggregate intercepts incorporate short lengths of high grade results and longer lengths of low grade results, the procedure used for such aggregation should be stated and some typical examples of such aggregations should be shown in detail.</li> <li>The assumptions used for any reporting of metal equivalent values should be clearly stated.</li> </ul>	Gold assay intercepts were composited to 3m length down the hole, using length weighting, in order to provide a uniform sample support size for grade estimation. High grade cuts have been applied to gold grade composites, but only for use in producing check estimates. The primary, reported estimates were based on a Uniform Conditioning approach which used cut grade values. The assay intervals are reported as down hole length as the true width variable is not known. Gold assays are rounded to two decimal places. No metal equivalent reporting is used or applied.
Relationship between mineralisation	These relationships are particularly important in the reporting of Exploration Results.	The intersection width is measured down the hole trace and may not be the true width.



CRITERIA	JORC CODE EXPLANATION	COMMENTARY
widths and intercept lengths	<ul> <li>If the geometry of the mineralisation with respect to the drill hole angle is known, its nature should be reported.</li> <li>If it is not known and only the down hole lengths are reported, there should be a clear statement to this effect (e.g. 'down hole length, true width not known').</li> </ul>	All drill results are downhole intervals only due to the variable orientation of the mineralisation.
Diagrams	<ul> <li>Appropriate maps and sections (with scales) and tabulations of intercepts should be included for any significant discovery being reported These should include, but not be limited to a plan view of drill hole collar locations and appropriate sectional views.</li> </ul>	A plan view is contained within this document. New cross- sectional interpretations are included.
Balanced reporting	<ul> <li>Where comprehensive reporting of all Exploration Results is not practicable, representative reporting of both low and high grades and/or widths should be practiced to avoid misleading reporting of Exploration Results.</li> </ul>	Diamond and RC drill holes forming the basis of the Mineral Resource estimate have been reported previously as part of the 2018 MRE. Additional drilling has informed the 2018 update.
Other substantive exploration data	Other exploration data, if meaningful and material, should be reported including (but not limited to): geological observations; geophysical survey results; geochemical survey results; bulk samples – size and method of treatment; metallurgical test results; bulk density, groundwater, geotechnical and rock characteristics; potential deleterious or contaminating substances.	No other exploration data is considered meaningful and material to this document.
Further work	<ul> <li>The nature and scale of planned further work (e.g. tests for lateral extensions or depth extensions or large-scale stepout drilling).</li> <li>Diagrams clearly highlighting the areas of possible extensions, including the main geological interpretations and future drilling areas, provided this information is not commercially sensitive.</li> </ul>	Future exploration may involve the drilling of more drill holes, both diamond core and reverse circulation, to further extend the mineralised zones and to collect additional detailed data on known mineralized zones. Geophysical exploration is also planned as part of the future exploration of the permit.



#### Section 3 Estimation and Reporting of Mineral Resources

CRITERIA	JORC CODE EXPLANATION	COMMENTARY
Database integrity	<ul> <li>Measures taken to ensure that data has not been corrupted by, for example, transcription or keying errors, between its initial collection and its use for Mineral Resource estimation purposes.</li> <li>Data validation procedures used.</li> </ul>	Database is maintained by PMC who compile and validate all data files on the project. Cube completed validation checks on the database including checks for overlapping sample intervals, checks on minimum and maximum assays, depths, azimuths, dips and co-ordinates for consistency. No material errors were identified. Cube undertook site based checks of the raw assay data to verify that grade intersections were consistent with a visual inspection of mineralisation in the core. A number of drill hole collar positions were also verified in the field.
Site visits	<ul> <li>Comment on any site visits undertaken by the Competent Person and the outcome of those visits.</li> <li>If no site visits have been undertaken indicate why this is the case.</li> </ul>	The competent Person (Marcus Osiejak) has not conducted a site visit. The previous Competent Person (Patrick Adams) a current employee of Cube Consulting conducted a site visit to the Mako Project between 8th and 14th February 2014 and 11th to 14th August 2018 and undertook independent inspection of all pertinent aspects of the project.
Geological interpretation	<ul> <li>Confidence in (or conversely, the uncertainty of) the geological interpretation of the mineral deposit.</li> <li>Nature of the data used and of any assumptions made.</li> <li>The effect, if any, of alternative interpretations on Mineral Resource estimation.</li> <li>The use of geology in guiding and controlling Mineral Resource estimation.</li> <li>The factors affecting continuity both of grade and geology.</li> </ul>	The geological confidence is considered by Cube to be moderate to high. The mineralised volume at Petowal has been based on a drill section interpretation of mineralisation defined by a lower limit gold grade of 0.2 g/t Au, along with the observed close association between mineralisation and the felsic lithological unit. The overall shape and trend of the mineralisation was guided by the form of the felsic unit and its contacts with the surrounding basalt. Four mineralisation domains, the first contained within the felsic unit, the second and third in the adjacent footwall basalt and the fourth in the hanging wall basalt unit, were defined (Domains 100 200 300 400, respectively). A separate Domain (500) was created based on mineralisation 450m northwest of the Mako deposit. An overall envelope, called Domain 1 encapsulating all the material not contained within Domains 100, 200, 300, 400 and 500 out to the limit of drill coverage, was also created. The resulting volumes encapsulate the complete mineralised distribution and produce a model that reduces the risk of conditional bias that could be introduced where the constraining interpretation and data selection is based on a significantly higher grade than the natural geological grade cut-off. The factors affecting continuity both of grade and geology are most likely to be associated with structural controls and local complexity, the knowledge of which is limited with the current spacing of information. The broad approach to the mineralisation modelling is an attempt to model an unbiased interpretation.
Dimensions	• The extent and variability of the Mineral Resource expressed as length (along strike or otherwise), plan width, and depth below surface to the upper and lower limits of the Mineral Resource.	The gold mineralisation identified to date varies from 30m to 60m in width, along the 1,700m strike length drilled to date. The zone dips approximately 20-30° to the northwest near surface, steepening to approximately 45° dip at depth.
Estimation and modelling techniques	• The nature and appropriateness of the estimation technique(s) applied and key assumptions, including treatment of extreme grade values, domaining, interpolation parameters and maximum distance of extrapolation from data points. If a computer assisted estimation method was chosen include a description of computer software and parameters used.	Three metre downhole composite gold grade data were interpolated into 20mE x 20mN x 5mRL sized panels using Ordinary Kriging (OK). The minimum number of composites was set at 8 and the maximum number of composites was set at either 16 (Domain



CRITERIA	J	ORC CODE EXPLANATION	COMMENTARY
			100), 26 (Domain 200) or 24 (Domains 300, 400 and 4000).
	• • • • •	<ul> <li>The availability of check estimates, previous estimates and/or mine production records and whether the Mineral Resource estimate takes appropriate account of such data.</li> <li>The assumptions made regarding recovery of by- products.</li> <li>Estimation of deleterious elements or other non-grade variables of economic significance (e.g. sulphur for acid mine drainage characterization).</li> <li>In the case of block model interpolation, the block size in relation to the average sample spacing and the search employed.</li> <li>In the case of block model interpolation, the block size in relation to the average sample spacing and the search employed.</li> <li>Any assumptions behind modelling of selective mining units.</li> <li>Any assumptions about correlation between variables.</li> <li>Description of how the geological interpretation was used to control the resource estimates.</li> <li>Discussion of basis for using or not using grade cutting or capping.</li> <li>The process of validation, the checking process used, the comparison of model data to drill hole data, and use of reconciliation data if available.</li> </ul>	The maximum search ellipse radius was set at either 180m (Domain 100), 160 (Domain 200), 120m (Domain 300), 200m (Domain 400) or 300m (Domain 4000). The orientation of the variogram model and search ellipse was dynamically set according to the shape of the felsic hanging wall and footwall, as well the trend of high grade mineralisation within the felsic unit. Change of Support (CoS) calculations were conducted, conditioned to the panel grade estimates, for selectivity on 5mE x 5mN x 2.5mRL SMU-sized blocks in order to produce a recoverable resource estimate. The Gaussian-based Uniform Conditioning approach was applied to the OK check grade estimates. An information effect correction was applied during the CoS calculations, to account for a future theoretical grade control drill configuration of 10mE x 10mN x 1mRL. The CoS process yields a set of array variables, stored in the panel block model, detailing the estimates for tonnage, grade and metal above a range of grade cut-offs. A process of localisation was completed, by which the output of the CoS is mapped into single grade estimate per 5mE x 5mN x 2.5mRL block in an SMU block model, which comprises the final product of the grade estimation. Domain 500 was estimated using ID2 methodology. Due to the limited number of samples within the domain a robust variogram could not be produced. Two passes were used with second pass
			having double the initial search radii of 45m.
			Surpac Mining software 6.9 and Isatis were used for estimation.
			No by-product recoveries were considered.
			Estimations of density were also made with this Mineral Resource estimation.
			Block model validation was undertaken globally by comparing the mean LUC block grade estimates to the mean of the informing composite grades on a domain by domain basis. The LUC estimates were also compared to the mean grade of a check ID <sup>2</sup> estimation.
Moisture	•	Whether the tonnages are estimated on a dry basis or with natural moisture, and the method of determination of the moisture content.	Moisture was not considered in the density assignment.
Cut-off parameters	•	The basis of the adopted cut-off grade(s) or quality parameters applied.	A nominal lower cut-off grade of 0.2g/t Au was used to define the mineralised domains to encompass the complete mineralised distribution and produce a model that reduces the risk of conditional bias that could be introduced where the constraining interpretation and data selection is based on a significantly higher grade than the natural geological grade cut-off.
			The cut-off grade for reporting (above 0.5g/t Au) was used in line with the previous resource reporting and is based on the results of Whittle optimisation shells using cost and recovery data sourced from the operation of the open pit mine by PMC during 2017-18.
			A Whittle optimisation shell using these operational costs and a gold price of US\$2,000/ounce has been used to limit the reported MRE to that with reasonable expectations of economic exploitation.
Mining factors or			The shallow occurrence of the mineralisation indicates that open



CRITERIA	JORC CODE EXPLANATION	COMMENTARY
	<ul> <li>Assumptions made regarding possible mining methods, minimum mining dimensions and internal (or, if applicable, external) mining dilution.</li> <li>It is always necessary as part of the process of determining reasonable prospects for eventual economic extraction to consider potential mining methods, but the assumptions made regarding mining methods and parameters when estimating Mineral Resources may not always be rigorous. Where this is the case, this should be reported with an explanation of the basis of the mining assumptions made.</li> </ul>	pit mining is appropriate for Petowal in line with other deposits in the area. The estimation methodology used results in an amount of edge dilution being incorporated into the blocks of the model. No account of mining loss has been incorporated.
Metallurgical factors or assumptions	• The basis for assumptions or predictions regarding metallurgical amenability. It is always necessary as part of the process of determining reasonable prospects for eventual economic extraction to consider potential metallurgical methods, but the assumptions regarding metallurgical treatment processes and parameters made when reporting Mineral Resources may not always be rigorous. Where this is the case, this should be reported with an explanation of the basis of the metallurgical assumptions made.	No specific assumptions were made regarding metallurgical factors for this estimate. Metallurgical test work on the mineralisation commenced in 2012 and is ongoing.
Environmental factors or assumptions	<ul> <li>Assumptions made regarding possible waste and process residue disposal options. It is always necessary as part of the process of determining reasonable prospects for eventual economic extraction to consider the potential environmental impacts of the mining and processing operation. While at this stage the determination of potential environmental impacts, particularly for a green fields project, may not always be well advanced, the status of early consideration of these potential environmental impacts should be reported. Where these aspects have not been considered this should be reported with an explanation of the environmental assumptions made.</li> </ul>	No assumptions were made regarding environmental restrictions.
Bulk density	<ul> <li>Whether assumed or determined. If assumed, the basis for the assumptions. If determined, the method used, whether wet or dry, the frequency of the measurements, the nature, size and representativeness of the samples.</li> <li>The bulk density for bulk material must have been measured by methods that adequately account for void spaces (vugs, porosity, etc). moisture and differences between rock and</li> </ul>	Specific gravity values for the Petowal Prospect have been measured based on the Archimedean Principle using the immersion method for individual core samples. A total of 16,078 density measurements were available for use, with the vast majority of these being in fresh rock below the saprock and laterite domains. This data has been used as the basis of the block model bulk density
	<ul> <li>alteration zones within the deposit.</li> <li>Discuss assumptions for bulk density estimates used in the evaluation process of the different materials.</li> </ul>	Visual inspection shows a clear relationship between lithology and density in fresh rock. No relationship between density and sulphur content or gold content could be established.
		A default bulk density of 1.70t/m <sup>3</sup> was assigned to the thin laterite horizon capping the deposit and to the underlying saprock.
		A default bulk density of 2.46t/m <sup>3</sup> was assigned to soft (oxidised?) rock.
		In fresh rock, Ordinary Kriging was used to estimate density, with the variogram and search neighbourhood being dynamically oriented as per the gold grade estimation. Default values for un- estimated fresh rock were set as undifferentiated rock=2.86t/m <sup>3</sup> ; fresh UBU 2.99t/m <sup>3</sup> ; fresh LBU 2.96t/m <sup>3</sup> and fresh FEL 2.75t/m <sup>3</sup> .
Classification	<ul> <li>The basis for the classification of the Mineral Resources into varying confidence categories.</li> <li>Whether appropriate account has been taken of all relevant factors (i.e. relative confidence in tonnage/grade estimations, reliability of input data, confidence in continuity of geology and metal values, quality, quantity and distribution of the data).</li> <li>Whether the result appropriately reflects the Competent Person's view of the deposit.</li> </ul>	The Measured, Indicated and Inferred classification is based on the confidence in the continuity of geology and mineralisation and quality/confidence in the estimation and quality of assay data and bulk density data. Sectional wireframe interpretations encompass material of Measured and Indicated classification. The classification is Measured where it is informed by 20m spaced drilling on 20m spaced sections or better, the slope of regression estimation quality parameter is greater than 0.8. It is classified as Indicated where it is informed by 20m to 40m



CRITERIA	JORC CODE EXPLANATION	COMMENTARY
		spaced drilling on 40m spaced sections or better, the slope of regression estimation quality parameter is greater than 0.7.
		Inferred classification is informed by 40m spaced drilling on 80m spaced sections, or better.
		The Mineral Resource estimate appropriately reflects the Competent Person's view of the deposit.
Audits or reviews	<ul><li>The results of any audits or reviews of Mineral</li><li>Resource estimates.</li></ul>	No external reviews have been completed.
Discussion of relative accuracy/ confidence	<ul> <li>Where appropriate a statement of the relative accuracy and confidence level in the Mineral Resource estimate using an approach or procedure deemed appropriate by the Competent Person. For example, the application of statistical or geostatistical procedures to quantify the relative accuracy of the resource within stated confidence limits, or, if such an approach is not deemed appropriate, a qualitative discussion of the factors that could affect the relative accuracy and confidence of the estimate.</li> <li>The statement should specify whether it relates to global or local estimates, and, if local, state the relevant tonnages, which should be relevant to technical and economic evaluation. Documentation should include assumptions made and the procedures used.</li> <li>These statements of relative accuracy and confidence of the estimate accuracy and confidence of the appropriate and the procedures used.</li> </ul>	Although the estimate for gold is considered to be without bias, it is for the some of the estimated volume based on relatively wide spaced data. The estimate is therefore of moderate confidence and expected to be of moderate relative accuracy at the local (SMU) scale when drilling density exceeds 20m x 20m. Infill grade control drilling will be required to improve the confidence of the local estimate. The LUC estimate has been compared to ID estimates and in a limited volume to an OK estimate of close spaced grade control drilling. Differences have been identified, however these do not exceed expectations and no material issues have been identified in these comparisons and the LUC estimate appropriately represents the source data.



#### Section 4 Estimation and Reporting of Ore Reserves

CRITERIA	JORC CODE EXPLANATION	COMMENTARY
Mineral Resource estimate for conversion to Ore Reserves	<ul> <li>Description of the Mineral Resource estimate used as a basis for the conversion to an Ore Reserve.</li> <li>Clear statement as to whether the Mineral Resources are reported additional to, or inclusive of, the Ore Reserve.</li> </ul>	Ore Reserves are the material reported as a sub-set of the resource, that which can be extracted from the mine and processed with an economically acceptable outcome. Mineral Resources are reported inclusive of Ore Reserves
Site visits	<ul> <li>Comment on any site visits undertaken by the Competent Person and the outcome of those visits.</li> <li>If no site visits have been undertaken indicate why this is the case.</li> </ul>	The Competent Person, Mr Kitwa Ndjibu, is a full-time employee of Resolute Mining Ltd and a Member of the Australasian Institute of Mining and Metallurgy. He conducted a site visit to the project area in October 2022.
Study status	The type and level of study undertaken to enable Mineral Resources to be converted to Ore Reserves.     The Code requires that a study to at least Bre Ecosibility	A mining study update was conducted by Mining Focus Consultants Pty Ltd in July 2020 based on the 2015 Definitive feasibility study
	<ul> <li>The code requires that a study to a feast Pre-reasibility Study level has been undertaken to convert Mineral Resources to Ore Reserves. Such studies will have been carried out and will have determined a mine plan that is technically achievable and economically viable, and that material Modifying Factors have been considered.</li> </ul>	Mako open pit has been in continuous mining operation since August 2017. During this time the performance of the open pit has shown a positive reconciliation between mineral resources and gold production and delivered positive cashflows.
		Primary contributors to the study were: Mining Eccus Consultants
Cut-off parameters	• The basis of the cut-off grade(s) or quality parameters applied.	A Mill breakeven cut-off grade (COG) change from 0.6 g/t to 0.9 g/t gold has been applied for Mako to account for the increase to the long-term processing costs.
Mining factors or assumptions	<ul> <li>The method and assumptions used as reported in the Pre-Feasibility or Feasibility Study to convert the Mineral Resource to an Ore Reserve (i.e. either by application of appropriate factors by optimization or by preliminary or detailed design).</li> <li>The choice, nature and appropriateness of the selected mining method(s) and other mining parameters including associated design issues such as pre-strip, access, etc.</li> <li>The assumptions made regarding geotechnical parameters (e.g. pit slopes, stope sizes, etc.), grade control and pre-production drilling.</li> <li>The major assumptions made and Mineral Resource model used for pit and stope optimization (if appropriate).</li> <li>The mining dilution factors used.</li> <li>Any minimum mining widths used.</li> <li>The manner in which Inferred Mineral Resources are utilized in mining studies and the sensitivity of the outcome to their inclusion.</li> <li>The infrastructure requirements of the selected mining methods.</li> </ul>	<ul> <li>Mako operations are open pit mining methods. Whittle pit shell optimisations were conducted as component of the mining study.</li> <li>Ground conditions at Mako are good with overall slope angle 55° with batter face angle of 75°.</li> <li>Footwall slope is on average 45 degrees in line with the dip of the orebody.</li> <li>The Resource model was a diluted model; no additional dilution is required.</li> <li>95% Mining recovery used.</li> <li>No Inferred Mineral Resource is included within the Reserve.</li> <li>No additional infrastructure is required for the remaining mine</li> </ul>
Metallurgical factors or assumptions	<ul> <li>The metallurgical process proposed and the appropriateness of that process to the style of mineralization.</li> <li>Whether the metallurgical process is well-tested technology or novel in nature.</li> <li>The nature, amount and representativeness of metallurgical test work undertaken, the nature of the metallurgical domaining applied and the corresponding metallurgical recovery factors applied.</li> <li>Any assumptions or allowances made for deleterious</li> </ul>	<ul> <li>Different recovery is used for different ore types. Basalt and Felsic ore have 90% and 95% recoveries respectively. The mentioned recoveries are in line with current plant performance.</li> <li>Recovery process is well tested and performing to expectation.</li> <li>No deleterious elements, no organics or other elements impacting on Au recovery</li> </ul>



CRITERIA	JORC CODE EXPLANATION	COMMENTARY
	<ul> <li>The existence of any bulk sample or pilot scale test work and the degree to which such samples are considered representative of the ore body as a whole.</li> </ul>	
	<ul> <li>For minerals that are defined by a specification, has the ore reserve estimation been based on the appropriate mineralogy to meet the specifications?</li> </ul>	
Environmental	<ul> <li>The status of studies of potential environmental impacts of the mining and processing operation. Details of waste rock characterization and the consideration of potential sites, status of design options considered and, where applicable, the status of approvals for process residue storage and waste dumps should be reported.</li> </ul>	No acid generation from the waste dumps have been observed in line with test work expectations. No acid forming metallurgy within waste rock material.
Infrastructure	<ul> <li>The existence of appropriate infrastructure: availability of land for plant development, power, water, transportation (particularly for bulk commodities), labour, accommodation; of the ease with which the infrastructure can be provided, or accessed.</li> </ul>	All infrastructure for the Mako project has been completed. Water supply dams, TSF dams have been completed with ongoing TSF lifts planned through the remaining mine life. All power station and camp accommodation infrastructure has been completed.
Costs	• The derivation of, or assumptions made, regarding projected	Royalties paid are variable dependent on gold price At 1500 the
	capital costs in the study.	
	<ul> <li>The methodology used to estimate operating costs.</li> <li>Allowances made for the content of deleterious elements.</li> </ul>	Costs used are taken from mine actuals and Mining contractor
	<ul> <li>The derivation of assumptions made of metal or commodity price(s) for the principal minorals and co. products.</li> </ul>	
	The source of exchange rates used in the study	
	Derivation of transportation charges	
	<ul> <li>The basis for forecasting or source of treatment and refining charges, penalties for failure to meet specification, etc.</li> </ul>	
	The allowances made for royalties payable, both Government and private.	
Revenue factors	<ul> <li>The derivation of, or assumptions made regarding revenue factors including head grade, metal or commodity price(s) exchange rates, transportation and treatment charges, penalties, net smelter returns, etc.</li> </ul>	A gold price of US\$1,500/oz formed the basis of the Ore Reserves. Gold price used for planning purposes are from consensus forecasts provided by external corporate advisers.
	<ul> <li>The derivation of assumptions made of metal or commodity</li> </ul>	No penalties are incurred for deleterious material
	price(s), for the principal metals, minerals and co-products.	No revenue received from co-products.
Market assessment	• The demand, supply and stock situation for the particular commodity, consumption trends and factors likely to affect	The market for gold is robust with prevailing gold price being well above US\$1,500/oz.
	supply and demand into the future.	Supply and demand are not considered material to the Ore Reserve calculations.
	A customer and competitor analysis along with the identification of likely market windows for the product.	
	• Price and volume forecasts and the basis for these forecasts.	
	<ul> <li>For industrial minerals the customer specification, testing and acceptance requirements prior to a supply contract.</li> </ul>	
Economic	• The inputs to the economic analysis to produce the net present value (NPV) in the study, the source and confidence of these economic inputs including estimated inflation, discount rate, etc.	The financial evaluation undertaken as part of the evaluation indicated a positive net present value (NPV) at a 7% annual discount rate. The following major economic inputs were used:



CRITERIA	JORC CODE EXPLANATION	COMMENTARY
	<ul> <li>NPV ranges and sensitivity to variations in the significant assumptions and inputs</li> </ul>	Costs as previously described.
		Gold price of US\$1500/oz.
		• Royalties of 3.5%.
Social	The status of agreements with key stakeholders and matters leading to social license to operate.	The government of Senegal has a 10% free carried interest in the operation.
		No other stakeholder agreements in place.
Other	<ul> <li>To the extent relevant, the impact of the following on the project and/or on the estimation and classification of the Ore Reserves:</li> </ul>	No additional naturally occurring risks. No flood risk, low seismicity risk.
	Any identified material naturally occurring risks.	
	<ul> <li>The status of material legal agreements and marketing arrangements.</li> </ul>	
	<ul> <li>The status of governmental agreements and approvals critical to the viability of the project, such as mineral tenement status, and government and statutory approvals. There must be reasonable grounds to expect that all necessary Government approvals will be received within the timeframes anticipated in the Pre-Feasibility or Feasibility study. Highlight and discuss the materiality of any unresolved matter that is dependent on a third party on which extraction of the reserve is contingent.</li> </ul>	
Classification	<ul> <li>The basis for the classification of the Ore Reserves into varying confidence categories.</li> </ul>	The Ore Reserve estimate appropriately reflects the Competent Person's view of the deposit.
	<ul> <li>Whether the result appropriately reflects the Competent Person's view of the deposit.</li> </ul>	
	<ul> <li>The proportion of Probable Ore Reserves that have been derived from Measured Mineral Resources (if any).</li> </ul>	
Audits or reviews	<ul> <li>The results of any audits or reviews of Ore Reserve estimates.</li> </ul>	
Discussion of relative accuracy/ confidence	<ul> <li>Where appropriate a statement of the relative accuracy and confidence level in the Ore Reserve estimate using an approach or procedure deemed appropriate by the Competent Person. For example, the application of statistical or geostatistical procedures to quantify the relative accuracy of the reserve within stated confidence limits, or, if such an approach is not deemed appropriate, a qualitative discussion of the factors which could affect the relative accuracy and confidence of the estimate.</li> </ul>	
	<ul> <li>The statement should specify whether it relates to global or local estimates, and, if local, state the relevant tonnages, which should be relevant to technical and economic evaluation. Documentation should include assumptions made and the procedures used.</li> </ul>	
	<ul> <li>Accuracy and confidence discussions should extend to specific discussions of any applied Modifying Factors that may have a material impact on Ore Reserve viability, or for which there are remaining areas of uncertainty at the current study stage.</li> </ul>	
	<ul> <li>It is recognized that this may not be possible or appropriate in all circumstances. These statements of relative accuracy and confidence of the estimate should be compared with production data, where available.</li> </ul>	

At 31 December 2022



### Syama North

### Section 1 Sampling Techniques and Data

CRITERIA	JORC CODE EXPLANATION	COMMENTARY
Sampling techniques	<ul> <li>Nature and quality of sampling (e.g. cut channels, random chips, or specific specialised industry standard measurement tools appropriate to the minerals under investigation, such as down hole gamma sondes, or handheld XRF instruments, etc.). These examples should not be taken as limiting the broad meaning of sampling.</li> <li>Include reference to measures taken to ensure sample representivity and the appropriate calibration of any measurement tools or systems used.</li> <li>Aspects of the determination of mineralisation that are Material to the Public Report.</li> <li>In cases where 'industry standard' work has been done this would be relatively simple (e.g. 'reverse circulation drilling was used to obtain 1 m samples from which 3 kg was pulverised to produce a 30 g charge for fire assay'). In other cases more explanation may be required, such as where there is coarse gold that has inherent sampling problems. Unusual commodities or mineralisation types (e.g. submarine nodules) may warrant disclosure of detailed information.</li> </ul>	The samples were collected from reverse circulation (RC) and diamond drill holes. RC samples were collected on 1m intervals by riffle split (dry) or by scoop (wet), to obtain a 1-3kg sample which was sent to the laboratory for crushing, splitting and pulverising to provide a 30g charge for analysis. Following splitting adjacent to the bottom-of-hole orientation line, the right-hand side of the core is sampled in 1m intervals Sampling and sample preparation protocols are industry standard and are deemed appropriate by the Competent Person.
Drilling techniques	<ul> <li>Drill type (e.g. core, reverse circulation, open-hole hammer, rotary air blast, auger, Bangka, sonic, etc.) and details (e.g. core diameter, triple or standard tube, depth of diamond tails, face-sampling bit or other type, whether core is oriented and if so, by what method, etc.).</li> </ul>	Drill types used include reverse circulation with face sampling bit and core drilling using PQ and HQ sized bits. A digital core orientation system is used to define the bottom of the hole which is transferred to the drilled core
Drill sample recovery	<ul> <li>Method of recording and assessing core and chip sample recoveries and results assessed.</li> <li>Measures taken to maximise sample recovery and ensure representative nature of the samples.</li> <li>Whether a relationship exists between sample recovery and grade and whether sample bias may have occurred due to preferential loss/gain of fine/coarse material.</li> </ul>	Appropriate measures are taken to maximise sample recovery and ensure the representative nature of the samples. No apparent relationship is noted between sample recovery and grade.
Logging	<ul> <li>Whether core and chip samples have been geologically and geotechnically logged to a level of detail to support appropriate Mineral Resource estimation, mining studies and metallurgical studies.</li> <li>Whether logging is qualitative or quantitative in nature. Core (or costean, channel, etc.) photography.</li> <li>The total length and percentage of the relevant intersections logged.</li> </ul>	Drill holes were geologically logged by geologists for colour, grainsize, lithology, minerals, alteration and weathering on geologically-domained intervals. Holes were logged in their entirety (100%) and this logging was considered reliable and appropriate.
Sub-sampling techniques and sample preparation	<ul> <li>If core, whether cut or sawn and whether quarter, half or all core taken.</li> <li>If non-core, whether riffled, tube sampled, rotary split, etc. and whether sampled wet or dry.</li> <li>For all sample types, the nature, quality and appropriateness of the sample preparation technique.</li> <li>Quality control procedures adopted for all sub-sampling stages to maximise representivity of samples.</li> <li>Measures taken to ensure that the sampling is representative of the in situ material collected, including for instance results for field duplicate/second-half sampling.</li> <li>Whether sample sizes are appropriate to the grain size of the material being sampled.</li> </ul>	Reverse circulation samples were collected on 1m intervals by riffle split (dry) or by scoop (wet) to obtain a 1-3kg sample. Core samples were sawn using a diamond saw blade with half of the core sent for analysis. Sample preparation includes oven drying, crushing to 10mm, splitting and pulverising to 85% passing -75µm. These preparation techniques are deemed to be appropriate to the material being sampled. Reverse circulation and core field duplicates were collected by the company at a rate of 1:20 samples. Sampling, sample preparation and quality control protocols are of industry standard and all attempts were made to ensure an unbiased representative sample was collected. The methods applied in this process were deemed appropriate by the Competent Person



CRITERIA	JORC CODE EXPLANATION	COMMENTARY
Quality of assay data and laboratory tests	<ul> <li>The nature, quality and appropriateness of the assaying and laboratory procedures used and whether the technique is considered partial or total.</li> <li>For geophysical tools, spectrometers, handheld XRF</li> </ul>	All samples were dispatched to ALS Bamako for gold analysis by 30g fire assay fusion with AAS instrument finish (method code Au-AA25). Over-range results were re-analysed and reported by 30g fire assay fusion with gravimetric finish (method code Au-GRA21). The analytical method was appropriate for the style of mineralisation.
	instruments, etc., the parameters used in determining the analysis including instrument make and model, reading times, calibrations factors applied and their derivation, etc.	No geophysical tools were used to determine elemental concentrations.
	<ul> <li>Nature of quality control procedures adopted (e.g. standards, blanks, duplicates, external laboratory checks) and whether acceptable levels of accuracy (i.e. lack of bias)</li> </ul>	Quality control (QC) procedures included the use of certified standards (1:40), non-certified sand blanks (1:40) and reverse circulation/core field duplicates (1:20).
	and precision have been established.	Laboratory quality control data, including laboratory standards, blanks, duplicates, repeats, grind size results and sample weights were also captured into the digital database.
		Analysis of the QC sample assay results indicates that an acceptable level of accuracy and precision has been achieved.
Verification of sampling and	<ul> <li>The verification of significant intersections by either independent or alternative company personnel.</li> </ul>	Verification of significant intersections have been completed by company personnel and the Competent Person.
assaying	The use of twinned holes.	No drill holes within the resource area were twinned.
	<ul> <li>Documentation of primary data, data entry procedures, data verification, data storage (physical and electronic) protocols.</li> <li>Discuss any adjustment to assay data.</li> </ul>	Drill holes were logged into digital templates with lookup codes, validated and then compiled into a relational SQL 2012 database using DataShed data management software. The database has verification protocols which are used to validate the data entry. The drill hole database is backed up on a daily basis to the head office server
		Assay result files were reported by the laboratory in PDF and CSV format and imported into the SQL database without adjustment or modification.
Location of data points	<ul> <li>Accuracy and quality of surveys used to locate drill holes (collar and down-hole surveys), trenches, mine workings and other locations used in Mineral Resource estimation.</li> </ul>	Collar coordinates were picked up in UTM (WGS84) by staff surveyors using an RTK DGPS with an expected accuracy of +/- 0.05m; elevations were height above EGM96 geoid.
	<ul><li>Specification of the grid system used.</li><li>Quality and adequacy of topographic control.</li></ul>	Down hole surveys were collected at 10m intervals using a Reflex EZ-Gyro north seeking instrument.
		Coordinates and azimuths are reported in UTM WGS84 Zone 29 North.
		Tabakoroni drill holes were translated to local mine grid coordinates using 1 point and rotation.
		Local topographic control is via LIDAR surveys, satellite photography and drone UAV aerial survey.
Data spacing and distribution	<ul> <li>Data spacing for reporting of Exploration Results.</li> <li>Whether the data spacing and distribution is sufficient to</li> </ul>	Drill hole spacing was sufficient to demonstrate geological and grade continuity appropriate for a Mineral Resource and the classifications applied under the 2012 JORC Code.
	establish the degree of geological and grade continuity appropriate for the Mineral Resource and Ore Reserve estimation procedure(s) and classifications applied.	The appropriateness of the drill spacing was reviewed by the geological technical team, both on site and head office. This was also reviewed by the Competent Person.
	Whether sample compositing has been applied.	Samples were collected on 1m intervals; no sample compositing is applied during sampling.
Orientation of	• Whether the orientation of sampling achieves unbiased	Holes were drilled predominantly perpendicular to mineralised domains where possible.
data in relation to geological structure	sampling ot possible structures and the extent to which this is known, considering the deposit type.	No orientation-based sampling bias has been identified in the data.
	<ul> <li>It the relationship between the drilling orientation and the orientation of key mineralised structures is considered to have introduced a sampling bias, this should be assessed and reported if material.</li> </ul>	
Sample security	The measures taken to ensure sample security.	Samples were collected from the drill site and stored on site. All samples were individually bagged and labelled with unique sample identifiers, then securely dispatched to the laboratories. All aspects of



CRITERIA		JORC CODE EXPLANATION	COMMENTARY
			sampling and dispatch process were supervised and tracked by SOMIFI personnel.
Audits or reviews	•	The results of any audits or reviews of sampling techniques and data.	External audits of procedures indicate protocols are within industry standards.



### **Section 2 Reporting of Exploration Results**

CRITERIA	JORC CODE EXPLANATION	COMMENTARY
Mineral tenement and land tenure status	<ul> <li>Type, reference name/number, location and ownership including agreements or material issues with third parties such as joint ventures, partnerships, overriding royalties, native title interests, historical sites, wilderness or national park and environmental settings.</li> <li>The security of the tenure held at the time of reporting along with any known impediments to obtaining a licence to</li> </ul>	Drilling at Syama North was conducted within the Malian Exploitation Concession Permit PE 93/003 which covers an area of 200.6 Km2. Resolute Mining Limited has an 80% interest in the Syama project and the Exploitation Permit PE 93/003, on which it is based, through its Malian subsidiary, Sociêtê des Mines de Syama SA (SOMISY). The Malian Government holds a free carried 20% interest in
	operate in the area.	SOMISY. Tabakoroni drilling was completed within the Finkolo-Tabakoroni Exploitation Licence PE 13/19. Resolute Mining Limited has an 90% interest in Exploitation Permit PE 13/19, through its Malian subsidiary, Société des Mines de Finkolo SA (SOMIFI). The Malian Government holds a free carried 10% interest in SOMIFI. The Permits are held in good standing. Malian mining law provides
		that all Mineral Resources are administered by DNIGM (Direction Nationale de la Géologie et des Mines) or National Directorate of Geology and Mines under the Ministry of Mines, Energy and Hydrology.
Exploration done by other parties	<ul> <li>Acknowledgment and appraisal of exploration by other parties.</li> </ul>	The Syama and Syama North deposits were originally discovered by a regional geochemical survey undertaken by the Direction National de Géologie et des Mines (DNGM) with assistance from the United Nations Development Program (UNDP) in 1985. There had also been a long history of artisanal activities on the hill where an outcropping chert horizon originally marked the present day position of the open pit.
		BHP during 1987-1996 sampled pits, trenches, auger, RC and diamond drill holes across Syama prospects. Randgold Resources Ltd during 1996-2000 sampled pits, trenches, auger, RAB, RC and diamond drill holes across Syama prospects.
Geology	• Deposit type, geological setting and style of mineralisation.	The Syama Project is found on the northern margin of the Achaean- Proterozoic Leo Shield which forms the southern half of the West African Craton. The project area straddles the boundary between the Kadiana–Madinani terrane and the Kadiolo terrane. The Kadiana- Madinani terrane is dominated by greywackes and a narrow belt of interbedded basalt and argillite. The Kadiolo terrane comprises polymictic conglomerate and sandstone that were sourced from the Kadiana-Madinani terrane and deposited in a late- to syntectonic basin.
		Prospects are centred on the NNE striking, west dipping, Syama- Bananso Fault Zone and Birimian volcano-sedimentary units of the Syama Formation. The major commodity being sought is gold.
Drill hole Information	<ul> <li>A summary of all information material to the understanding of the exploration results including a tabulation of the following information for all Material drill holes:</li> </ul>	All information, including easting, northing, elevation, dip, azimuth, coordinate system, drill hole length, intercept length and depth are measured and recorded in UTM Zone 29 WGS84.
	<ul> <li>easting and northing of the drill hole collar</li> </ul>	The Syama belt is mostly located on the Tengrela 1/200,000 topo sheet (Sheet NC 29-XVIII)
	<ul> <li>elevation or RL (Reduced Level – elevation above sea level in metres) of the drill hole collar</li> </ul>	The Tabakoroni local grid has been tied to the UTM Zone 29 WGS84 co-ordinate system.
	o dip and azimuth of the hole	Spectrum Survey & Mapping from Australia established survey
	<ul> <li>down hole length and interception depth</li> <li>Whole length.</li> </ul>	control at Tabakoroni using AusPos online processing to obtain an accurate UTM Zone 29 (WGS84) and 'above geoid' RL for the origin of the output acated points.
	<ul> <li>If the exclusion of this information is justified on the basis that the information is not Material and this exclusion does not detract from the understanding of the report, the Competent Person should clearly explain why this is</li> </ul>	Accuracy of the survey measurements is considered to meet acceptable industry standards.



CRITERIA	JORC CODE EXPLANATION	COMMENTARY
	the case.	Drill hole information has been tabulated for this release in the intercepts table of the accompanying text.
		For completeness the following information about the drill holes is provided:
		<ul> <li>Easting, Northing and RL of the drill hole collars are measured and recorded in UTM Zone 29 (WGS84)</li> </ul>
		• Dip is the inclination of the drill hole from horizontal. A drill hole drilled at -60° is 60° from the horizontal
		• Down hole length is the distance down the inclination of the hole and is measured as the distance from the horizontal to end of hole
		Intercept depth is the distance from the start of the hole down the inclination of the hole to the depth of interest or assayed interval of interest.
Data aggregation methods	<ul> <li>In reporting Exploration Results, weighting averaging techniques, maximum and/or minimum grade truncations (e.g. cutting of high grades) and cut-off grades are usually Material and should be stated.</li> <li>Where aggregate intercents incorporate short lengths of</li> </ul>	<ul> <li>Exploration results reported in this announcement are tabulated using the following parameters:</li> <li>Grid coordinates are WGS84 Zone 29 North</li> <li>Cut-off grade for reporting of intercepts is &gt;=1g/t Au</li> </ul>
	high grade results and longer lengths of low grade results, the procedure used for such aggregation should be stated and some typical examples of such aggregations should be	<ul> <li>No top cut of individual assays prior to length weighted compositing of the reported intercept has been applied</li> </ul>
	<ul> <li>The assumptions used for any reporting of metal equivalent</li> </ul>	Maximum 3m consecutive internal dilution included within the intercept
	values should be clearly stated.	Metal equivalent values are not used in reporting.
Relationship between	<ul> <li>These relationships are particularly important in the reporting of Exploration Results.</li> </ul>	The Syama North mineralisation is steeply dipping at approximately 50 degrees from the horizontal.
mineralisation widths and intercept lengths	<ul> <li>If the geometry of the mineralisation with respect to the drill hole angle is known, its nature should be reported.</li> <li>If it is not known and only the down hole lengths are</li> </ul>	The majority of the drill holes are planned at a general inclination of -60 degrees east and as close to perpendicular to the ore zone as possible.
	<ul> <li>If it is not known and only the down hole lengths are reported, there should be a clear statement to this effect (e.g. 'down hole length, true width not known').</li> </ul>	At the angle of the drill holes and the dip of the ore zones, the reported intercepts will be slightly more than true width.
Diagrams	<ul> <li>Appropriate maps and sections (with scales) and tabulations of intercepts should be included for any significant discovery being reported These should include, but not be limited to a plan view of drill hole collar locations and appropriate sectional views.</li> </ul>	Relevant maps, diagrams and tabulations are included in the body of text.
Balanced reporting	<ul> <li>Where comprehensive reporting of all Exploration Results is not practicable, representative reporting of both low and high grades and/or widths should be practiced to avoid misleading reporting of Exploration Results.</li> </ul>	Exploration results and infill drilling results are being reported in this announcement and tabulated in the body of the text
Other substantive exploration data	<ul> <li>Other exploration data, if meaningful and material, should be reported including (but not limited to): geological observations; geophysical survey results; geochemical survey results; bulk samples – size and method of treatment; metallurgical test results; bulk density, groundwater, geotechnical and rock characteristics; potential deleterious or contaminating substances.</li> </ul>	No geophysical and geochemical data or any additional exploration information has been reported in this release, as they are not deemed relevant to the release.



CRITERIA	JORC CODE EXPLANATION	COMMENTARY
Further work	<ul> <li>The nature and scale of planned further work (e.g. tests for lateral extensions or depth extensions or large-scale step-out drilling).</li> <li>Diagrams clearly highlighting the areas of possible extensions, including the main geological interpretations and future drilling areas, provided this information is not commercially sensitive.</li> </ul>	Future drilling at depth is planned.



#### **Section 3 Estimation and Reporting of Mineral Resources**

CRITERIA	JORC CODE EXPLANATION	COMMENTARY
Database integrity	<ul> <li>Measures taken to ensure that data has not been corrupted by, for example, transcription or keying errors, between its initial collection and its use for Mineral Resource estimation purposes.</li> <li>Data validation procedures used.</li> </ul>	Data have been compiled into a relational SQL database; the setup of this database precludes the loading of data which do not meet the required validation protocols. The data is managed using DataShed© drill hole management software using SQL database techniques. Validation checks are conducted using SQL and DataShed© relational database standards. Data has also been checked against original hard copies for 85% of the data, and where possible, loaded from original data sources.
		Resolute carried out the following basic validation checks on the data supplied prior to resource estimation:
		<ul> <li>Drill holes with overlapping sample intervals;</li> <li>Sample intervals with no assay data or duplicate records;</li> <li>Assay grade ranges;</li> <li>Collar coordinate ranges;</li> <li>Valid hole orientation data.</li> </ul>
Site visits	<ul> <li>Comment on any site visits undertaken by the Competent Person and the outcome of those visits.</li> <li>If no site visits have been undertaken indicate why this is the case.</li> </ul>	The Competent Person – Mr. Patrick Smillie – is a full time employee of Resolute Mining Ltd, and a member of the Society for Mining, Metallurgy & Exploration, visited the site in November of 2022.
Geological interpretation	<ul> <li>Confidence in (or conversely, the uncertainty of) the geological interpretation of the mineral deposit.</li> </ul>	a/The digital database used for the interpretation included logged intervals for the key stratigraphic zones.
	<ul> <li>Nature of the data used and of any assumptions made.</li> <li>The effect, if any, of alternative interpretations on Mineral Resource estimation.</li> <li>The use of geology in guiding and controlling Mineral Resource estimation.</li> </ul>	Drill density (25m by 50m) for the majority of the deposit area allows for interpretation of the geology and mineralized domains. More recent infill/verification drilling of selected more structurally complicated areas, confirms the positions of mineralized zones. Geological and structural controls support modelled mineralized zones.
	• The factors affecting continuity both of grade and geology.	Continuity of mineralization is affected by proximity to structural conduits, stratigraphic position, lithology of key stratigraphic units and porosity of host lithologies.
		The interpretations for the weathering surfaces have been compiled by site geological personnel using the drill hole database and the logs identifying Oxide, Transitional and Fresh material.
Dimensions	<ul> <li>The extent and variability of the Mineral Resource expressed as length (along strike or otherwise), plan width, and depth below surface to the upper and lower limits of the Mineral Resource.</li> </ul>	The Syama North area extends for approximately 6,000 metres in strike and the west dipping gold mineralised zone is between 200- 500 metres in horizontal width. The Mineral Resource is limited in depth by drilling, which extends from surface to a maximum depth of approximately 350 metres vertically.
Estimation and modelling techniques	<ul> <li>The nature and appropriateness of the estimation technique(s applied and key assumptions, including treatment of extreme grade values, domaining, interpolation parameters and maximum distance of extrapolation from data points. If a computer assisted estimation method was chosen include a description of computer software and parameters used.</li> </ul>	Estimation of gold grade has been completed using Ordinary Kriging (OK). The deposit mineralisation has been constrained by wireframes constructed using a combination of downhole gold assay and associated lithological logging. These lode wireframes have been used to define domain codes used for estimation. The drillholes have been flagged with the domain code and composited using the domain code to segregate the data.
	<ul> <li>The availability of check estimates, previous estimates and/or mine production records and whether the Mineral Resource estimate takes appropriate account of such data.</li> </ul>	Domain boundary analysis has been undertaken, with hard boundaries used for all domains.
	The assumptions made regarding recovery of by- products.	

At 31 December 2022



CRITERIA	JORC CODE EXPLANATION	COMMENTARY
	<ul> <li>Estimation of deleterious elements or other variables of economic significance (e.g. su drainage characterization).</li> </ul>	r non-grade Drillholes have been composited to 1m intervals using Leapfrog Iphur for acid mine Geo 2021.2.5 with residual lengths distributed evenly across all composites. There are no residual samples.
	<ul> <li>In the case of block model interpolation, the relation to the average sample spacing and employed.</li> <li>In the case of block model interpolation, the same same same same same same same sam</li></ul>	e block size in d the search The influence of extreme gold assays has been reduced by top- cutting across selected domains. Top-cuts have been determined using a combination of log probability, log histogram, and mean- variance plots. Top-cuts have been reviewed and applied to the
	<ul> <li>employed.</li> <li>Any assumptions behind modelling of selection and the selection of how the geological interpretation the resource estimates.</li> <li>Discussion of basis for using or not using geotropping.</li> <li>The process of validation, the checking procomparison of model data to drill hole data reconciliation data if available.</li> </ul>	<ul> <li>Variography has been determined using Datamine Supervisor v.8.14 software using top-cut values. Where there is insufficient data in individual domains to generate meaningful variograms, domains have been grouped, or variograms borrowed from other similar domains.</li> <li>Drillhole data spacing ranges from 10m spacing in areas of dense drilling to approximately 100m spacing in sparsely drilled, deeper areas.</li> <li>The block model parent block size is 5m (X) by 10m (Y) by 5m (Z) with sub-blocks down to 0.3125m (X) by 0.625m (Y) by 0.3125m (Z), with the sub-blocks estimated at the scale of the parent block. The block size is considered appropriate for the drillhole spacing throughout the deposit.</li> <li>Grade estimation has been completed in three passes:</li> <li>Pass 1 estimation has been undertaken using a minimum and maximum number of sample composites (determined using Datamine Supervisor v.8.14 KNA tool) into a search ellipsoid with dimensions equal to half the variogram range of the domain.</li> </ul>
		<ul> <li>Pass 2 estimation has been undertaken with the same minimum/maximum samples as Pass 1 into a search ellipsoid twice the first pass.</li> <li>Pass 3 estimation has been undertaken with a minimum of 4 samples, and the same maximum number of samples as the first two passes into a search ellipsoid twice the second pass</li> <li>A four drillhole limit has been applied to the passes.</li> <li>Previous Mineral Resource estimates are comparable in size and scope when considering the additional extensional drilling included in the current estimate.</li> </ul>
		The Mineral Resource estimate has been validated using visual validation tools, mean grade comparisons between the block model and declustered composite grade means, and swath plots comparing the input composite grades and the block model grades by Northing, Easting, and RL
		No selective mining units are assumed in the estimate.
		There will be no by-products recovered from mining.
		No additional or deleterious elements have been estimated.
		The model focuses on interpreting mineralisation beneath existing open pits. Historical reconciliation data is incomplete and has not been used.
Moisture	<ul> <li>Whether the tonnages are estimated on a natural moisture, and the method of determ moisture content.</li> </ul>	dry basis or with Tonnages are estimated on a dry basis. No moisture values have been reviewed.
Cut-off parameters	The basis of the adopted cut-off grade(s) of parameters applied.	A cut-off grade of 1.0 g/t Au has been used for construction of mineralised wireframes, based on mining parameters of the nearby Syama and Tabakoroni deposits.

At 31 December 2022



CRITERIA	JORC CODE EXPLANATION	COMMENTARY
Mining factors or assumptions	<ul> <li>Assumptions made regarding possible mining methods, minimum mining dimensions and internal (or, if applicable, external) mining dilution.</li> <li>It is always necessary as part of the process of determining reasonable prospects for eventual economic extraction to consider potential mining methods, but the assumptions made regarding mining methods and parameters when estimating Mineral Resources may not always be rigorous. Where this is the case, this should be reported with an explanation of the basis of the mining assumptions made.</li> </ul>	It is assumed that mining methods would be similar to Resolute's nearby Syama deposit. Mining method for the extraction of gold at Syama was previously by open pit mining excavating benches of 2.5 metres in height. Grade control is conducted on sampling from high quality reverse circulation drilling, spaced at approximately 4mE by 10mN, with samples taken at one and half metre intervals down-hole. Sub-Level Caving (SLC) is used for underground mining at Syama.
Metallurgical factors or assumptions	• The basis for assumptions or predictions regarding metallurgical amenability. It is always necessary as part of the process of determining reasonable prospects for eventual economic extraction to consider potential metallurgical methods, but the assumptions regarding metallurgical treatment processes and parameters made when reporting Mineral Resources may not always be rigorous. Where this is the case, this should be reported with an explanation of the basis of the metallurgical assumptions made.	Extensive metallurgical investigations and reporting have been completed prior to the commencement of mining and milling at the nearby Syama deposit. The processing method involves crushing, milling, flotation and roasting, followed by conventional CIL recovery. There is no evidence to suggest that the metallurgical characteristics of ore extracted from Syama North would change from that encountered at Syama.
Environmental factors or assumptions	<ul> <li>Assumptions made regarding possible waste and process residue disposal options. It is always necessary as part of the process of determining reasonable prospects for eventual economic extraction to consider the potential environmental impacts of the mining and processing operation. While at this stage the determination of potential environmental impacts, particularly for a green fields project, may not always be well advanced, the status of early consideration of these potential environmental impacts should be reported. Where these aspects have not been considered this should be reported with an explanation of the environmental assumptions made.</li> </ul>	It is assumed that environmental factors would be largely similar to those at the nearby Syama Deposit. It is a requirement of Decree No.03-594/P-RM of 31 December 2003 of Malian law that an Environmental and Social Impact Study (Étude d'Impact Environmental et Social – EIES) must be undertaken to update the potential environmental and social impacts of the mine's redevelopment. In November 2007 the EIES for the Syama Gold Mine was approved and an Environment and Social/(07-0054/MEA – SG) issued by the Ministry of Environment and Sanitation on the 22 November 2007.
		At Syama there are three key practices for disposal of wastes and residues namely, stacking of waste rock from open pit mining; storage of tailings from mineral processes; and "tall-stack dispersion" of sulphur dioxide from the roasting of gold bearing concentrate.
		The Environmental & Social Impact Study – "Société des Mines de Syama, Syama Gold Mine, Mali, dated 2007, found "a minimal potential for acid drainage from waste rock, as historical analysis indicates that the high carbonate content of the material will suppress any potential acid generation." Progressive rehabilitation of waste rock landforms has begun and a management plan for waste rock dumping is the subject of ongoing development.
		The landform of tailings impoundments does not have a net acid generating potential. The largest volume is flotation tailings where the sulphide minerals have already been removed from the host rock. Its mineralogy includes carbonates which further buffer any acid-formation potential from sulphides that may also be present.
		Cyanide levels in the leached-calcine tailings are typically less than 50 ppm in the weak acid dissociable form. Groundwater away from the tailings landform is intercepted by trenches and sump pumps.
		Sulphur dioxide is generated from the roasting of gold concentrate so that gold can be extracted and refined. Tall-Stack "dispersion" of the sulphur dioxide emission is monitored continuously. Prevailing weather and dissipation of the sulphur dioxide is modelled daily to predict the need to pause the roasting process in order to meet the air quality criteria set out in the Environmental & Social Impact Study

Bulk density

Whether assumed or determined. If assumed, the basis for the Bulk density values have been determined through analysis of rock assumptions. If determined, the method used, whether wet or and diamond core samples.

*dry, the frequency of the measurements, the nature, size and representativeness of the samples.* A total of 576 bulk density measurements have been gathered using the water immersion method.



CRITERIA	JORC CODE EXPLANATION	COMMENTARY
	<ul> <li>The bulk density for bulk material must have been measured by methods that adequately account for void spaces (vugs, porosity, etc), moisture and differences between rock and alteration zones within the deposit.</li> </ul>	An average bulk density value has been assigned to each of the oxide, transitional, and fresh material across the deposit
	<ul> <li>Discuss assumptions for bulk density estimates used in the evaluation process of the different materials.</li> </ul>	
Classification	The basis for the classification of the Mineral Resources into varying confidence categories.	Mineral Resources were classified in accordance with the Australasian Code for the Reporting of Exploration Results, Mineral Resources and Ore Reserves (JORC, 2012).
	<ul> <li>Whether appropriate account has been taken of all relevant factors (i.e. relative confidence in tonnage/grade estimations, reliability of input data, confidence in continuity of geology and metal values, quality, quantity and distribution of the data)</li> </ul>	The deposit has been classified as Measured, Indicated, and Inferred Mineral Resource based on a combination of quantitative and qualitative criteria which include geologic continuity, confidence
	Whether the result appropriately reflects the Competent Person's view of the deposit.	in volume models, data quality, sample spacing, lode continuity, and estimation parameters (number of informing composites, estimation pass number, kriging quality parameters, and minimum and average distance composites).
		The Measured portion of the Resource was defined using areas populated on the first estimation pass, within 20m of informing composites; the kriging efficiency and slope of regression were generally $>=0.7$ ; and high confidence exists in lode continuity (strike and thickness).
		The Indicated portion of the Resource was defined using areas populated on the first two estimation passes within 50m of informing composites; the kriging efficiency and slope of regression were generally $>=0.7$ ; and moderate to high confidence exists in lode continuity (strike and thickness).
		Mineralisation that not classified by the above parameters has been classified as Inferred.
		The input data is comprehensive in its coverage and does not favour or misrepresent the in situ mineralisation. The definition of the mineralised zones is based on a high level of geologic understanding from good quality sample data, producing models of continuous mineralised lodes. Validation of the block model shows good correlation of the input data to the block estimated grades.
		The Mineral Resource estimate appropriately reflects the view of the Competent Person
Audits or reviews	<ul><li>The results of any audits or reviews of Mineral</li><li>Resource estimates.</li></ul>	No external reviews have been completed.
Discussion of relative accuracy/ confidence	<ul> <li>Where appropriate a statement of the relative accuracy and confidence level in the Mineral Resource estimate using an approach or procedure deemed appropriate by the Competent Person. For example, the application of statistical or geostatistical procedures to quantify the relative accuracy of the resource within stated confidence limits, or, if such an approach is not deemed appropriate, a qualitative discussion of the factors that could affect the relative accuracy and confidence of the estimate.</li> <li>The statement should specify whether it relates to global or local estimates, and, if local, state the relevant tonnages, which should be relevant to technical and economic evaluation. Documentation should include assumptions made and the procedures used.</li> <li>These statements of relative accuracy and confidence of the estimate should be compared with production data, where</li> </ul>	The relative accuracy of the Mineral Resource estimate is reflected in the reporting of Measured, Indicated and Inferred as per the guidelines of the 2012 JORC Code.



#### Section 4 Estimation and Reporting of Ore Reserves

CRITERIA	JORC CODE EXPLANATION	COMMENTARY
Mineral Resource estimate for conversion to Ore Reserves	<ul> <li>Description of the Mineral Resource estimate used as a basis for the conversion to an Ore Reserve.</li> <li>Clear statement as to whether the Mineral Resources are reported additional to, or inclusive of, the Ore Reserve.</li> </ul>	The Ore Reserves are based on the Mineral Resource estimate detailed in the ASX release dated January 2023. The resource was reported above a 1.0 g/t gold grade cut-off, based on an equivalent gold price of US\$2,000/oz and using an Open pit mining methodology. The Material below this cut-off is not included in the Mineral Resource.
		Ore Reserves are the Material reported as a sub-set of the resource, that which can be extracted from the region and processed with an economically acceptable outcome.
Site visits	<ul> <li>Comment on any site visits undertaken by the Competent Person and the outcome of those visits.</li> <li>If no site visits have been undertaken indicate why this is the page</li> </ul>	The Competent Person, Mr Kitwa Ndjibu, is a full-time employee of Resolute Mining Ltd and a Member of the Australasian Institute of Mining and Metallurgy.
	trie case.	Regular site visit to the project area was conducted during the year 2022, and weekly contact with site teams was maintained throughout the period. These site visits help to validate technical and operating assumptions used in the preparation of these ore reserves
		The site visit reviewed the project site and proposed waste dump location, a review of current operations at Syama and Tabakoroni, existing open pit infrastructure available, a review of selected drill core and various meetings were held with site personnel key stakeholders to the study.
Study status	The type and level of study undertaken to enable Mineral     Descurses to be converted to Ore Descurses	Syama North Consist of A21, Beta, Alpha & Ba04.
	<ul> <li>The Code requires that a study to at least Pre-Feasibility Study level has been undertaken to convert Mineral Resources to Ore Reserves. Such studies will have been carried out and will have determined a mine plan that is technically achievable and economically viable, and that material Modifying Factors have been considered.</li> </ul>	Feasibility Studies were completed for mining of Open pit satellite deposits in 2009, and mining of satellite pits has been occurring since then. Recent drilling in Syama North has identified a significant resource in sulphide, spread across the Syama North region, an extension to the known oxide deposit. Additional drilling was completed targeting the A21 area and the resource model was updated in Dec 22 with additional information. Pit was reoptimized using the new model and redesigned to match the latest optimisation. All Reserves were declared as Probable as more test works and drilling is ongoing to firm up the modifying factors (geotechnical inputs).
		The work undertaken to date has addressed all material Modifying Factors required for the conversion of a Mineral Resources estimate into an Ore Reserve estimate and has shown material change to the reserve; i.e, change in tonnes, grades, rock type (Oxide; Transisitional and Fresh). Furthermore, the result shows that the mine plan is technically feasible and economically viable.
Cut-off parameters	• The basis of the cut-off grade(s) or quality parameters applied.	Syama North uses a cut-off of 1.0 g/t, based on the economic parameters described in subsequent sections.
Mining factors or assumptions	<ul> <li>The method and assumptions used as reported in the Pre-Feasibility or Feasibility Study to convert the Mineral Resource to an Ore Reserve (i.e. either by application of appropriate factors by optimization or by preliminary or detailed design).</li> </ul>	The reported Ore Reserve estimates for Syama North are based on pit optimisations conducted using the Lerchs-Grossman (LG) algorithm utilizing the NPV Scheduler and reviewed in Whittle to calculate the optimal pit at specific input parameters and pit designs. Costs are based on existing contract mining and haulage rates and site costs which are understood with a high degree of
	<ul> <li>The choice, nature and appropriateness of the selected mining method(s) and other mining parameters including associated design issues such as pre-strip, access, etc.</li> </ul>	accuracy. Mining is planned to be undertaken by conventional open pit methods of drill and blast, followed by load and haul.



CRITERIA	JORC CODE EXPLANATION	COMMENTARY
	<ul> <li>The assumptions made regarding geotechnical parameters (e.g. pit slopes, stope sizes, etc.), grade control and pre-production drilling.</li> <li>The major assumptions made and Mineral Resource model used for pit and stope optimization (if appropriate).</li> <li>The mining dilution factors used.</li> <li>The mining recovery factors used.</li> <li>Any minimum mining widths used</li> </ul>	Detailed pit design work was completed based on pit optimisation: result. Only Measured and Indicated Resources were used in the pit optimisation. Overall slope angles are dependent on rock type; approximately 34° for Oxide, 38° for Transisitional and 50° for Fresh as recommended by Geotechnical consultants and operational experience in mining other similar pits in same region.
	<ul> <li>The manner in which Inferred Mineral Resources are utilized in mining studies and the sensitivity of the outcome to their inclusion.</li> <li>The infrastructure requirements of the selected mining methods.</li> </ul>	A 5% dilution and 10 % mining loss factor applied. All Inferred material is treated as waste and is excluded from Reserve Reporting. Inferred Mineral Resources are not included in the pit optimisation and pit design. A mining and production schedule were completed with Inferred Mineral Resource treated as waste. As a result, the conversion of Inferred Mineral Resource to processed product is not required for the overall financial viability of the project.
Metallurgical factors or assumptions	<ul> <li>The metallurgical process proposed and the appropriateness of that process to the style of mineralization.</li> <li>Whether the metallurgical process is well-tested technology or novel in nature.</li> <li>The nature, amount and representativeness of metallurgical test work undertaken, the nature of the metallurgical domaining applied and the corresponding metallurgical recovery factors applied.</li> <li>Any assumptions or allowances made for deleterious elements.</li> <li>The existence of any bulk sample or pilot scale test work and the degree to which such samples are considered representative of the ore body as a whole.</li> <li>For minerals that are defined by a specification, has the ore reserve estimation been based on the appropriate mineralogy to meet the specifications?</li> </ul>	<ul> <li>Metallurgical test work was conducted on multiple samples. The tests indicated that, similarly to the Syama ore. The processing of the ore will be similar to that of the Syama sulphide circuit which has been in operation for several years and is well understood, consisting of the following stages: <ul> <li>Crushing and grinding utilising the existing oxid process plant infrastructure</li> <li>Gravity gold recovery utilising the existing oxide gravit circuit</li> <li>Flotation to produce a sulphide rich concentrate</li> <li>Concentrate thickening</li> <li>Roasting, followed by calcine quench and wash</li> <li>Carbon-in-leach (CIL)</li> <li>Tailings disposal</li> </ul> </li> <li>The oxide crushing and grinding circuit has an oxide capacity of 1.6 Mtpa, and Sulphide crushing &amp; grinding has a sulphide capacity of 2.4 Mtpa. PFS study is underway to expand the oxid circuit to a dual feed circuit to feed additional Sulphide ore once the oxide ore depletes.</li> <li>The Syama roaster, CIL circuit and tailings storage facility has enough capacity to process the additional concentrate from Syama North Sulphide ore stream.</li> <li>A total gold recovery of 86%, 80% and 78%, has been assumed for Oxide, Transitional and Fresh Material respectively, based or test results to date. This is in line with similar ore being processed at Syama.</li> </ul>
Environmental	• The status of studies of potential environmental impacts of the mining and processing operation. Details of waste rock characterization and the consideration of potential sites, status of design options considered and, where applicable, the status of approvals for process residue storage and waste dumps should be reported.	An active waste rock characterisation program has been put in place. Potentially Acid Forming (PAF) and Non Acid Forming (NAF) will be identified for waste material dumping in light of closure plan consideration. Ore from these pits will be processed at Syama and tailings
Infrastructure	• The existence of appropriate infrastructure: availability of land for plant development, power, water, transportation (particularly for bulk commodities), labour, accommodation; or the ease with which the infrastructure can be provided, or accessed.	These pits will be supported by existing infrastructure at Syama as they are close to the main facility.
Costs		The Syama North pits are located within approximately 8km of Syama. Ore is trucked to Syama where it is processed at Syama.



CRITERIA	JORC CODE EXPLANATION	COMMENTARY
	The derivation of, or assumptions made, regarding projected capital costs in the study.     The methodology used to estimate operating costs	General and administration costs are shared between the oxide plant and the sulphide plant. As part of ongoing operations, capital and operating budgets are prepared from first principles and
	<ul> <li>Allowances made for the content of deleterious elements</li> </ul>	considering existing contractual agreements.
	<ul> <li>The derivation of assumptions made of metal or commodity price(s), for the principal minerals and co- products.</li> </ul>	The processing plant produces gold doré (without problematic deleterious elements) that is subsequently refined offsite. Refining
	• The source of exchange rates used in the study.	costs are not material.
	Derivation of transportation charges.	Exchange rates used for planning purposes are from
	<ul> <li>The basis for forecasting or source of treatment and refining charges, penalties for failure to meet specification, etc.</li> </ul>	consensus forecasts provided by external corporate advisers.
	<ul> <li>The allowances made for royalties payable, both Government and private.</li> </ul>	Ad valorem Government royalties of 6% are payable on gold production
Revenue factors	<ul> <li>The derivation of, or assumptions made regarding revenue factors including head grade, metal or commodity price(s) exchange rates, transportation and treatment charges, penalties, net smelter returns, etc.</li> </ul>	A gold price of US\$1,500/oz formed the basis of the Ore Reserves. Gold prices used for planning are from consensus forecasts provided by external corporate advisers.
	<ul> <li>The derivation of assumptions made of metal or commodity price(s), for the principal metals, minerals and co-products.</li> </ul>	No penalties are incurred, nor is any revenue received from co- products.
Market assessment	<ul> <li>The demand, supply and stock situation for the particular commodity, consumption trends and factors likely to affect supply and demand into the future.</li> </ul>	The gold market is robust with the prevailing gold price being well above US\$1,500/oz.
	supply and demand into the future.	Supply and demand are not considered material to the Ore Reserve calculations.
	• A customer and competitor analysis along with the identification of likely market windows for the product.	
	• Price and volume forecasts and the basis for these forecasts.	
	<ul> <li>For industrial minerals the customer specification, testing and acceptance requirements prior to a supply contract.</li> </ul>	
Economic	<ul> <li>The inputs to the economic analysis to produce the net present value (NPV) in the study, the source and confidence of these economic inputs including estimated inflation, discount rate, etc.</li> </ul>	The financial evaluation undertaken as part of the evaluation indicated a positive net present value (NPV) at a 7% annual discount rate. The following major economic inputs were used:
	<ul> <li>NPV ranges and sensitivity to variations in the significant assumptions and inputs.</li> </ul>	<ul> <li>Costs as previous described</li> <li>Gold price of US\$1500/oz</li> <li>Povaltice of 6%</li> </ul>
		<ul> <li>Effective tax rate of 25% (Corporate tax rate of 30% with 5% discount provided by the Malian government to Tabakoroni)</li> <li>Discount rate of 7% per annum for real, post-tax cash flows</li> </ul>
Social	The status of agreements with key stakeholders and matters	The Syama North Pits fall within the Syama exploitation permit
	leading to social license to operate.	and will be managed and operated by SOMISY SA. Development of the Northern pits requires updating of the SOMISY ESIA. The ESIA process requires consultation with local community and government leadership and other relevant stakeholders. Engagement will continue up to and during operations including the payment of compensation to farmers whose fields are disturbed as per Malian legal requirements.
		Malian nationals are anticipated to fill most operating and management positions related to the Southern Satellite open pits. The intention is to encourage economic development within the local community

At 31 December 2022



CRITERIA	JORC CODE EXPLANATION	COMMENTARY
Other	<ul> <li>To the extent relevant, the impact of the following on the project and/or on the estimation and classification of the Ore Reserves:</li> <li>Any identified material naturally occurring risks.</li> <li>The status of material legal agreements and marketing arrangements.</li> <li>The status of governmental agreements and approvals critical to the viability of the project, such as mineral tenement status, and government and statutory approvals. There must be reasonable grounds to expect that all necessary Government approvals will be received within the timeframes anticipated in the Pre-Feasibility or Feasibility study. Highlight and discuss the materiality of any unresolved matter that is dependent on a third party on which extraction of the reserve is contingent.</li> </ul>	All current government agreements and approvals are in good standing and no anticipated changes are expected. Political instability is a potential risk in Mali, but the owner has many years operating experience in this environment through the current Syama and Tabakoroni operations. The current Malian government is supportive of mining operations and the current Syama and Tabakoroni operations are in good standing with the authorities. There are no current unresolved matters affecting this project.
Classification	<ul> <li>The basis for the classification of the Ore Reserves into varying confidence categories.</li> <li>Whether the result appropriately reflects the Competent Person's view of the deposit.</li> <li>The proportion of Probable Ore Reserves that have been derived from Measured Mineral Resources (if any).</li> </ul>	Proved and Probable Ore Reserves were declared based on the Measured and Indicated Mineral Resources. The Ore Reserve estimate appropriately reflects the Competent Person's view of the deposit. None of the Measured Mineral Resource was converted to Proven Ore Reserves as the PFS study for plant expansion is underway.
Audits or reviews	<ul> <li>The results of any audits or reviews of Ore Reserve estimates.</li> </ul>	No external audits of Resources/Reserves were undertaken.
Discussion of relative accuracy/ confidence	<ul> <li>Where appropriate a statement of the relative accuracy and confidence level in the Ore Reserve estimate using an approach or procedure deemed appropriate by the Competent Person. For example, the application of statistical or geostatistical procedures to quantify the relative accuracy of the reserve within stated confidence limits, or, if such an approach is not deemed appropriate, a qualitative discussion of the factors which could affect the relative accuracy and confidence of the estimate.</li> <li>The statement should specify whether it relates to global or local estimates, and, if local, state the relevant tonnages, which should be relevant to technical and economic evaluation. Documentation should include assumptions made and the procedures used.</li> </ul>	The relative accuracy and confidence of the Ore Reserve estimate is inherent in the Ore Reserve Classification. All the parameters assumed and adopted along with financial modelling and analysis have been subject to internal peer review.
	<ul> <li>Accuracy and confidence discussions should extend to specific discussions of any applied Modifying Factors that may have a material impact on Ore Reserve viability, or for which there are remaining areas of uncertainty at the current study stage.</li> <li>It is recognized that this may not be possible or appropriate in all circumstances. These statements of relative accuracy and confidence of the estimate should be compared with production data, where available.</li> </ul>	